

Recommended nomenclature for zeolite minerals: report of the subcommittee on zeolites of the International Mineralogical Association, Commission on New Minerals and Mineral Names

DOUGLAS S. COOMBS (Chairman)

Geology Department, University of Otago, P.O. Box 56, Dunedin, New Zealand

ALBERTO ALBERTI

Istituto di Mineralogia, Università di Ferrara, Corso Ercole I° d'Este, 32, I-44100, Italy

THOMAS ARMBRUSTER

Laboratorium für chemische und mineralogische Kristallographie, Universität Bern, Freiestrasse 3, CH-3012 Bern, Switzerland

GILBERTO ARTIOLI

Dipartimento di Scienze della Terra, Università di Milano, via Botticelli, 23, I-20133 Milano, Italy

CARMINE COLELLA

Dipartimento di Ingegneria dei Materiali e della Produzione, Università Federico II di Napoli, Piazzale V. Tecchio 80, I-80125 Napoli, Italy

ERMANNO GALLI

Dipartimento di Scienze della Terra, Università di Modena, via S. Eufemia, 19, I-41100 Modena, Italy

JOEL D. GRICE

Mineral Sciences Division, Canadian Museum of Nature, Ottawa, Ontario K1P 6P4, Canada

FRIEDRICH LIEBAU

Mineralogisch-Petrographisches Institut, Universität Kiel, Olshausenstrasse 40, D-24098 Kiel, Germany

JOSEPH A. MANDARINO (retired from Subcommittee, December, 1994)

Department of Mineralogy, Royal Ontario Museum, Toronto, Ontario M5S 2C6, Canada

HIDEO MINATO

5-37-17 Kugayama, Suginami-ku, Tokyo 168, Japan

ERNEST H. NICKEL

Division of Exploration and Mining, CSIRO, Private Bag, Wembley 6014, Western Australia, Australia

ELIO PASSAGLIA

Dipartimento di Scienze della Terra, Università di Modena, via S. Eufemia, 19, I-41100 Modena, Italy

DONALD R. PEACOR

Department of Geological Sciences, University of Michigan, Ann Arbor, Michigan 48109, U.S.A.

SIMONA QUARTIERI

Dipartimento di Scienze della Terra, Università di Modena, via S. Eufemia, 19, I-41100 Modena, Italy

ROMANO RINALDI

Dipartimento di Scienze della Terra, Università di Perugia, I-06100 Perugia, Italy

MALCOLM ROSS

U.S. Geological Survey, MS 954, Reston, Virginia 20192, U.S.A.

RICHARD A. SHEPPARD

U.S. Geological Survey, MS 939, Box 25046, Federal Centre, Denver, Colorado 80225, U.S.A.

EKKEHART TILLMANN

Institut für Mineralogie und Kristallographie, Universität Wien, Althanstasse 14, A-1090, Wien, Austria

AND

GIOVANNA VEZZALINI

Dipartimento di Scienze della Terra, Università di Modena, via S. Eufemia, 19, I-41100 Modena, Italy

ABSTRACT

This report embodies recommendations on zeolite nomenclature approved by the International Mineralogical Association Commission on New Minerals and Mineral Names. In a working definition of a zeolite mineral used for this review, interrupted tetrahedral framework structures are accepted where other zeolitic properties prevail, and complete substitution by elements other than Si and Al is allowed. Separate species are recognized in topologically distinctive compositional series in which different extra-framework cations are the most abundant in atomic proportions. To name these, the appropriate chemical symbol is attached by a hyphen to the series name as a suffix except for the names harmotome, pollucite and wairakite in the phillipsite and analcime series. Differences in space-group symmetry and in order-disorder relationships in zeolites having the same topologically distinctive framework do not in general provide adequate grounds for recognition of separate species. Zeolite species are not to be distinguished solely on Si : Al ratio except for heulandite (Si : Al < 4.0) and clinoptilolite (Si : Al \geq 4.0). Dehydration, partial hydration, and over-hydration are not sufficient grounds for the recognition of separate species of zeolites. Use of the term 'ideal formula' should be avoided in referring to a simplified or averaged formula of a zeolite.

Newly recognized species in compositional series are as follows: brewsterite-Sr, -Ba; chabazite-Ca, -Na, -K; clinoptilolite-K, -Na, -Ca; dachiardite-Ca, -Na; erionite-Na, -K, -Ca; faujasite-Na, -Ca, -Mg; ferrierite-Mg, -K, -Na; gmelinite-Na, -Ca, -K; heulandite-Ca, -Na, -K, -Sr; levyne-Ca, -Na; paulingite-K, -Ca; phillipsite-Na, -Ca, -K; stilbite-Ca, -Na.

Key references, type locality, origin of name, chemical data, IZA structure-type symbols, space-group symmetry, unit-cell dimensions, and comments on structure are listed for 13 compositional series, 82 accepted zeolite mineral species, and three of doubtful status. Herschelite, leonhardite, svetlozarite, and wellsite are discredited as mineral species names. Obsolete and discredited names are listed.

KEYWORDS: zeolite nomenclature, herschelite, leonhardite, svetlozarite, wellsite, brewsterite, chabazite, clinoptilolite, dachiardite, erionite, faujasite, ferrierite, gmelinite, heulandite, levyne, paulingite, phillipsite, stilbite.

Introduction

THE name 'zeolite' was introduced by the Swedish mineralogist Cronstedt in 1756 for certain silicate minerals in allusion to their behaviour on heating in a borax bead (Greek *zeo* = boil; *lithos* = stone). Three such minerals were listed by Haüy (1801), namely stilbite, analcime, and harmotome, together with 'mesotype', which has not survived. Chabazite and leucite had been named even earlier. Nineteen had been described with their present meaning by 1842. Forty-six zeolites were listed by Gottardi and Galli (1985), and new species continue to be described. The first crystal-structure determination of a zeolite was done on analcime (Taylor, 1930); following this, Hey (1930) concluded that zeolites in general have aluminosilicate frameworks with loosely bonded alkali or alkali-earth cations, or both. Molecules of H₂O occupy extra-framework positions. He pointed out the consequential requirements that the molar ratio Al₂O₃:(Ca,Sr,Ba,Na₂,K₂)O = 1 and that O:(Si + Al) = 2 in the empirical formula.

Zeolites have other highly characteristic features developed to varying degrees, notably the potential for reversible low-temperature dehydration, the ability of the dehydrated forms to reversibly absorb other molecules, a tendency towards more or less easy low-temperature exchange of extra-framework cations, and a lack of clear-cut, structurally controlled constraints on end-member compositions in terms of Si:Al ratios within the framework. In some cases, observed extra-framework compositions may be artefacts of cation exchange resulting from human activities in the laboratory or elsewhere, and furthermore, the compositions are not conveniently determined by traditional optical methods. Perhaps for a combination of such reasons, separate names have been given to few zeolites on the basis of the dominant extra-framework cation in solid-solution series. This conflicts with standard practice in most mineral groups and with guidelines of the Commission on New Minerals and Mineral Names (CNMMN) (Nickel and Mandarino, 1987).

With intensification of research and the advent of the electron microprobe, a flood of information on compositions has become available, and with automated single-crystal X-ray diffractometers and other developments, many complexities have been investigated, including order-disorder relationships in the frameworks and associated

changes in unit-cell parameters and symmetry. Thus in the case of analcime, Mazzi and Galli (1978), Teertstra *et al.* (1994), and others have demonstrated a wide range of space-group symmetries associated with different patterns of order in the framework and possible displacive transformations. Sites of extra-framework cations are commonly less well defined in an open, zeolitic structure than in most other minerals, and are variably occupied. Guidelines allowing recognition of separate species depending on the dominant ion occupying each structural site are thus compromised in the case of extra-framework sites in zeolites. Furthermore, changes in the occupancy of such sites can distort the framework to varying degrees, changing the space-group symmetry.

Some minerals meet traditional criteria for zeolites in all respects except that they contain P, Be, or other elements in tetrahedral sites, with consequent departure from the requirement of Hey (1930) that O:(Si + Al) = 2. Other structurally related minerals with zeolitic properties have all tetrahedral sites occupied by elements other than Si and Al. Certain other minerals displaying zeolitic properties depart from traditional requirements for a zeolite in having a framework that is interrupted by some (OH) groups. An example is parthéite, listed by Gottardi and Galli (1985) as a zeolite. Synthesis and structural analysis of materials having zeolitic properties have become major fields of research and have led to a voluminous literature, as has the industrial use of zeolitic materials. The recommendations of an IMA CNMMN subcommittee set up to review zeolite nomenclature are set out below. These recommendations have been adopted by the Commission.

Definition of a zeolite mineral

In arriving at its working definition of a zeolite, the Subcommittee took the view that zeolites in the historical and mineralogical sense are naturally occurring minerals, irrespective of how the term may be applied to synthetic materials and in industry. In the light of advances in mineralogy, the Hey (1930) definition is found to be too restrictive. The Subcommittee gave particular consideration to the following questions. Is more than 50% substitution of elements other than Si and Al permissible in tetrahedral sites? Is the presence of water and of extra-framework cations absolutely essential? Can

'interrupted' framework structures qualify as zeolite minerals? These matters are further discussed in Appendix 1.

Definition: A zeolite mineral is a crystalline substance with a structure characterized by a framework of linked tetrahedra, each consisting of four O atoms surrounding a cation. This framework contains open cavities in the form of channels and cages. These are usually occupied by H₂O molecules and extra-framework cations that are commonly exchangeable. The channels are large enough to allow the passage of guest species. In the hydrated phases, dehydration occurs at temperatures mostly below about 400°C and is largely reversible. The framework may be interrupted by (OH,F) groups; these occupy a tetrahedron apex that is not shared with adjacent tetrahedra.

Application of the definition (see also Appendix 1): Relatively easy exchange of extra-framework cations at relatively low temperature is a characteristic feature of zeolites and zeolitic behaviour, but varies greatly from species to species. Its extent does not provide a convenient basis for the definition of zeolites. In practice, it appears that channels must have a minimum width greater than that of 6-membered rings (i.e. rings consisting of six tetrahedra) in order to allow zeolitic behaviour at normal temperatures and pressures. Framework structures such as in feldspars, nepheline, sodalites, scapolites, melanophlogite, and probably leifite, in which any channels are too restricted to allow typical zeolitic behaviour such as reversible dehydration, molecular sieving, or cation exchange, are not regarded as zeolites.

Framework density, defined as the number of tetrahedral sites in 1000 Å³, was used as the criterion for inclusion in the *Atlas of Zeolite Structure Types* (Meier *et al.*, 1996). However, this criterion provides no evidence that the channels necessary for diffusion are present as well as cages, and it has not been adopted in the present definition.

In some minerals with a tetrahedral framework structure and other zeolitic characteristics as described, namely parthéite, roggianite, maricopaite, and chiavennite, one apex of some tetrahedra is occupied by an (OH) group or F atom instead of being occupied by an O atom. This (OH) group or F atom does not form a bridge with an adjacent tetrahedron. The framework is thus interrupted. Such minerals are here accepted as zeolites.

In terms of the definition adopted, minerals of the cancrinite group can arguably be considered as zeolites. This group has long been regarded by many or most mineralogists as distinct from the zeolites, in part, at least, because of the presence of large volatile anions (e.g. Hassan, 1997). They are not reviewed in the present report. Rather similarly, wenkite contains large cages and channels, but these are blocked by SO₄, Ca, and Ba ions (Wenk, 1973; Merlino, 1974), inhibiting zeolitic behaviour. In addition, no water is lost below 500°C. Wenkite is not listed in this report as a zeolite.

Leucite has seldom been regarded as a zeolite, as it does not display a full range of zeolitic behaviour. Nevertheless, it has the same framework structure as analcime and conforms to the adopted definition. Ammonioleucite can be regarded as an analcime derivative, can be synthesized from analcime by cation exchange, and may have formed naturally by low-temperature replacement of analcime. Leucite and ammonioleucite are included in the list of zeolites, as is kalborsite, a derivative of the edingtonite structure.

Also conforming to the definition adopted are the beryllphosphates pahasapaite and weinebeneite. These contain neither Si nor Al and can be regarded as end-member examples of Si-free zeolites or zeolite phosphates.

Rules for nomenclature of zeolite minerals

In presenting the following rules for nomenclature of zeolite minerals, the Subcommittee feels strongly that they should be viewed as guidelines rather than as being rigidly prescriptive. As stated by Nickel and Mandarino (1987): "It is probably not desirable to formulate rigid rules to define whether or not a compositional or crystallographic difference is sufficiently large to require a new mineral name, and each new mineral proposal must be considered on its own merits". Explanatory notes following the proposed rules or guidelines give examples of how the Subcommittee envisages that rule being applied, but like Nickel and Mandarino, the Subcommittee urges that each case be treated on its merits. In some cases, compelling reasons may exist on grounds of historical usage for retaining an existing name, or other grounds may exist for departing from the rules for giving a new name. Cases arising under Rule 2 are particularly difficult, and require individual consideration.

Rule 1

(a) One or more zeolite minerals having a topologically distinctive framework of tetrahedra and a composition that is distinctive for zeolites having that framework, constitute separate *species*. (b) Zeolites having the same topologically distinctive framework of tetrahedra constitute a *series* when they display a substantial range in composition in which differing extra-framework cations may be the most abundant in atomic proportions. These cations may occupy different extra-framework sites. Such *series* consist of two or more *species* that are distinguished on the basis of the most abundant extra-framework cation.

Application of the rule: Laumontite, for example, has a topologically distinctive framework and a composition which, as far as is currently known, is distinctive in that Ca is always the dominant extra-framework cation. It is a separate zeolite species under Rule 1a. Natrolite, mesolite, and scolecite have the same topologically distinctive framework structure as each other, and have compositions that are distinctive. They also are separate species under Rule 1a.

Zeolites having the topologically distinctive chabazite structure have a range of compositions in which any one of Ca, Na, or K may be the most abundant extra-framework cation. Substantial Sr is in some cases present as well, but so far has never been reported as the most abundant in natural examples. Chabazite is a series consisting of three separate species under Rule 1b. It is known that near-end-member Na, K, Ca, and Sr compositions are readily obtainable by ion exchange from natural Ca-dominant chabazite at 110°C (Alberti *et al.*, 1982a), but this is not the essential criterion for recognition of the natural series.

Mesolite may have either Na or Ca slightly in excess of the other, but the ratio Na:Ca is always close to 1:1. The range of its composition is not regarded as 'substantial', and mesolite is not divided into more than one species on grounds of composition.

Several distinct structural sites for extra-framework cations are recognized in many zeolites, but in view of the relatively loose bonding and specialized problems in establishing the individual site-occupancies, only the total population of extraframework cations should in general be used in defining zeolite species.

Rule 2

(a) Differences in space-group symmetry and in order-disorder relationships in zeolite minerals

having the same topologically distinctive framework do not in general provide adequate grounds for recognition of separate species, but each case should be treated on its merits. (b) In assessing such cases, other factors, such as relationship to chemical composition, should be taken into consideration.

Application of the rule: The Subcommittee found it to be impracticable to formulate quantified criteria for handling problems arising from this rule. Irrespective of decisions that have been made in the past, care should be taken that departures envisaged in Rule 2b from the principle enunciated in Rule 2a are based on grounds that are truly compelling.

Analcime and certain other zeolites exist with several different space-group symmetries, in some cases occurring on a very fine scale in the same hand specimen and with the same chemistry. Even though this may be related to Si,Al ordering, separate species names in these cases are in general not warranted.

Gismondine and garronite are examples of zeolites that have the same topologically distinctive framework. Both have Ca as the dominant extra-framework cation. Their differing space-group symmetry is associated with disordered Si,Al and the presence of significant Na in garronite. They are accepted as separate species. Gobbinsite and amicitte have topologically the same framework structure as gismondine, but are alkali-dominant. Their different space-group symmetries appear to be related to Si,Al disorder in gobbinsite and possible chemical differences, and they are provisionally retained. Barrerite is topologically similar to stilbite and stellerite, but it has different symmetry correlated with the presence of extra cations which cause rotational displacements within the framework (Galli and Alberti, 1975b); it is similarly retained.

Rule 3

Zeolite mineral species shall not be distinguished solely on the basis of the framework Si:Al ratio. An exception is made in the case of heulandite and clinoptilolite; heulandite is defined as the zeolite mineral series having the distinctive framework topology of heulandite and the ratio Si:Al < 4.0. Clinoptilolite is defined as the series with the same framework topology and Si:Al ≥ 4.0.

Application of the rule: Many zeolites have a widely variable Si:Al ratio, but this, in itself, is

not regarded as providing adequate grounds for recognition of separate species. The exception is based on entrenched usage of the names heulandite and clinoptilolite, and their convenience for recognizing an important chemical feature. The cut-off value adopted (following Boles, 1972) is arbitrary in a continuous range of compositions. The usual 50% compositional rule cannot be applied, as there are no clearly defined Si,Al end-member compositions for heulandite and clinoptilolite. Thermal stability has been used by some investigators to distinguish clinoptilolite from heulandite. This is a derivative property, however, suggested by Mumpton (1960) as an aid to identification, and it is not appropriate as the basis for definition. Alietti (1972) and Boles (1972) have shown that there is no gap in composition either in framework or extra-framework cation contents between heulandite and clinoptilolite, and that samples transitional in composition may show intermediate properties in terms of thermal stability.

Rule 4

Dehydration, partial hydration, and over-hydration, whether reversible or irreversible, are not sufficient grounds for the recognition of separate species of zeolite minerals.

Application of the rule: If a new topologically distinctive framework arises from over-hydration or partial dehydration, separate species status would result from application of Rule 1. Leonhardite, a partially and in most cases reversibly dehydrated form of laumontite, is not accepted as a separate mineral species.

Rule 5

Individual species in a zeolite mineral series with varying extra-framework cations are named by attaching to the series name a suffix indicating the chemical symbol for the extra-framework element that is most abundant in atomic proportions, e.g. chabazite-Ca.

The following exceptions are made: (a) On grounds of historical precedence and long-established usage, the name harmotome is retained for the Ba-dominant member of the phillipsite series. (b) On grounds of long-established usage, pollucite is retained as the Cs-dominant zeolite of the analcime structure-type. On grounds of established usage and markedly different space-group symmetry and

Si,Al order related to the extra-framework cation content (Rule 2b), wairakite is retained as the Ca-dominant zeolite of the analcime structure-type. On the other hand, herschelite is suppressed in favour of chabazite-Na (Appendix 2).

Application of the rule: New species arising from Rule 5 that are well authenticated by published data are set out in Table 1. Future proposals for additional new species under this rule should be dealt with as for any other proposal for a new mineral name.

Adoption of a Levinson-style system of suffixes avoids the proliferation of a large number of new and potentially unrelated species names, and ensures that all members of a topologically identical compositional series are indexed together. It has the great advantage that where adequate chemical data are not required or are not available, a mineral can be referred to correctly by an unambiguous series name. The system adopted here is without the brackets (parentheses) used by Levinson (1966) in suffixes for rare-earth minerals.

Substantial amounts of extra-framework cations other than the dominant one may be indicated, if desired, by the use of adjectives such as calcian and sodian, e.g. calcian clinoptilolite-K. Such adjectival modifiers are not part of the formal name of a species.

Informal use is often made of descriptive terms such as calcium chabazite and Ca chabazite, in which the name or symbol of an element is used adjectivally. In conformity with general IMA guidelines, these should not appear in print as mineral names or in hyphenated form. The correct name for the mineral species in this case is chabazite-Ca. Terms such as sodium-substituted chabazite-Ca are suggested for what in effect would be a synthetic chabazite-Na prepared by cation exchange from chabazite-Ca. Chabazite remains the correct name for a member of the chabazite series that is not specifically identified on compositional grounds.

Rule 6

(a) Space-group variants of zeolite mineral species may be indicated by placing the space-group symbol in round brackets (parentheses) after the mineral species name, e.g. analcime (*Ibca*), heulandite-Ca (*C2/m*). (b) Levels of order may be indicated by adjectival use of words such as 'disordered' or 'fully ordered' before the mineral name.

NOMENCLATURE OF ZEOLITE MINERALS

TABLE 1. Newly proposed zeolite species within compositional series

Series	Species name	Series	Species name
brewsterite	brewsterite-Sr brewsterite-Ba	gmelinite	gmelinite-Na gmelinite-Ca gmelinite-K
chabazite	chabazite-Ca chabazite-Na chabazite-K	heulandite	heulandite-Ca heulandite-Na heulandite-K heulandite-Sr
clinoptilolite	clinoptilolite-K clinoptilolite-Na clinoptilolite-Ca	levyne	levyne-Ca levyne-Na
dachiardite	dachiardite-Ca dachiardite-Na	paulingite	paulingite-K paulingite-Ca
erionite	erionite-Na erionite-K erionite-Ca	phillipsite	phillipsite-Na phillipsite-Ca phillipsite-K
faujasite	faujasite-Na faujasite-Ca faujasite-Mg	stilbite	stilbite-Ca stilbite-Na
ferrierite	ferrierite-Mg ferrierite-K ferrierite-Na		

The first-named member of each series is the one to which the original type specimen for the series appears to belong.

Application of the rule: Modifiers as suggested here are not part of the formal name of the mineral.

Accepted zeolite series and species

Zeolites to be elevated to series status and the consequential new species to be recognized on the basis of the most abundant extra-framework cation (Rule 5) are set out in Table 1.

An annotated list of accepted zeolite series and species follows below. In each entry for series, and for those species that are not members of compositional series, a simplified or generalized formula is given in the first line. This is followed by Z, the number of these formula units per unit cell, as given later in the entry. The simplified or generalized formula should be regarded as representative only and should not be regarded as an 'ideal' composition (see next paragraph). Users of the list should bear in mind that the Si : Al ratio, or, more generally, occupancy of tetrahedral

sites by Si, Al, P, Be, Zn, and possibly other elements, varies widely in many zeolites. The total extra-framework cation charge varies accordingly. Major variation in more-or-less exchangeable, extra-framework cations is also a feature of many natural zeolites. Contents of H₂O tend to decrease with increasing number and size of extra-framework cations, as well as with increasing temperature and decreasing P_{H₂O}. Such variations can be vital to petrological, geochemical, environmental, and experimental considerations.

Simplified or generalized formulae of zeolites, e.g. NaAlSi₂O₆·H₂O for analcime, are often referred to as 'ideal' formulae. However, the supposed ideality may be in writers' desire for simplicity, rather than in anything fundamental to the zeolites concerned, and can lead to false assumptions. There is much evidence that the composition of naturally occurring analcime is a function of the chemical environment in which it forms (e.g. Coombs and Whetten, 1967). In environments of low Si activity, as in altered

strongly silica-deficient alkaline rocks, natural analcime approaches an Si:Al ratio of 1.5. The composition in burial metamorphic rocks in equilibrium with quartz appears to be distinctly more Si-rich than the supposed 'ideal' Si:Al value of 2. The evidently metastable equilibrium in natural environments containing siliceous volcanic glass or other source of silica yielding higher activity of Si than coexistence with quartz, leads to analcime with Si:Al approaching 3. Analogous observations apply to heulandite and other zeolites. If 'ideal' is taken to imply equilibrium, it can therefore be concluded that this is a function of the chemical (and $P-T$) environment during crystallization, rather than simply being a function of crystal structure. Differing Si:Al ratios may in turn favour different patterns of order in the framework. Application of the term 'ideal' to simplified or averaged formulae of zeolites should be avoided.

Also given in the first line of each entry is the structure-type code allocated by the Structure Commission of the International Zeolite Association (IZA) and listed in Meier *et al.* (1996). The code consists of three capital letters. A preceding hyphen indicates an interrupted framework of tetrahedra.

The second line of each relevant entry starts with the original reference in which the current name of the mineral, or a near variant of that name, is given, followed by the type locality, or, in the case of descriptions that predate the concept of type localities, the general region of origin of the material on which the name and original description are based, where this is known. The locality is followed by a note on the derivation of the name. Further information on these matters is given by Gottardi and Galli (1985), Clark (1993), and Blackburn and Dennen (1997), but in some cases the information is here revised.

Next is given information on the currently known range in composition of the mineral concerned. This includes known values, or range of values, for T_{Si} , the proportion of tetrahedron sites occupied by Si atoms, as reported in acceptable published analyses. For many zeolites T_{Si} varies widely, and the values reported may not indicate the full range possible, especially in the case of the rarer zeolites.

Much information on zeolite compositions was given by Gottardi and Galli (1985). The present compilation incorporates results of further extensive searches of the literature. A widely used criterion for acceptability of zeolite compositions

is that the value of the balance error function of Passaglia (1970)


$$E\% = 100 \times \frac{(Al + Fe^{3+}) - (Li + Na + K) - 2(Mg + Ca + Sr + Ba)}{(Li + Na + K) + 2(Mg + Ca + Sr + Ba)}$$

should be less than 10%, a figure that is itself arguably excessive. The calculation of $E\%$ may be modified to allow for other suspected cations, such as Fe^{2+} and Cs^+ . The role of Fe causes problems that may not be resolvable. Some Fe reported in zeolites is undoubtedly a contaminant, but there are reasons to suspect that both Fe^{2+} and Fe^{3+} may enter the structures of some zeolites in extra-framework or framework sites, or both.

Space-group symmetry and crystallographic parameters follow. Many accepted zeolite species exist with more than one known space-group symmetry, and these are listed. Variations in space-group symmetry and variations in order-disorder relationships of framework cations are not in themselves adequate evidence for establishing new species (Rule 2). Cell parameters given are as reported for material specified in key references. Cell dimensions of many species vary widely as a result of variable compositions, variable ordering, and differing levels of hydration. Except for a few newly described species, details of structure, including size and orientation of channels, can be obtained for each structure type from Meier *et al.* (1996) and are discussed in Gottardi and Galli (1985).

The accepted series and species are as follows:

Amicite



Alberti *et al.* (1979). Type locality: Höwenegg (a Tertiary melilite nephelinite volcano), Hegau, southwestern Germany. Named after Giovan Battista Amici (1786–1863), inventor of the Amici lens and microscope objectives with a hemispherical front lens.

Both type amicite and the only other known example (Khomyakov *et al.*, 1982) include minor Ca. $T_{Si} = 0.51, 0.49$.

Monoclinic, $I2$, $a = 10.226(1)$, $b = 10.422(1)$, $c = 9.884(1)$ Å, $\beta = 88.32(2)^\circ$.

The framework is characterized by double crankshaft chains as in gismondine (Alberti and Vezzalini, 1979).

Amicite has the same framework topology as gismondine. Si,Al and Na,K distributions are

ordered and lower the symmetry from topological $I4_1/amd$ to real symmetry $I2$.

Ammonioleucite

$(NH_4)[AlSi_2O_6]$ $Z = 16$ ANA
 Hori *et al.* (1986). Type locality: Tatarazawa, Fujioka, Gumma Prefecture, Japan. The name reflects composition and relationship to leucite. Material from the only known locality contains significant K. $T_{Si} = 0.70$.
 Tetragonal, $I4_1/a$, $a = 13.214(1)$, $c = 13.713(2)$ Å.

Analcime


$Na[AlSi_2O_6] \cdot H_2O$ $Z = 16$ ANA
 Haüy (1797, p. 278). Type locality: near Catanes, Cyclopean Isles, Italy (Haüy, 1801, pp. 180–185). Name from Greek roots meaning ‘without strength’, in allusion to the weak electrical effects induced by friction. In most analyses, Na is the only substantial extra-framework cation, but analcime forms a continuous series with pollucite and possibly with wairakite (Seki and Oki, 1969; Seki, 1971, Cho and Liou, 1987). T_{Si} varies widely, 0.59–0.73 (e.g. Coombs and Whetten, 1967). As Si increases, NaAl decreases and H_2O increases. Topological symmetry is cubic, $Ia3d$. Real symmetry variants include:
 cubic, $Ia3d$, $a = 13.725$ Å;
 tetragonal, $I4_1/acd$, $a = 13.723(7)$, $c = 13.686(10)$ Å; $a = 13.721(1)$, $c = 13.735(1)$ Å (Mazzi and Galli, 1978);
 tetragonal, $I4_1/a$;
 orthorhombic, $Ibca$, $a = 13.733(1)$, $b = 13.729(1)$, $c = 13.712(1)$ Å; $a = 13.727(2)$, $b = 113.714(2)$, $c = 13.740(2)$ Å (Mazzi and Galli, 1978);
 monoclinic with 2-fold axis parallel both to pseudo-cubic [100] and [110];
 triclinic, $a = 13.6824(5)$, $b = 13.7044(6)$, $c = 13.7063(5)$ Å, $\alpha = 90.158(3)$, $\beta = 89.569(3)$, $\gamma = 89.543(3)^\circ$ (Hazen and Finger, 1979);
 and probably trigonal; with variable Si,Al order (e.g. Hazen and Finger, 1979; Teertstra *et al.*, 1994).
 The name applies to Na-dominant compositions with this framework structure regardless of the degree and patterns of order.

Barrerite

$Na_2[Al_2Si_7O_{18}] \cdot 6H_2O$ $Z = 8$ STI
 Passaglia and Pongiluppi (1974, 1975). Type locality: Capo Pula, Sardinia, Italy. Named after

Professor Richard M. Barrer (1910–1996) of Imperial College, London, for contributions to the chemistry of molecular sieves.

Also known from Kuiu Island, Alaska (Di Renzo and Gabelica, 1997). T_{Si} in the range 0.77–0.78. The type example has composition:



Orthorhombic, *Amma* or *Ammm*, $a = 13.643(2)$, $b = 18.200(3)$, $c = 17.842(3)$ Å (Passaglia and Pongiluppi, 1974).

The structure is similar to that of stilbite and stellerite, but it has different symmetry as a result of extra cations, which cause rotational displacements within the framework (Galli and Alberti, 1975b).

Bellbergite

$(K,Ba,Sr)_2Sr_2Ca_2(Ca,Na)_4[Al_{18}Si_{18}O_{72}] \cdot 30H_2O$
 $Z = 1$ EAB
 Rüdinger *et al.* (1993). Type and only known locality: Bellberg (or Bellerberg) volcano, near Mayen, Eifel, Germany. Named after the locality. Ca is overall the dominant extra-framework cation. $T_{Si} = 0.51$.
 Hexagonal, possible space-groups $P6_3/mmc$, $P\bar{6}2c$, and $P6_3mc$, $a = 13.244(1)$, $c = 15.988(2)$ Å. The framework structure is as for synthetic zeolite TMA-EAB.

Bikitaite

$Li[AlSi_2O_6] \cdot H_2O$ $Z = 2$ BIK
 Hurlbut (1957). Type locality: Bikita, Zimbabwe. Named after the type locality.
 Two known localities, the bikitaite having very similar compositions. $T_{Si} = 0.67$.
 Monoclinic, $P2_1$, $a = 8.613(4)$, $b = 4.962(2)$, $c = 7.600(4)$ Å, $\beta = 114.45(1)^\circ$ (Kocman *et al.*, 1974). Also triclinic, $P1$, $a = 8.606(1)$, $b = 4.953(1)$, $c = 7.599(1)$ Å, $\alpha = 89.89(2)^\circ$, $\beta = 114.42(2)^\circ$, $\gamma = 89.96(2)^\circ$ (Bissert and Liebau, 1986).
 The framework structure consists of 5-membered rings linked by additional tetrahedra. Its topological symmetry is $P2_1$. The monoclinic $P2_1$ variant of Kocman *et al.* has partly ordered Si,Al distribution; the triclinic $P1$ variant of Bissert and Liebau is highly ordered.

Boggsite

$Ca_8Na_3[Al_{19}Si_{77}O_{192}] \cdot 70H_2O$ $Z = 1$ BOG
 Pluth *et al.* (1989) and Howard *et al.* (1990). Type locality: Basalt above cliff, Goble Creek, south

side of the Neer Road, 0.2 km north of Goble, Columbia County, Oregon, U.S.A. Named after Robert Maxwell Boggs (father) and Russell Calvin Boggs (son), mineral collectors in the Pacific Northwest.

Type boggsite approximates the above formula, with minor Fe, Mg, and K. Boggsite from Mt. Adamson, Antarctica (Galli *et al.*, 1995) approximates $\text{Ca}_6\text{Na}_5\text{K}[\text{Al}_{18}\text{Si}_{78}\text{O}_{192}] \cdot 70\text{H}_2\text{O}$, with minor Fe, Mg, Sr, Ba. $T_{\text{Si}} = 0.81$.

Orthorhombic, *Imma*, $a = 20.236(2)$, $b = 23.798(1)$, $c = 12.798(1)$ Å (Pluth and Smith, 1990).

Si,Al highly disordered.

Brewsterite (series)

$(\text{Sr},\text{Ba})_2[\text{Al}_4\text{Si}_{12}\text{O}_{32}] \cdot 10\text{H}_2\text{O}$ $Z = 1$ BRE
Brooke (1822). Type locality: Strontian, Argyll, Scotland. Named after Sir David Brewster (1781–1868), Scottish natural philosopher who discovered laws of polarization of light in biaxial crystals.

Monoclinic, $P2_1/m$, $P2_1$, or triclinic (Akizuki, 1987a, Akizuki *et al.*, 1996).

The structure is sheet-like parallel to (010) (Perrotta and Smith, 1964).

Brewsterite-Sr

New name for the original species of the series; Sr is the most abundant extra-framework cation. T_{Si} in the range 0.74–0.75.

Monoclinic, $P2_1/m$, $a = 6.793(2)$, $b = 17.573(6)$, $c = 7.759(2)$ Å, $\beta = 94.54(3)^\circ$, for composition $(\text{Sr}_{1.42}\text{Ba}_{0.48}\text{K}_{0.02})[\text{Al}_{4.12}\text{Si}_{11.95}\text{O}_{32}] \cdot n\text{H}_2\text{O}$ (Schlenker *et al.*, 1977a).

On optical grounds, possibly triclinic (Akizuki, 1987a). Refined as triclinic in three separate growth sectors by Akizuki *et al.* (1996).

Partly ordered Si,Al distribution.

Brewsterite-Ba

New name; Ba is the most abundant extra-framework cation.

Proposed type example: the Gouverneur Talc Company's No. 4 wollastonite mine near Harrisville, Lewis County, New York, U.S.A. (Robinson and Grice, 1993). Also Cerchiara mine, Liguria, Italy (Cabella *et al.*, 1993, including structure refinement). T_{Si} in the range 0.73–0.74. Monoclinic, $P2_1/m$ or $P2_1$, $a = 6.780(3)$, $b =$

17.599(9), $c = 7.733(2)$ Å, $\beta = 94.47(3)^\circ$ for type example, containing up to 0.85 Ba per 16 O atoms.

Chabazite (series)

$(\text{Ca}_{0.5}\text{Na},\text{K})_4[\text{Al}_4\text{Si}_8\text{O}_{24}] \cdot 12\text{H}_2\text{O}$

$Z = 1$ (trigonal)CHA

Bosc d'Antic (1792), as 'chabazie'. The source of the original specimen is unclear. The name is from a word 'chabazion' used for an unknown substance in the story of Orpheus.

Ca-, Na-, and K-dominant species occur in that order of frequency, with Sr and Mg occasionally significant, Ba more minor. T_{Si} varies widely, 0.58–0.81.

Topological symmetry of the framework, trigonal ($R\bar{3}m$) where $a \approx 13.2$, $c \approx 15.1$ Å (pseudo-hexagonal cell). Significant deviations to triclinic, $P\bar{1}$, $a \approx 9.4$, $b \approx 9.4$, $c \approx 9.4$ Å, $\alpha \approx 94^\circ$, $\beta \approx 94^\circ$, $\gamma \approx 94^\circ$ (Smith *et al.*, 1964; Mazzi and Galli, 1983).

Partial order leads to the lower symmetry.

Chabazite-Ca

New name for the original and most common species; Ca is the most abundant single extra-framework cation. Other cations vary widely. T_{Si} in the range 0.58–0.80.

$a = 13.790(5)$, $c = 15.040(4)$ Å, for pseudo-hexagonal cell, with composition

$(\text{Ca}_{1.86}\text{Na}_{0.03}\text{K}_{0.20}\text{Mg}_{0.02}\text{Sr}_{0.03})-$

$[\text{Al}_{3.94}\text{Fe}_{0.01}\text{Si}_{8.03}\text{O}_{24}] \cdot 13.16\text{H}_2\text{O}$, from Col de Lares, Val di Fassa, Italy (Passaglia, 1970, #13).

Chabazite-Na

New name; Na is the most abundant single extra-framework cation. Other cations vary widely. T_{Si} in the range 0.62–0.79.

Suggested type locality: biggest 'Fraglione' facing Aci Trezza, Sicily, Italy (Passaglia, 1970, #1). $a = 13.863(3)$, $c = 15.165(3)$ Å, for hexagonal cell, with composition

$(\text{Na}_{3.11}\text{K}_{1.05}\text{Ca}_{0.19}\text{Mg}_{0.06}\text{Sr}_{0.05})-$

$[\text{Al}_{4.53}\text{Fe}_{0.01}\text{Si}_{7.40}\text{O}_{24}] \cdot 11.47\text{H}_2\text{O}$.

Although originally described as containing 'silex, alumina, and potash' (Lévy, 1825), the name *herschelite* has often been applied to chabazite minerals of tabular habit and high Na content. Herschelite should no longer be used as a species name.

Chabazite-K

New name; K is the most abundant single extra-framework cation. Other cations vary widely. T_{Si} in the range 0.60–0.74.

Suggested type specimen: Tufo Ercolano, Ercolano, Naples, Italy (De Gennaro and Franco, 1976), $a = 13.849(3)$, $c = 15.165(3)$ Å, for hexagonal cell, with composition $(K_{2.06}Na_{0.98}Ca_{0.46}Mg_{0.10}Sr_{0.01})-[Fe_{0.08}Al_{4.37}Si_{17.60}O_{24}] \cdot 11.42H_2O$.

Chiavennite

$CaMn[Be_2Si_5O_{13}(OH)_2] \cdot 2H_2O$ Z = 4 CHI
Bondi *et al.* (1983), Raade *et al.* (1983). Type locality: Chiavenna, Lombardy, Italy. Named after type locality.

Limited available data show up to 0.72 Al and 0.15 B in tetrahedral sites, and significant extra-framework Fe and Na (Raade *et al.*, 1983; Langhof and Holstam, 1994). T_{Si} 0.63 – 0.68. Orthorhombic, $Pnab$, $a = 8.729(5)$, $b = 31.326(11)$, $c = 4.903(2)$ Å (Tazzoli *et al.*, 1995). A Ca,Mn beryllsilicate with an interrupted framework of four-connected $[SiO_4]$ and three-connected $[BeO_4]$ tetrahedra.

Clinoptilolite (series)

$(Na,K,Ca_{0.5},Sr_{0.5},Ba_{0.5},Mg_{0.5})_6[Al_6Si_{30}O_{72}] \cdot \sim 20H_2O$
Z = 1 HEU

Schaller (1923, 1932). Type locality: in decomposed basalt at a high point on ridge running east from Hoodoo Mountain, Wyoming, U.S.A. ('crystallized mordenite' of Pirsson, 1890). The name reflects its inclined extinction and supposed similarity in composition to 'ptilolite' (mordenite). Ptilo-, from Greek, alludes to the downy, finely fibrous nature of that mineral.

The cation content is highly variable. Ca-, Na-, and K-dominant compositions are known, and Sr, Ba, and Mg are in some cases substantial. Fe^{2+} and Fe^{3+} are possible constituents. In Pirsson's (1890) analysis, K is the most abundant single cation by a small margin. Clinoptilolite-K is therefore taken as the type species of the series. T_{Si} in the range 0.80–0.84.

Minerals with the same framework topology but with $T_{Si} < 0.80$, $Si/Al < 4.0$ are classified as heulandite, with which clinoptilolite forms a continuous series.

Monoclinic, $C2/m$, or $C2$, or Cm .

Structure refinements by Alberti (1975a) and Armbruster (1993) demonstrate variations in

extra-framework cation sites compared with heulandite and as a function of the extent of dehydration.

Clinoptilolite-K

New name for the original species; K is the most abundant single extra-framework cation. A moderately K-rich clinoptilolite-K was referred to as 'potassium clinoptilolite' by Minato and Takano (1964). T_{Si} in the range 0.80–0.83.

Monoclinic, $C2/m$, $C2$, or Cm , $a = 17.688(16)$, $b = 17.902(9)$, $c = 7.409(7)$ Å, $\beta = 116.50(7)^\circ$, for $(K_{4.72}Na_{0.85}Ca_{0.04}Sr_{0.37}Mg_{0.19}Fe_{0.03}Mn_{0.01})[Al_{6.52}Si_{29.38}O_{72}] \cdot nH_2O$, from an off-shore borehole, Japan (Ogihara and Iijima, 1990).

Clinoptilolite-Na

New name; Na is the most abundant single extra-framework cation. Other cations vary widely. T_{Si} in the range 0.80–0.84.

Suggested type example: Barstow Formation, about 1.6 km east of mouth of Owl Canyon, San Bernardino County, California, U.S.A., USGS Lab. no. D100594 (Sheppard and Gude, 1969a). Monoclinic, $C2/m$, $C2$, or Cm , $a = 17.627(4)$, $b = 17.955(4)$, $c = 7.399(4)$ Å, $\beta = 116.29(2)^\circ$ (Boles, 1972), for type material of Sheppard and Gude (1969a), $(Na_{3.78}K_{1.31}Ca_{0.61}Ba_{0.09}Mg_{0.23}Mn_{0.01})[Al_{6.61}Fe_{0.16}Si_{29.19}O_{72}] \cdot 20.4H_2O$.

Clinoptilolite-Ca

New name; Ca is the most abundant single extra-framework cation. Other cations vary widely. T_{Si} in the range 0.80–0.84.

Suggested type specimen: Kuruma Pass, Fukushima Prefecture, Japan (Koyama and Takéuchi, 1977).

Monoclinic, $C2/m$, $C2$, or Cm , $a = 17.660(4)$, $b = 17.963(5)$, $c = 7.400(3)$ Å, $\beta = 116.47(3)^\circ$ based on $C2/m$, (Koyama and Takéuchi, 1977), for Kuruma Pass specimen, $(Na_{1.76}K_{1.05}Ca_{1.90}Mg_{0.17})[Al_{6.72}Si_{29.20}O_{72}] \cdot 23.7H_2O$.

Cowlesite

$Ca[Al_2Si_3O_{10}] \cdot 5.3H_2O$

Z = 52 (IZA code not assigned)

Wise and Tschernich (1975). Type locality: road cuts 0.6 km northwest of Goble, Columbia County, Oregon, U.S.A. Named after John Cowles of Rainier, Oregon, amateur mineralogist.

Minor substitution for Ca by Na and lesser K, Mg, Sr, Ba, Fe. T_{Si} in the range 0.60–0.62 (Vezzalini *et al.*, 1992).

Orthorhombic, $P222_1$ or $Pmmm$, $Pmm2$, $P2mm$, $P222$ (Nawaz, 1984), $a = 23.249(5)$ $b = 30.629(3)$ $c = 24.964(4)$ Å (Artioli *et al.*, 1987).

Structure and degree of order of framework cations have not been determined.

Dachiardite (series)

$(Ca_{0.5}, Na, K)_{4-5}[Al_{4-5}Si_{20-19}O_{48}] \cdot \sim 13H_2O$

Z = 1 DAC

D'Achiardi (1906). Type locality: San Piero in Campo, Elba, Italy. Named by the author in memory of his father, Antonio D'Achiardi (1839–1902), first full professor of mineralogy at the University of Pisa.

May contain minor Cs and Sr. T_{Si} in the range 0.78–0.86.

Monoclinic, topological symmetry $C2/m$, real symmetry Cm .

The structure consists of complex chains of 5-membered rings cross-linked by 4-membered rings (Gottardi and Meier, 1963), but with complexities that commonly result in diffuse and streaked X-ray diffraction maxima (Quartieri *et al.*, 1990).

Dachiardite-Ca

New name for the original species of the series; Ca is the most abundant extra-framework cation. Dachiardite from the type locality contains 0.12 Cs atoms per formula unit (atoms *pfu*) (Bonardi, 1979). T_{Si} in the range 0.78–0.83.

Monoclinic, topological symmetry $C2/m$, real symmetry Cm , $a = 18.676$, $b = 7.518$, $c = 10.246$ Å, $\beta = 107.87^\circ$, for composition

$(Ca_{1.54}Na_{0.42}K_{0.92}Cs_{0.11}Sr_{0.12}Ba_{0.01})[Al_{4.86}Fe_{0.02}Si_{18.96}O_{48}] \cdot 12.56H_2O$ from the type locality (Vezzalini, 1984).

Partly ordered distribution of Si, Al.

Dachiardite-Na

New name; Na is the most abundant extra-framework cation.

Suggested type example: Alpe di Siusi, Bolzano, Italy (Alberti, 1975b).

Available analyses of material from seven localities, e.g. Bonardi *et al.*, (1981), show considerable variation in Na:K:Ca proportions. T_{Si} in the range 0.81–0.86.

Monoclinic, $a = 18.647(7)$, $b = 7.506(4)$, $c = 10.296(4)$ Å, $\beta = 108.37(3)^\circ$, for

$(Na_{2.59}K_{0.71}Ca_{0.53}Mg_{0.04}Ba_{0.01})[Fe_{0.11}Al_{4.27}Si_{19.61}O_{48}] \cdot 13.43H_2O$ from the type locality (Alberti, 1975b).

Diffuse diffraction spots indicate disorder.

Edingtonite

$Ba[Al_2Si_3O_{10}] \cdot 4H_2O$ Z = 2 EDI

Haidinger (1825). Type locality: Kilpatrick Hills, near Glasgow, Scotland. Named after a Mr Edington of Glasgow, in whose collection Haidinger found the mineral.

Small amounts of K, Na, and Ca may replace Ba. T_{Si} in the range 0.59–0.61.

Orthorhombic, $P2_12_12_1$, $a = 9.550(10)$, $b = 9.665(10)$, $c = 6.523(5)$ Å (Böhlet Mine, Westergotland, Sweden) (Galli, 1976).

Also tetragonal, $P\bar{4}2_1m$, $a = 9.584(5)$, $c = 6.524(3)$ Å (Old Kilpatrick, near Glasgow, Scotland) (Mazzi *et al.*, 1984).

From optical evidence, Akizuki (1986) suggested that a triclinic true symmetry is also possible.

The structure is similar to that of natrolite, but with a distinctive cross-linking of the chains (Taylor and Jackson, 1933; Mazzi *et al.*, 1984). Examples of orthorhombic edingtonite have nearly perfect (Si, Al) order. The tetragonal form is disordered, and available analyses show that slightly more Ba has been replaced by other ions.

Epistilbite

$(Ca, Na_2)[Al_2Si_4O_{12}] \cdot 4H_2O$ Z = 4 EPI

Rose (1826). Type localities: 'Iceland' and 'Farøe Islands'. Named from Greek *epi* in the sense of near, and stilbite, from its supposed similarity to the latter.

Na/(Na + Ca) varies from about 0.1 to 0.3, with minor K and Ba (e.g. Galli and Rinaldi, 1974). T_{Si} in the range 0.72–0.77.


Monoclinic, $C2$, $a = 9.101(2)$, $b = 17.741(1)$, $c = 10.226(1)$ Å, $\beta = 124.66(2)^\circ$ (Teigarhorn, Iceland: Alberti *et al.*, 1985) or:

triclinic, $C1$, $a = 9.083(1)$, $b = 17.738(3)$, $c = 10.209(1)$ Å, $\alpha = 89.95(1)^\circ$, $\beta = 124.58(1)^\circ$, $\gamma = 90.00(1)^\circ$ (Gibelsbach, Valais, Switzerland: Yang and Armbruster, 1996).

The structural framework belongs to the mordenite group (Gottardi and Galli, 1985). Earlier work suggested space-group symmetry $C2/m$ (Perrotta, 1967). Alberti *et al.* (1985)

proposed a domain structure involving acentric configurations of tetrahedra and space group $C2$. Yang and Armbruster (1996) indicated that the proposed domains can be modelled by (010) disorder caused by a local mirror plane, and that increased partial order of Si,Al leads to triclinic symmetry.

Erionite (series)



Eakle (1898). Type locality: Durkee, Oregon, U.S.A., in rhyolitic, welded ash-flow tuff. Name from Greek root meaning wool, in reference to its appearance.

Substantial amounts of any or all of Ca, Na, and K, and subordinate Mg may be present, and there is evidence that trace Fe may enter tetrahedral and extra-framework sites. Eakle's (1898) analysis of type erionite shows Na as the most abundant extra-framework cation; Passaglia *et al.* (in press) found Ca to be the most abundant in a type-locality specimen. T_{Si} in the range 0.68–0.79.

Hexagonal, $P6_3/mmc$, $a = 13.15$, $c = 15.02$ Å (Kawahara and Curien, 1969).

The structure is related to those of offretite, with which it may form intergrowths with stacking faults (Schlenker *et al.*, 1977b), and levyne, on which it forms epitactic growths (Passaglia *et al.*, 1998). The three minerals have 4-, 6- and 8-membered rings. They differ in the stacking of single and double 6-membered rings, resulting in different c dimensions and differently sized and shaped cages. Si,Al disordered.

Erionite-Na

New name; Na is the most abundant extra-framework cation.

Proposed type example: Cady Mountains, California, U.S.A. (Sheppard *et al.*, 1965). T_{Si} in the range 0.74–0.79.

For the type specimen, $a = 13.214(3)$, $c = 15.048(4)$ Å, composition $(Na_{5.59}K_{2.00}Ca_{0.11}Mg_{0.18}Fe_{0.02})[Al_{17.57}Si_{28.27}O_{72}] \cdot 24.60H_2O$ (Sheppard and Gude, 1969b).

Erionite-K

New name; K is the most abundant extra-framework cation.

Proposed type example: Rome, Oregon, U.S.A., in which K makes up 58% of extra-framework

cations; significant Na, Ca, and Mg are also present (Eberly, 1964). T_{Si} in the range 0.74–0.79.

For a specimen from Ortenberg, Germany, $a = 13.227(1)$, $c = 15.075(3)$ Å, $(K_{3.32}Na_{2.31}Ca_{0.99}Mg_{0.06}Ba_{0.02})[Al_{8.05}Si_{28.01}O_{72}] \cdot 31.99H_2O$ (Passaglia *et al.*, 1998).


Erionite-Ca

New name; Ca is the most abundant extra-framework cation.

Proposed type example: Mazé, Niigata Prefecture, Japan (Harada *et al.*, 1967). T_{Si} in the range 0.68–0.79.

For the type example: $a = 13.333(1)$, $c = 15.091(2)$ Å; $(Ca_{2.28}K_{1.54}Na_{0.95}Mg_{0.86})[Al_{8.83}Si_{26.90}O_{72}] \cdot 31.35H_2O$ (Harada *et al.*, 1967).

Faujasite (series)



Damour (1842). Type locality: Sasbach, Kaiserstuhl, Germany. Named after Barthélémy Faujas de Saint Fond, noted for his work on extinct volcanoes.

Major amounts of Na, Ca, and Mg are commonly present, and in some cases, K; minor Sr is also reported. The ratio Si : Al ratios also varies; T_{Si} in the range 0.68–0.74, with one record of 0.64. For most analyses, x in the above generalized formula is in the range 3.2–3.8 with one record of 4.4 (Rinaldi *et al.*, 1975a; Wise, 1982; Ibrahim and Hall, 1995).

Cubic, $Fd\bar{3}m$. $a = 24.65$ Å (material from Sasbach; Bergerhoff *et al.*, 1958).

The framework structure is very open, with complete sodalite-type cages and with very large cavities having 12-membered ring openings. Up to 260 molecules of H_2O can be accommodated per unit cell (Bergerhoff *et al.*, 1958; Baur, 1964).

Faujasite-Na

New name; Na is the most abundant extra-framework cation, as it is in the original (incomplete) and most subsequent analyses of material from the type locality, Sasbach, Kaiserstuhl, and some other localities. T_{Si} in the range 0.70–0.74, with one report of 0.64.

Reported values of a range from 24.638(3) Å (Wise, 1982) to 24.728(2) Å (Ibrahim and Hall, 1995).

Faujasite-Ca

New name; Ca is the most abundant extra-framework cation. Reported T_{Si} in the range 0.68–0.73. Proposed type example: drill core from Haselborn near Ilbeshausen, Vogelsberg, Hessen, Germany (Wise, 1982), composition $(Ca_{1.32}Na_{0.56}Mg_{0.26}K_{0.04}) [Al_{3.83}Si_{8.19}O_{24}] \cdot nH_2O$, $Z = 16$.

Reported values of $a = 24.714(4) \text{ \AA}$ and $24.783(3) \text{ \AA}$ (Jabal Hanoun, Jordan; Ibrahim and Hall, 1995).

Faujasite-Mg

New name; Mg is the most abundant extra-framework cation.

Proposed type (and only) example: 'Old (museum) sample' (# 32, Genth Collection, Pennsylvania State University) from Sasbach, Kaiserstuhl, Germany (anal. #15, Rinaldi *et al.*, 1975a), composition

$(Mg_{15.5}Ca_{4.0}Na_{7.0}K_{6.4}) [Al_{56}Si_{137}O_{384}] \cdot nH_2O$,
 $Z = 1$.

Ferrierite (series)

$(K, Na, Mg_{0.5}, Ca_{0.5})_6 [Al_6Si_{30}O_{72}] \cdot 18H_2O$
 $Z = 1$ FER

Graham (1918). Type locality: Kamloops Lake, British Columbia, Canada. Named after Dr Walter F. Ferrier, mineralogist, mining engineer, and one-time member of the Geological Survey of Canada, who first collected it.

Substantial amounts of any or all of Mg, K, Na, and Ca may be present, and smaller amounts of Fe, Ba, and Sr. T_{Si} in the range 0.80–0.88.

Statistical symmetry, orthorhombic, *Immm*; true symmetries orthorhombic, *Pnmm*, $a = 19.23$, $b = 14.15$, $c = 7.50 \text{ \AA}$ (Alberti and Sabelli, 1987). Also monoclinic, $P2_1/n$, $a = 18.89$, $b = 14.18$, $c = 7.47 \text{ \AA}$, $\beta = 90.0^\circ$ (Gramlich-Meier *et al.*, 1985). The structure was first determined by Vaughan (1966). Framework Si, Al partially ordered (Alberti and Sabelli, 1987).

Ferrierite-Mg

New name for the original member of the series; Mg is the most abundant single extra-framework cation.

Substantial extra-framework Na, K, and lesser Ca commonly present. T_{Si} in the range 0.80–0.84.

True symmetry orthorhombic, *Pnmm*, $a = 19.231(2)$, $b = 14.145(2)$, $c = 7.499(1) \text{ \AA}$ for

specimen from Monastir, Sardinia, of composition $(Mg_{2.02}K_{1.19}Na_{0.56}Ca_{0.52}Sr_{0.14}Ba_{0.02}) [Al_{6.89}Si_{29.04}O_{72}] \cdot 17.86H_2O$ (Alberti and Sabelli, 1987).

Ferrierite-K

New name; K is the most abundant single extra-framework cation.

Proposed type example: Santa Monica Mountains, California, U.S.A., composition $(K_{2.05}Na_{1.14}Mg_{0.74}Ca_{0.14}) [Al_{5.00}Si_{31.01}O_{72}] \cdot nH_2O$ (Wise and Tschernich, 1976, #3).

T_{Si} in the range 0.81–0.87.

Orthorhombic, $a = 18.973(7)$, $b = 14.140(6)$, $c = 7.478(4) \text{ \AA}$ for type specimen.

Ferrierite-Na

New name; Na is the most abundant single extra-framework cation.

Proposed type example: Altoona, Washington, U.S.A., composition $(Na_{3.06}K_{0.97}Mg_{0.38}Ca_{0.05}Sr_{0.03}Ba_{0.02}) [Al_5Si_{31}O_{72}] \cdot 18H_2O$ (Wise and Tschernich, 1976, #1).

T_{Si} in the range 0.85–0.88.

Monoclinic, $P2_1/n$, $a = 18.886(9)$, $b = 14.182(6)$, $c = 7.470(5) \text{ \AA}$, $\beta = 90.0(1)^\circ$ (Gramlich-Meier *et al.*, 1985, for a specimen from Altoona, Washington).

Garronite

$NaCa_{2.5} [Al_6Si_{10}O_{32}] \cdot 14H_2O$ $Z = 1$ GIS

Walker (1962). Type locality: slopes of Glenariff Valley, County Antrim, Northern Ireland. Named after the Garron Plateau, where the type locality is sited.

Ca/(Na + K) is variable, but Ca predominates. Type-locality garronite has about 1.3 Na atoms *pfu*; some others have $(Na + K) < 0.2$ atoms *pfu*. H_2O 13.0–14.0 molecules *pfu*. T_{Si} 0.60–0.65.

The crystal structure has been refined in tetragonal symmetry, $\bar{I}4m2$, $a = 9.9266(2)$, $c = 10.3031(3) \text{ \AA}$, by Artioli (1992), and for a Na-free synthetic garronite, in $I4_1/a$, $a = 9.873(1)$, $c = 10.288(1) \text{ \AA}$, by Schröpfer and Joswig (1997). Orthorhombic symmetry has been proposed on the basis of X-ray diffraction with twinned crystals (Nawaz, 1983) and crystal morphology (Howard, 1994).

The framework topology is the same as for gismondine, but Si and Al are essentially disordered. The different space-group symmetry

(Artioli, 1992) is associated with disorder and the presence of significant Na. Gottardi and Alberti (1974) proposed partial ordering subsequent to growth to explain twin domains.

Gaultite



Ercit and Van Velthuizen (1994). Type locality: Mont Saint Hilaire, Quebec, Canada. Named after Robert A. Gault (b. 1943), mineralogist at the Canadian Museum of Nature, Ottawa, Ontario, Canada.

No other elements detected in the one reported example; $T_{\text{Si}} = 0.78$.

Orthorhombic, $F2dd$, $a = 10.211(3)$, $b = 39.88(2)$, $c = 10.304(4)$ Å.

The zincosilicate framework of tetrahedra is characterized by stacked sheets of edge-sharing 4- and 8-membered rings. The sheets are cross-linked by tetrahedra. Gaultite is isostructural with synthetic zeolite VPI-7 and similar in structure to lovdarite (Ercit and Van Velthuizen, 1994).

Gismondine




von Leonhard (in footnote, 1817), renaming 'zeagonite' of Gismondi (1817). Type locality: Capo di Bove, near Rome, Italy. Named after Carlo Giuseppe Gismondi (1762–1824), lecturer in mineralogy in Rome.

(K + Na) does not exceed 0.12 atoms *pfu*, with K less than 0.08 atoms *pfu*; analyses showing high K result from intergrown phillipsite. Minor Sr may be present. T_{Si} in the range 0.51–0.54 (Vezzalini and Oberti, 1984). H_2O is slightly variable (4.4–4.5 molecules *pfu*) because of mixed 6- and 7-coordination of Ca (Artioli *et al.*, 1986b). Monoclinic, originally refined in $P2_1/a$ by Fischer and Schramm (1970); cell converted to standard $P2_1/c$ second setting is $a = 10.023(3)$, $b = 10.616(5)$, $c = 9.843(15)$ Å, $\beta = 92.42(25)^\circ$. Also refined (two samples) by Rinaldi and Vezzalini (1985).

The framework topology is based on crankshaft chains of 4-membered rings as in feldspars, connected in UDD configuration.

Si,Al are strictly ordered.

Gmelinite (series)



Brewster (1825a). Type locality: the name was proposed for minerals occurring both at Little Deer Park, Glenarm, County Antrim, Northern Ireland, and at Montecchio Maggiore, Vicenza, Italy. Named after Christian Gottlob Gmelin, Professor of Chemistry, University of Tübingen. Na-dominant members are the most common. T_{Si} 0.65–0.72.

Hexagonal, $P6_3/mmc$, $a = 13.62$ – 13.88 , $c = 9.97$ – 10.25 Å.

The structure is similar to that of chabazite, with which it is commonly intergrown (Strunz, 1956), but gmelinite has a different stacking of the double 6-membered rings (Fischer, 1966). Si,Al are disordered.

Gmelinite-Na

New name for the most common species of the series. It occurs in at least one of the gmelinite type localities (Montecchio Maggiore). The Ca content is commonly substantial, K is minor, and Sr is significant in a few analysed samples. T_{Si} in the range 0.65–0.71.

Hexagonal, $P6_3/mmc$, $a = 13.756(5)$, $c = 10.048(5)$ Å (Galli *et al.*, 1982), for near-end-member material from Queensland, Australia, of composition $(\text{Na}_{7.61}\text{Ca}_{0.03}\text{K}_{0.16})[\text{Al}_{7.41}\text{Si}_{16.49}\text{O}_{48}] \cdot 21.51\text{H}_2\text{O}$ (Passaglia *et al.*, 1978a).

Gmelinite-Ca

New name for a species that also occurs in at least one of the type localities (Montecchio Maggiore). Ca is the most abundant single extra-framework cation. Significant to substantial Sr and Na, minor K. T_{Si} in the range 0.68–0.70.

Hexagonal, $P6_3/mmc$, $a = 13.800(5)$, $c = 9.964(5)$ Å (Galli *et al.*, 1982), from Montecchio Maggiore, Vicenza, composition $(\text{Ca}_{2.06}\text{Sr}_{1.35}\text{Na}_{0.78}\text{K}_{0.11})[\text{Al}_{7.82}\text{Si}_{16.21}\text{O}_{48}] \cdot 23.23\text{H}_2\text{O}$ (Passaglia *et al.*, 1978a).

Gmelinite-K

New name; K is the most abundant single extra-framework cation. Proposed type example: Fara Vicentina, Vicenza, Italy, composition $(\text{K}_{2.72}\text{Ca}_{1.67}\text{Sr}_{0.39}\text{Na}_{0.22}\text{Mg}_{0.13})[\text{Al}_{7.79}\text{Si}_{16.32}\text{O}_{48}] \cdot 23.52\text{H}_2\text{O}$ (Vezzalini *et al.*, 1990). Also known from the Kola Peninsula (Malinovskii, 1984).

Hexagonal, $P6_3/mmc$, $a = 13.621(3)$, $c = 10.254(1)$ Å.


Gobbinsite

Nawaz and Malone (1982). Type locality: basalt cliffs near Hills Port, south of the Gobbins area, County Antrim, Northern Ireland. Named after the locality.

Na:Ca:Mg:K variable, with Na greatly predominant, Ca < 0.6 atoms *pfu*. High K analyses result from intergrown phillipsite (Artioli and Foy, 1994). $T_{\text{Si}} = 0.62\text{--}0.68$, substantially higher than in gismondine.

Orthorhombic, $Pmn2_1$, $a = 10.108(1)$, $b = 9.766(1)$, $c = 10.171(1)$ Å for the anhydrous composition ($\text{Na}_{2.50}\text{K}_{2.11}\text{Ca}_{0.59}$) $[\text{Al}_{6.17}\text{Si}_{9.93}\text{O}_{32}]$ from Two-Mouth Cave, County Antrim, Northern Ireland (McCusker *et al.*, 1985); $a = 10.1027(5)$, $b = 9.8016(5)$, $c = 10.1682(6)$ Å for ($\text{Na}_{4.3}\text{Ca}_{0.6}$) $[\text{Al}_{5.6}\text{Si}_{10.4}\text{O}_{32}] \cdot 12\text{H}_2\text{O}$ from Magheramorne quarry, Larne, Northern Ireland (Artioli and Foy, 1994).

The framework topology is the same as for gismondine and is based on crankshaft chains of 4-membered rings, as in feldspars. Distortion from tetragonal topological symmetry results from the arrangement of cations in the channels. Si,Al in the framework are disordered.

Gonnardite

Lacroix (1896). Type locality Chaux de Bergonne, Gignat, Puy-de-Dôme, France. Named after Ferdinand Gonnard, who had earlier described the material as 'mesole' (= thomsonite).

Forms an extensive substitution series, commonly approximating

$\text{Na}_{8-3x}\text{Ca}_{2x}[\text{Al}_{8+x}\text{Si}_{12-x}\text{O}_{40}] \cdot 12\text{H}_2\text{O}$ (after Ross *et al.*, 1992), with minor Fe^{3+} , Mg, Ba, Sr, and K. T_{Si} in the range 0.52–0.59 (or 0.52–0.62 if tetranatrolite = gonnardite).

Tetragonal, $I\bar{4}2d$, $a = 13.21(1)$, $c = 6.622(4)$ Å for material from Tvedalen, Langesund, Norway, of composition ($\text{Na}_{6.42}\text{K}_{0.01}\text{Ca}_{1.50}$) $[\text{Al}_{9.22}\text{Si}_{10.73}\text{O}_{40}] \cdot 12.37\text{H}_2\text{O}$ (Mazzi *et al.*, 1986). The structure is similar to that of natrolite, but with Si,Al disordered, and usually with significant to substantial Ca (Mazzi *et al.*, 1986; Artioli and Torres Salvador, 1991; Alberti *et al.*, 1995).


Goosecreekite

Dunn *et al.* (1980). Type locality: Goose Creek quarry, Loudoun County, Virginia. Named after the locality.

The single available analysis conforms closely to the formula given, with no other elements detected. $T_{\text{Si}} = 0.75$.

Monoclinic, $P2_1$, $a = 7.401(3)$, $b = 17.439(6)$, $c = 7.293(3)$ Å, $\beta = 105.44(4)^\circ$ (Rouse and Peacor, 1986).

The framework consists of 4-, 6-, and 8-membered rings that link to form layers parallel to (010), with some similarities to the brewsterite structure. Si,Al are nearly perfectly ordered (Rouse and Peacor, 1986).


Gottardiite

Alberti *et al.* (1996), Galli *et al.* (1996). Mt. Adamson, Victoria Land, Antarctica. Named after Professor Glauco Gottardi (1928–1988), University of Modena, in recognition of his pioneering work on the structure and crystal chemistry of natural zeolites.

Known from the type locality only, with composition approximating the above simplified formula; minor K, and very high Si. $T_{\text{Si}} = 0.86$.

Orthorhombic, topological symmetry $Fmmm$, real symmetry $Cmca$, $a = 13.698(2)$, $b = 25.213(3)$, $c = 22.660(2)$ Å (Alberti *et al.*, 1996).

The framework topology is the same as for the synthetic zeolite NU-87, which, however, has monoclinic symmetry, $P2_1/c$. Some Si,Al order is probable.

Harmotome

Haüy (1801, p. 191–195), renaming andreasbergolite, also known as andréolite, of Delamétherie (1795, p. 393). Type locality: Andreasberg, Harz, Germany. Named from Greek words for a 'joint' and 'to cut', in allusion to a tendency to split along junctions (twin planes).


Ba is the most abundant extra-framework cation. Harmotome forms a continuous series with phillipsite-Ca. The name *harmotome* predates *phillipsite*, and on grounds of history and usage both are retained in spite of Rule 1 of the present report. T_{Si} in the range 0.68–0.71 (e.g. Černý *et al.*, 1977).

Monoclinic, refined in $P2_1/m$, but on piezoelectric

and optical grounds, the true symmetry may be noncentrosymmetric and triclinic, $P1$ (e.g. Akizuki, 1985; Stuckenschmidt *et al.*, 1990), $a = 9.879(2)$, $b = 14.139(2)$, $c = 8.693(2)$ Å, $\beta = 124.81(1)^\circ$ for $(Ba_{1.93}Ca_{0.46}K_{0.07})[Al_{4.66}Si_{11.29}O_{32}] \cdot 12H_2O$ from Andreasberg, Harz (Rinaldi *et al.*, 1974).

The structure is the same as for phillipsite, with little or no Si,Al order.

Heulandite (series)



Brooke (1822). Type locality: none; the name was given to the more distinctly monoclinic minerals previously known as stilbite. Named after Henry Heuland, English mineral collector.

The cation content is highly variable. Ca-, Na-, K-, and Sr-dominant compositions are known, and Ba and Mg are in some cases substantial. T_{Si} in the range 0.71–0.80. Minerals with the same framework topology but with $T_{Si} \geq 0.80$, $Si/Al \geq 4.0$, are distinguished as clinoptilolite.

Monoclinic, with highest possible topological symmetry $C2/m$ ($I2/m$). Cm and $C2$ have also been suggested.

The sheet-like structure was solved by Merkle and Slaughter (1968). There is partial order of Si,Al.

Heulandite-Ca

New name for the most common species of the series, and that recognized in most older analyses. Ca is the most abundant single extra-framework cation. T_{Si} in the range 0.71–0.80.

Monoclinic, $C2/m$, Cm , or $C2$, $a = 17.718(7)$, $b = 17.897(5)$, $c = 7.428(2)$ Å, $\beta = 116.42(2)^\circ$ from Faröe Islands, composition $(Ca_{3.57}Sr_{0.05}Ba_{0.06}Mg_{0.01}Na_{1.26}K_{0.43})[Al_{9.37}Si_{26.70}O_{72}] \cdot 26.02H_2O$ ($T_{Si} = 0.74$) (Alberti, 1972).

Heulandite-Sr

New name; Sr is the most abundant single extra-framework cation.

One known example: Campegli, Eastern Ligurian ophiolites, Italy, of composition $(Sr_{2.10}Ca_{1.76}Ba_{0.14}Mg_{0.02}Na_{0.40}K_{0.22})[Al_{9.19}Si_{26.94}O_{72}] \cdot nH_2O$, $T_{Si} = 0.75$ (Lucchetti *et al.*, 1982).

Monoclinic, $C2/m$, Cm , or $C2$, $a = 17.655(5)$, $b = 17.877(5)$, $c = 7.396(5)$ Å, $\beta = 116.65^\circ$.

Heulandite-Na

New name; Na is the most abundant single extra-framework cation.

Proposed type example: Challis, Idaho, U.S.A., U.S. National Museum #94512/3 (Ross and Shannon, 1924; Boles, 1972, #6).

Monoclinic, $C2/m$, Cm , or $C2$, $a = 17.670(4)$, $b = 17.982(4)$, $c = 7.404(2)$ Å, $\beta = 116.40(2)^\circ$ (Boles, 1972) for the type example, of composition $(Na_{3.98}Ca_{1.77}K_{0.55})[Al_{7.84}Si_{28.00}O_{72}] \cdot 21.74H_2O$, $T_{Si} = 0.78$.

Heulandite-K

New name; K is the most abundant single extra-framework cation.

Proposed type example: Albergo Bassi, Vicenza, Italy (Passaglia, 1969a), composition $(K_{2.40}Na_{0.96}Ca_{1.64}Mg_{0.64}Sr_{0.56}Ba_{0.12})[Fe_{0.56}Al_{9.08}Si_{26.48}O_{72}] \cdot 25.84H_2O$, $T_{Si} = 0.73$.

Monoclinic, $C2/m$, Cm , or $C2$, $a = 17.498$, $b = 17.816$, $c = 7.529$ Å, $\beta = 116.07^\circ$.

A close approach to end-member $K_9[Al_9Si_{27}O_{72}] \cdot nH_2O$ has been reported by Nørnberg (1990).

Hsianghualite



Huang *et al.* (1958). Type locality unclear, in metamorphosed Devonian limestone, Hunan Province, China. The name is from a Chinese word for fragrant flower.

Known from the original locality only. Minor Al, Fe, Mg, Na, and 1.28% loss on ignition reported (Beus, 1960). $T_{Si} = 0.48$.

Cubic, $I2_13$, $a = 12.864(2)$ Å.

Has an analcime-type structure, with tetrahedral sites occupied alternately by Si and Be. Extra-framework Ca, Li, and F ions (Rastsvetaeva *et al.*, 1991).

Kalbarsite



Khomyakov *et al.* (1980), Malinovskii and Belov (1980). Type locality: rischorrite pegmatite, Mt. Rasvumchorr, Khibina alkaline massif, Kola Peninsula, Russia. The name alludes to the composition.

Known from two localities in Khibina massif, both with compositions close to the above

formula (Pekov and Chukanov, 1996). T_{Si} values are 0.59, 0.61.

Tetragonal, $P4_2/c$, $a = 9.851(5)$, $c = 13.060(5)$ Å. Framework of Si,Al tetrahedra, with channels along c containing $B(OH)_4$ tetrahedra and K, Cl (Malinovskii and Belov, 1980). Considered by Smith (1988) to be an anhydrous analogue of the edingtonite structure-type EDI.

Laumontite

$Ca_4[Al_8Si_{16}O_{48}] \cdot 18H_2O$ $Z = 1$ LAU

As lomonite, Jameson (1805), who credits the name to Werner without specific reference; spelling changed to laumonite by Haiüy (1809), and to laumontite by von Leonhard (1821). Named after Gillet de Laumont, who collected material described as 'zéolithe efflorescente' by Haiüy (1801, pp. 410–412), from lead mines of Huelgoët, Brittany. The later spellings were applied to this material, and the Huelgoët mines are effectively the type locality.

Always Ca-dominant, with minor (K,Na). 'Primary leonhardite' of Fersman (1908) is laumontite with approximately 1.5 Ca replaced by 3(K,Na) atoms *pfu* and reduced H_2O . T_{Si} in the range 0.64–0.70.

Monoclinic, $C2/m$ (although reported to be pyroelectric), $a = 14.845(9)$, $b = 13.167(2)$, $c = 7.5414(8)$ Å, $\beta = 110.34(2)^\circ$ (Nasik, India; Artioli and Ståhl, 1993).

Except where unusually rich in (K,Na), reversibly loses $c \cdot 4H_2O$ at low humidity at room temperature and pressure to form the variety termed 'leonhardite' (e.g. Fersman, 1908; Armbruster and Kohler, 1992); structure refined by Bartl (1970) and others. Si,Al in the framework is highly ordered.

Leucite

$K[AlSi_2O_6]$ $Z = 16$ ANA

Blumenbachs (1791), who attributes the name to Werner, who had previously described the mineral as 'white garnet'. Type locality: Vesuvius, Italy. Named from Greek, meaning white, in reference to colour.

Minor substitution of Na for K at low temperatures, and Si in excess of that in the simplified formula, are commonly reported, also significant Fe^{3+} . T_{Si} in the range 0.66–0.69.

Tetragonal, $I4_1/a$, $a = 13.09$, $c = 13.75$ Å (Mazzi *et al.*, 1976).

At ordinary temperatures, leucite is invariably finely

twinned as a result of a displacive inversion from a cubic polymorph with the structure of analcime, space group $Ia3d$, apparently stable above $630^\circ C$ (Wyart, 1938; Peacor, 1968). Heaney and Veblen (1990) noted that high leucite inverts to lower symmetry at temperatures between 600° and $750^\circ C$ depending on the sample, and that there is a tetragonal, metrically cubic form intermediate to high (cubic) and (low) tetragonal forms.

Levyne (series)

$(Ca_{0.5}, Na, K)_6[Al_6Si_{12}O_{36}] \cdot \sim 17H_2O$
 $Z = 3$ LEV

Brewster (1825*b*). Type locality: Dalsnypen, Farøe Islands. Named after Armand Lévy (1794–1841), mathematician and crystallographer, Université de Paris.

Extra-framework cations range from strongly Ca-dominant to strongly Na-dominant, with minor K and, in some cases, minor Sr or Ba; Si:Al is also variable (Galli *et al.*, 1981). T_{Si} in the range 0.62–0.70.

Trigonal, $R\bar{3}m$, $a = 13.32$ – 13.43 , $c = 22.66$ – 23.01 Å. The stacking of single and double 6-membered rings differs from that in the related structures of erionite and offretite (Merlino *et al.*, 1975).

Levyne-Ca

New name for the original member of the series; Ca is the most abundant extra-framework cation. Type locality: Dalsnypen, Farøe Islands. Material closely approaching end-member $Ca_3[Al_6Si_{12}O_{36}] \cdot 17H_2O$ has been reported by England and Ostwald (1979) from near Merriwa, New South Wales, Australia. T_{Si} in the range 0.62–0.70.

Trigonal, $R\bar{3}m$, $a = 13.338(4)$, $c = 23.014(9)$ Å for composition $(Ca_{2.73}Na_{0.65}K_{0.20})[Al_{6.31}Si_{11.69}O_{36}] \cdot 16.66H_2O$ from near the Nurri to Orroli road, Nuora, Sardinia (Passaglia *et al.*, 1974; Merlino *et al.*, 1975).

Levyne-Na

New name; Na is the most abundant extra-framework cation.

Proposed type example: Chojabaru, Nagasaki Prefecture, Japan (Mizota *et al.*, 1974). T_{Si} 0.65–0.68.

Trigonal, $R\bar{3}m$, $a = 13.380(5)$, $c = 22.684(9)$ Å for $(Na_{3.84}K_{0.38}Ca_{0.89}Mg_{0.08})[Al_{6.33}Si_{11.71}O_{36}]$ (Mizota *et al.*, 1974).

Lovdarite

$K_4Na_{12}[Be_8Si_{28}O_{72}] \cdot 18H_2O$ Z = 1 LOV
Men'shikov *et al.* (1973). Type locality: alkaline pegmatites on Mt. Karnasurt, Lovozero massif, Kola Peninsula, Russia. Name means 'a gift of Lovozero'.

In the type and only known occurrence, approximately 1 Al atom substitutes for Si in the above structure-derived formula, with introduction of additional extra-framework Na and Ca. T_{Si} 0.75. Orthorhombic, *Pma2*, but contains *b*-centred domains in which *a* is doubled; $a = 39.576(1)$, $b = 6.9308(2)$, $c = 7.1526(3)$ Å (Merlino, 1990).

The structure consists of a three-dimensional framework of Si (with minor Al) and Be tetrahedra. It contains 3-membered rings, made possible by the presence of Be instead of Si in one of the tetrahedra.

Maricopaite

$(Pb_7Ca_2)[Al_{12}Si_{36}(O,OH)_{100}] \cdot n(H_2O,OH)$ $n \approx 32$
Z = 1 Structure closely related to MOR
Peacor *et al.* (1988). Type locality: Moon Anchor mine, near Tonopah, Maricopa County, Arizona, U.S.A. Named after the locality.

Only one known occurrence. T_{Si} 0.76. Orthorhombic, *Cm2m* (pseudo-*Cmcm*), $a = 19.434(2)$, $b = 19.702(2)$, $c = 7.538(1)$ Å (Rouse and Peacor, 1994).

Has an interrupted, mordenite-like framework. Pb atoms form $Pb_4(O,OH)_4$ clusters with Pb_4 tetrahedra within channels (Rouse and Peacor, 1994).

Mazzite

$(Mg_{2.5}K_2Ca_{1.5})[Al_{10}Si_{26}O_{72}] \cdot 30H_2O$
Z = 1 MAZ

Galli *et al.* (1974). Type locality: in olivine basalt near top of Mont Semiol, south slope, near Montbrison, Loire, France. Named after Fiorenzo Mazzi, Professor of Mineralogy at the University of Pavia, Italy.

A new chemical analysis from the type and only known locality (G. Vezzalini, personal communication, 1996) gives the above formula (*cf.* Rinaldi *et al.*, 1975*b*). T_{Si} 0.72.

Hexagonal, *P6₃/mmc*, $a = 18.392(8)$, $c = 7.646(2)$ Å. The framework is characterized by stacked gmelinite-type cages (Galli, 1975), with evidence for limited Si,Al order (Alberti and Vezzalini, 1981*b*).

Merlinoite

$K_5Ca_2[Al_9Si_{23}O_{64}] \cdot 22H_2O$ Z = 1 MER
Passaglia *et al.* (1977). Type locality: Cupaello quarry in kalsilite melilitite, near Santa Rufina, Rieti, Italy. Named after Stefano Merlino, Professor of Crystallography at the University of Pisa.

Available reliable data (Passaglia *et al.*, 1977; Della Ventura *et al.*, 1993) show strongly K-dominant compositions with significant Ca, and less Na and Ba; T_{Si} 0.66, 0.71.

Orthorhombic, *Immm*, $a = 14.116(7)$, $b = 14.229(6)$, $c = 9.946(6)$ Å (Passaglia *et al.*, 1977). The framework is built of double 8-membered rings linked with 4-membered rings (Galli *et al.*, 1979). The structure is related to, but different from, that of phillipsite.

Mesolite

$Na_{16}Ca_{16}[Al_{48}Si_{72}O_{240}] \cdot 64H_2O$ Z = 1 NAT
Gehlen and Fuchs (1813), as Mesolith, for some varieties of 'mesotype' (mostly natrolite) of Haüy (1801). No type locality was given. Fuchs (1816) clarified the distinctions among natrolite, scolecite, and mesolite, and gave analyses of mesolite from the Faröe Islands, Iceland, and Tyrol. The name recognizes its compositional position between natrolite and scolecite.

$(Na + K)/(Mg + Ca + Sr + Ba)$ varies from 0.45 to 0.52, with K, Mg, Sr, Ba very minor (Alberti *et al.*, 1982*b*). T_{Si} in the range 0.59–0.62.

Orthorhombic, *Fdd2*, $a = 18.4049(8)$, $b = 56.655(6)$, $c = 6.5443(4)$ Å, for material from Poona, India (Artioli *et al.*, 1986*a*).


Ordered Si,Al in the framework, with one natrolite-like layer alternating with two scolecite-like layers parallel to (010) (Artioli *et al.*, 1986*a*; Ross *et al.*, 1992).

Montesommaite

$K_9[Al_9Si_{23}O_{64}] \cdot 10H_2O$ Z = 1 MON
Rouse *et al.* (1990). Type locality: Pollena, Monte Somma, Vesuvius, Italy. Named after the locality. Minor Na was detected in the one published analysis. T_{Si} = 0.70.

Orthorhombic, *Fdd2*, $a = b = 10.099(1)$, $c = 17.307(3)$ Å (pseudotetragonal, *I4₁/amd*).

The framework can be constructed by linking (100) sheets of 5- and 8-membered rings; it has similarities to those of merlinoite and the gismondine group (Rouse *et al.*, 1990).


Mordenite

How (1864). Type locality: shore of Bay of Fundy, ~3–5 km east of Morden, King's County, Nova Scotia, Canada. Named after the locality.

The cation content is variable, with Na/(Na + Ca) typically in the range 0.50–0.81. Some K, Mg, Fe, Ba, and Sr also may be present (Passaglia, 1975; Passaglia *et al.*, 1995). In some examples, K is reported as the dominant cation (Thugutt, 1933; Lo *et al.*, 1991; Lo and Hsieh, 1991), potentially justifying the recognition of a mordenite series with Na- and K-dominant species. T_{Si} in the range 0.80–0.86.

Orthorhombic, *Cmcm*, a 18.052–18.168, b 20.404–20.527, c 7.501–7.537 Å (Passaglia, 1975).

Structure determined by Meier (1961). Si,Al disorder in the framework is extensive, but not complete.

Mutinaite

Galli, *et al.* (1997b); Vezzalini *et al.* (1997b). Type locality: Mt. Adamson, Northern Victoria Land, Antarctica. The name is for Mutina, the ancient Latin name for Modena, Italy.

Electron microprobe analyses of mutinaite from the type and only known locality show limited departure from the simplified formula, with minor Mg (~0.21 atoms *pfu*) and K (~0.11 atoms *pfu*). Very high Si, T_{Si} 0.88.

Orthorhombic, *Pnma*, a = 20.223(7), b = 20.052(8), c = 13.491(5) Å.

Mutinaite conforms closely in structure to synthetic zeolite ZSM-5.

Natrolite


Klaproth (1803). Type locality: Hohentwiel, Hegau, Baden-Württemberg, Germany. Name from *natro-* for sodium-bearing.

(Na + K)/(Mg + Ca + Sr + Ba) varies from 0.97 to 1.00, with K, Mg, Sr, and Ba very minor. T_{Si} in the range 0.59–0.62 (Alberti *et al.*, 1982b; Ross *et al.*, 1992).

Orthorhombic, *Fdd2*, a = 18.272, b = 18.613, c = 6.593 Å (Si,Al highly ordered, Dutoitspan, South Africa: Artioli *et al.*, 1984); a = 18.319(4), b = 18.595(4), c = 6.597(1) Å (~70% Si,Al order,

Zeilberg, Germany: Hesse, 1983).

Si,Al partly to highly ordered (Alberti and Vezzalini, 1981a; Ross *et al.*, 1992; Alberti *et al.*, 1995).


Offretite

Gonnard (1890), as offretite. Type locality: Mont Simionse (Mont Semiol), Loire, France. Named after Albert J. J. Offret, professor in the Faculty of Sciences, Lyon, France.

Ca, Mg, and K substantial, commonly in proportions approaching 1:1:1; Na commonly trace or minor. Passaglia *et al.* (1998) and W.D. Birch (personal communication, 1997) show that earlier published analytical data pertaining to apparently Ca- and Na-dominant variants are compromised by identification problems, including possible mixtures. T_{Si} in the range 0.69–0.74.

Hexagonal, $P\bar{6}m2$, a = 13.307(2), c = 7.592(2) Å for composition $(\text{Mg}_{1.06}\text{Ca}_{0.97}\text{K}_{0.88}\text{Sr}_{0.01}\text{Ba}_{0.01})[\text{Al}_{5.26}\text{Si}_{12.81}\text{O}_{36}] \cdot 16.85\text{H}_2\text{O}$ from the type locality (Passaglia and Tagliavini, 1994).

The framework is related to those of erionite and levyne, but differs in the stacking of sheets of 6-membered rings, resulting in different values for c and differently sized and shaped cages (Gard and Tait, 1972). A high degree of Si,Al order is inferred. Offretite may contain intergrown macro- or crypto-domains of erionite (e.g. Rinaldi, 1976). It forms epitactic intergrowths with chabazite, but epitactic associations with levyne are questionable (Passaglia *et al.*, 1998).


Pahasapaite

Rouse *et al.* (1987). Type locality: Tip Top mine, Black Hills, South Dakota, U.S.A. Named after Pahasapa, a Sioux Indian name for the Black Hills.

Known from the type locality only. $T_{\text{Si}} = 0$.

Cubic, *I23*, a = 13.781(4) Å.

A beryllophosphate zeolite with ordered BeO_4 and PO_4 tetrahedra and a distorted synthetic zeolite RHO-type framework, structurally related to the faujasite series (Rouse *et al.*, 1989).

Parthéite

Sarp *et al.* (1979). Type locality: in ophiolitic rocks, 7 km southeast of Doganbaba, Burdur province, Taurus Mountains, southwestern Turkey. Named after Erwin Parthé, professor of structural crystallography, University of Geneva, Switzerland.

Minor Na and K. $T_{Si} = 0.52$ and 0.495 in the only two known occurrences.

Monoclinic, $C2/c$, $a = 21.553(3)$, $b = 8.761(1)$, $c = 9.304(2)$ Å, $\beta = 91.55(2)^\circ$ (type locality; Engel and Yvon, 1984).

The framework contains various 4-, 6-, 8-, and 10-membered rings, and is interrupted at every second AlO_4 tetrahedron by an hydroxyl group. Si and Al are ordered.

Paulingite (series)

$(K, Ca_{0.5}, Na, Ba_{0.5})_{10}[Al_{10}Si_{32}O_{84}] \cdot 27-44H_2O$
 $Z = 16$ PAU

Kamb and Oke (1960). Type locality: Rock Island Dam, Columbia River, Wenatchee, Washington, U.S.A. Named after Linus C. Pauling, Nobel Prize winner and Professor of Chemistry, California Institute of Technology.

Electron microprobe analyses show K as the most abundant cation at three known localities and Ca at two. Significant Ba and Na are also reported (Tschernich and Wise, 1982, Lengauer *et al.*, 1997). T_{Si} , $0.73-0.77$.

Cubic, $Im\bar{3}m$, $a = 35.093(2)$ Å (Gordon *et al.*, 1966).

The framework contains several kinds of large polyhedral cages (Gordon *et al.*, 1966). The structure has been refined by Bieniok *et al.* (1996) and by Lengauer *et al.* (1997).

Paulingite-K

New name; K is the most abundant extra-framework cation.

Average of five analyses, Rock Island Dam, Washington, U.S.A., the suggested type example for paulingite-K:

$(K_{4.44}Na_{0.95}Ca_{1.88}Ba_{0.18}) [Al_{9.82}Si_{32.21}O_{84}] \cdot 44H_2O$ (Tschernich and Wise, 1982); $a = 35.093(2)$ Å (Gordon *et al.*, 1966).

Paulingite-Ca

New name; Ca is the most abundant extra-framework cation. Average of four analyses, Ritter, Oregon, U.S.A., the suggested type locality for paulingite-Ca: $(Ca_{3.70}K_{2.67}Na_{0.86}Ba_{0.10})$

$[Al_{10.78}Si_{31.21}O_{84}] \cdot 34H_2O$; $a = 35.088(6)$ Å (Tschernich and Wise, 1982).

Lengauer *et al.* (1997) found evidence of reduced H_2O content ($27 H_2O$ for $Z = 16$) in barian paulingite-Ca from Vinarická Hora, Czech Republic.

Perlielite

$K_9Na(Ca,Sr) [Al_{12}Si_{24}O_{72}] \cdot 15H_2O$
 $Z = 1$ LTL

Men'shikov (1984). Type locality: Pegmatites of Mt. Eveslogchorr and Mt. Yukspor, Khibina massif, Kola Peninsula, Russia. Named after Lily Alekseevna Perekrest, instructor in mineralogy at Kirov Mining Technical School.

Minor substitution by Sr and Ba, but little other compositional variation in the two known occurrences. T_{Si} , $0.65, 0.67$.

Hexagonal, $P6/mmm$, $a = 18.49(3)$, $c = 7.51(1)$ Å (Men'shikov, 1984).

Perlielite has the same framework topology as synthetic zeolite-L (Artioli and Kvik, 1990). Structural columns have alternating cancrinite-type cages and double 6-membered rings. No Si,Al order has been detected.

Phillipsite (series)

$(K, Na, Ca_{0.5}, Ba_{0.5})_x [Al_x Si_{16-x} O_{32}] \cdot 12H_2O$
 $Z = 1$ PHI

Lévy (1825). Type locality as recorded by Lévy: Aci Reale, now Acireale, on the slopes of Etna, Sicily, Italy. Contemporary literature (see Di Franco, 1942) and present-day exposures suggest that the occurrence was probably in basaltic lavas at Aci Castello, nearby. Named for William Phillips (1773–1828), author of geological and mineralogical treatises and a founder of the Geological Society of London.

K, Na, Ca, or Ba may be the most abundant extra-framework cation, but the name harmotome is retained for the Ba-dominant member of the series. Minor Mg and Sr may be present. In the generalized formula above, x ranges from about 4 to about 7. T_{Si} varies widely, from approximately 0.56 to 0.77 .

Monoclinic, $P2_1$ or $P2_1/m$, $a = 9.865(2)$, $b = 14.300(4)$, $c = 8.668(2)$ Å, $\beta = 124.20(3)^\circ$ (phillipsite-K with substantial Ca from Casal Brunori, Rome, Italy: Rinaldi *et al.*, 1974). A pseudo-orthorhombic cell has $a \approx 9.9$, $b \approx 14.2$, $c \approx 14.2$ Å, $\beta \approx 90.0^\circ$, $Z = 2$.

Two cation sites have been identified, one, with two atoms *pfu* fully occupied by K in phillipsite-K

and by Ba in harmotome, is surrounded by eight framework atoms of oxygen and four molecules of H₂O; the other is partly occupied by Ca and Na in distorted octahedral coordination with two framework atoms of oxygen and four molecules of H₂O (Rinaldi *et al.*, 1974). Framework Si, Al largely disordered.

Phillipsite-Na

New name; Na is the most abundant extra-framework cation.

Na forms 81% of all extra-framework cations in material from Aci Castello, Sicily, Italy, suspected to be the original locality for phillipsite (#6 of Galli and Loschi Ghittoni, 1972). Known range in T_{Si}: 0.64–0.77.

For pseudocell, a 9.931–10.003, b 14.142–14.286, c 14.159–14.338 Å, $\beta = 90^\circ$, $Z = 2$ (e.g. Galli and Loschi Ghittoni, 1972; Sheppard and Fitzpatrick, 1989).

Phillipsite-K

New name; K is the most abundant extra-framework cation. Proposed type locality: Capo di Bove, Rome, Italy (Hintze, 1897; #2 of Galli and Loschi Ghittoni, 1972).

Known range in T_{Si}: 0.59–0.76.

For the pseudocell, a 9.871–10.007, b 14.124–14.332, c 14.198–14.415 Å, $\beta = 90^\circ$, $Z = 2$ (e.g. Galli and Loschi Ghittoni, 1972; Sheppard *et al.*, 1970).

Phillipsite-Ca

New name; Ca is the most abundant extra-framework cation. Proposed type locality: In Lower Salt Lake Tuff, Puuloa Road near Moanalua Road junction, Oahu, Hawaii (Iijima and Harada, 1969).

Known range in T_{Si}: 0.57–0.74.

For the pseudocell, a 9.859–9.960, b 14.224–14.340, c 14.297–14.362 Å, $\beta = 90^\circ$, $Z = 2$ (e.g. Galli and Loschi Ghittoni, 1972; Passaglia *et al.*, 1990).

Pollucite

(Cs,Na) [AlSi₂O₆] $\cdot n$ H₂O, where (Cs + n) = 1

$Z = 16$ ANA

Breithaupt (1846). Type locality: Elba, Italy. Named 'pollux' with coexisting mineral 'castor' (a variety of petalite) for twins Castor and Pollux,

of Greek mythology; name modified to pollucite by Dana (1868).

Forms a series with analcime (Černý, 1974) reaching end-member compositions (Teertstra and Černý, 1995). T_{Si} in the range 0.67–0.74. Minor Rb and Li may be present. Sodian pollucite commonly contains more Si than the simplified formula. The name pollucite applies where Cs exceeds Na in atomic proportions.

Cubic, $Ia\bar{3}d$, $a = 13.69$ Å for (Cs_{11.7}Na_{3.1}Li_{0.25}K_{0.4})[Al₁₅Si₃₃O_{96.2}] $\cdot 4$ H₂O (Beger, 1969); a in the range 13.672(1)–13.674(1) Å for 0.114–0.173 Na atoms *pfu*, $Z = 16$ (Černý and Simpson, 1978). Si,Al disordered.

Roggianite

Ca₂[Be(OH)₂Al₂Si₄O₁₃] $\cdot <2.5$ H₂O

$Z = 8$ -ROG

Passaglia (1969*b*). Type locality: in sodium feldspar dike at Alpe Rosso in Val Vigizzo about 1.5 km south of Orcesco, Novara Province, Italy. Named after Aldo G. Roggiani, a teacher of natural sciences, who first found the mineral.

Contains minor Na and K.

Tetragonal, $I4/mcm$, $a = 18.33(1)$, $c = 9.16(1)$ Å (Galli, 1980).

Contains framework tetrahedrally coordinated Be (Passaglia and Vezzalini, 1988) and framework-interrupting (OH) groups (Giuseppetti *et al.*, 1991).

Scolecite

Ca[Al₂Si₃O₁₀] $\cdot 3$ H₂O

$Z = 4$ or 8 NAT


Gehlen and Fuchs (1813), as skolezit. Clark (1993) gave the type locality as Berufjord, Iceland, but this is not apparent in the original reference. Fuchs (1816) clarified the distinctions among natrolite, scolecite, and mesolite. He listed occurrences of scolecite as Farøe Islands, Iceland, and Staffa (Western Isles, Scotland), with analytical data for specimens from the Farøe Islands and Staffa. Named from Greek *skolex*, worm, for a tendency to curl when heated.

(Na + K)/(Mg + Ca) varies from 0 to 0.16, with very little K, Mg, or other elements. T_{Si} in the range 0.60–0.62 (Alberti *et al.*, 1982*b*).

Monoclinic, Cc , $a = 6.516(2)$, $b = 18.948(3)$, $c = 9.761(1)$ Å, $\beta = 108.98(1)^\circ$, $Z = 4$ (Bombay, India: Kwick *et al.*, 1985), or, by analogy with natrolite, pseudo-orthorhombic $Fd\bar{2}$, e.g. $a = 18.508(5)$, $b = 18.981(5)$, $c = 6.527(2)$ Å, $\beta = 90.64(1)^\circ$, $Z = 8$ (Berufjord, Iceland: Joswig *et al.*, 1984).

The structure is similar to that of natrolite with a well-ordered Si,Al framework, Ca instead of Na₂, and an extra molecule of H₂O.

Stellerite



Morozewicz (1909). Type locality: Commander Island, Bering Sea. Named after Wilhelm Steller (1709–1746), natural scientist and military doctor who made important observations on Commander Island.


Variations in composition include up to about 0.2 atoms of Na *pfu* and minor K, Mg, Fe. T_{Si} in the range 0.75–0.78.

Orthorhombic, *Fmmm*, *a* 13.507–13.605, *b* 18.198–18.270, *c* 17.823–17.863 Å (Passaglia *et al.*, 1978*b*).

The framework is topologically the same as for stilbite, but it has higher symmetry, correlated with fewer extra-framework cations. Only one independent extra-framework site is occupied, and the symmetry is *Fmmm* (Galli and Alberti, 1975*a*). Na-exchanged stellerite retains the *Fmmm* symmetry, unlike the Na zeolite, barrerite, with which it is isostructural (Passaglia and Sacerdoti, 1982).

Villarroel (1983) has suggested the occurrence of Na-dominant *Fmmm* stellerite at Roberts Island, South Shetland group.

Stilbite (series)



Z = 1 STI

Häuy (1801, p. 161–6), for minerals, apparently including heulandite, that had previously been described with informal names. He mentioned occurrences in volcanic terranes, and named Iceland, Andreasberg in Harz, Alpes Dauphinoises, and Norway, but there is no clear type locality. Named from Greek word for mirror, in allusion to its lustre ('un certain éclat').

Ca is almost always the dominant extra-framework cation, accompanied by subordinate Na and minor K and Mg, approximating Ca₄(Na,K) *pfu*, but Na-rich members are also known. T_{Si} in the range 0.71–0.78.

Monoclinic, *C2/m*, *a* = 13.64(3), *b* = 18.24(4), *c* = 11.27(2) Å, β = 128.00(25)° (Galli and Gottardi, 1966; Galli, 1971); an alternative setting is pseudo-orthorhombic, *F2/m*, Z = 2.

Increasing departure from the topological symmetry of the orthorhombic framework,

Fmmm, tends to correlate with increasing content of monovalent cations (Passaglia *et al.*, 1978*b*), which causes the framework to rotate (Galli and Alberti, 1975*a,b*). However, {001} growth sectors with appreciable Na and orthorhombic *Fmmm* symmetry have been observed in crystals in which other isochemical sectors are monoclinic, *C2/m* (Akizuki and Konno, 1985; Akizuki *et al.*, 1993). The centrosymmetric space group depends on statistically complete Si,Al disorder, and the true space group may be noncentrosymmetric (Galli, 1971).

Stilbite-Ca

New name for common stilbite in which Ca is the most abundant extra-framework cation.

For the pseudo-orthorhombic cell, *F2/m*, *a* 13.595–13.657, *b* 18.201–18.291, *c* 17.775–17.842 Å, β 90.06–90.91° (Passaglia *et al.*, 1978*b*).

Stilbite-Na

New name; Na is the most abundant extra-framework cation.

Proposed type locality: Capo Pula, Cagliari, Sardinia, Italy (Passaglia *et al.*, 1978*b*, #21).

Known examples contain significant Ca and K and minor Mg, as well as clearly predominant Na. T_{Si} in the range 0.73–0.78 (Passaglia *et al.*, 1978*b*; Ueno and Hanada, 1982; Di Renzo and Gabelica, 1997).

Monoclinic, *C2/m*. Using the pseudo-orthorhombic *F2/m* setting, *a* = 13.610, *b* = 18.330, *c* = 17.820 Å, β = 90.54° for type material of composition (Na_{8.18}K_{1.94}Ca_{3.45}Mg_{0.08}) [Al_{16.62}Si_{55.25}O₁₄₄]·53.53H₂O (Quartieri and Vezzalini, 1987).

In spite of the high Na content, the monoclinic *C2/m* symmetry of stilbite is retained, in contrast to stellerite, *Fmmm*, and barrerite, *Amma*.

Terranovaite



Galli *et al.* (1997*a*). Type locality: Mt. Adamson, Northern Victoria Land, Antarctica. Named after the Italian Antarctic station at Terranova Bay.

Type material contains minor amounts of K and Mg. T_{Si} 0.85.

Orthorhombic, *Cmcm*, *a* = 9.747(1), *b* = 23.880(2), *c* = 20.068(2) Å.

The framework topology is not known in other

natural or synthetic zeolites. It contains polyhedral units found in laumontite, heulandite, and boggsite.

Thomsonite

$\text{Ca}_2\text{Na}[\text{Al}_5\text{Si}_5\text{O}_{20}]\cdot 6\text{H}_2\text{O}$ $Z = 4$ THO
Brooke (1820). Type locality: Old Kilpatrick, near Dumbarton, Scotland. Named after Dr Thomas Thomson (1773–1852), editor of the journal in which the name was published, and who contributed to the improvement of methods of chemical analysis.

Extensive variation in Na:(Ca + Sr) and Si:Al approximately according to the formula $\text{Na}_{4+x}(\text{Ca},\text{Sr})_{8-x}[\text{Al}_{20-x}\text{Si}_{20+x}\text{O}_{80}]\cdot 24\text{H}_2\text{O}$, where x varies from about 0 to 2; small amounts of Fe, Mg, Ba, and K may also be present (Ross *et al.*, 1992). T_{Si} in the range 0.50–0.56.

Orthorhombic, *Pncn*, $a = 13.1043(14)$, $b = 13.0569(18)$, $c = 13.2463(30)$ Å (Stähl *et al.*, 1990).

Chains with a repeat unit of five tetrahedra occur as in the NAT structure type, but they are cross-linked in a different way; Si,Al are highly ordered, but disorder increases with increasing Si:Al (Alberti *et al.*, 1981).

Tschernichite

$\text{Ca}[\text{Al}_2\text{Si}_6\text{O}_{16}]\cdot \sim 8\text{H}_2\text{O}$ $Z = 8$ BEA
Smith *et al.* (1991), Boggs *et al.* (1993). Type locality: Goble Creek, 0.2 km north of Goble, Columbia County, Oregon, U.S.A. Named after Rudy W. Tschernich, zeolite investigator of the American Pacific Northwest, who discovered the mineral.

Na, Mg, and K are minor but variable constituents in specimens from the one known locality. T_{Si} in the range 0.74–0.78 (0.73, 0.80 in a tschernichite-like mineral from Mt. Adamson, Antarctica: Galli *et al.*, 1995).

Tetragonal, possible space-group *P4/mmm*, $a = 12.880(2)$, $c = 25.020(5)$ Å, but may consist of an intergrowth of a tetragonal enantiomorphic pair with space groups *P4*, *22* and *P4*₃*22* and a triclinic polymorph *P1*. See also Galli *et al.* (1995).

This is a structural analogue of synthetic zeolite beta.

Tschörtnerite

$\text{Ca}_4(\text{K}_2, \text{Ca}, \text{Sr}, \text{Ba})_3\text{Cu}_3(\text{OH})_8[\text{Al}_{12}\text{Si}_{12}\text{O}_{48}]\cdot n\text{H}_2\text{O}$,
 $n \geq 20$ $Z = 16$ (IZA code not assigned)

Krause *et al.* (1997), Effenberger *et al.* (1998). Bellberg volcano, near Mayen, Eifel, Germany. Named after Jochen Tschörtner, mineral collector and discoverer of the mineral.

$T_{\text{Si}} = 0.50$ for the only known occurrence.

Cubic, *Fm* $\bar{3}m$, $a = 31.62(1)$ Å.

Cages in the framework include a large super-cage with 96 tetrahedra and 50 faces. A Cu₄(OH)-bearing cluster occupies another cage. The framework density is the lowest known for a zeolite with a non-interrupted framework.

Wairakite

$\text{Ca}[\text{Al}_2\text{Si}_4\text{O}_{12}]\cdot 2\text{H}_2\text{O}$ $Z = 8$ ANA
Steiner (1955), Coombs (1955). Wairakei, Taupo Volcanic Zone, New Zealand. Named after the locality.

Most analysed samples have Na/(Na + Ca) less than 0.3, but wairakite possibly forms a continuous solid-solution series with analcime (Seki and Oki, 1969; Seki, 1971, Cho and Liou, 1987). Other reported substitutions are very minor. T_{Si} in the range 0.65–0.69.

Monoclinic (highly ordered), *I2/a*, $a = 13.692(3)$, $b = 13.643(3)$, $c = 13.560(3)$ Å, $\beta = 90.5(1)^\circ$ for $(\text{Ca}_{0.96}\text{Na}_{0.14})[\text{Al}_{1.92}\text{Si}_{4.07}\text{O}_{12}]\cdot 2\text{H}_2\text{O}$ (Takéuchi *et al.*, 1979).

Tetragonal or near-tetragonal, *I4*₁*acd*, $a = 13.72(4)$, $c = 13.66(4)$ Å for $(\text{Ca}_{0.92}\text{Na}_{0.10})[\text{Al}_{1.92}\text{Si}_{4.07}\text{O}_{12}]\cdot 2.11\text{H}_2\text{O}$ (Nakajima, 1983).

The framework topology is similar to that of analcime, but Al is preferentially located in a pair of tetrahedral sites associated with Ca, and Ca is in one specific extra-framework site. Smaller departures from cubic symmetry are correlated with decreased Si,Al order. The name applies to zeolites of ANA structural type in which Ca is the most abundant extra-framework cation, irrespective of the degree of order or space-group symmetry.

Weinebeneite

$\text{Ca}[\text{Be}_3(\text{PO}_4)_2(\text{OH})_2]\cdot 4\text{H}_2\text{O}$ $Z = 4$ WEI
Walter (1992). Type locality: spodumene-bearing pegmatite, 2 km west of Weinbene Pass, Koralpe, Carinthia, Austria. Named after the locality.


No elements other than those in the given formula were detected in the one known occurrence.

Monoclinic, *Cc*, $a = 11.897(2)$, $b = 9.707(1)$, $c = 9.633(1)$ Å, $\beta = 95.76(1)^\circ$.

A calcium beryllophosphate zeolite with 3-, 4-

and 8-membered rings in the framework (Walter, 1992).

Willhendersonite



Peacor *et al.* (1984). Type locality: San Venanzo quarry, Terni, Umbria, Italy. Named after Dr William A. Henderson, of Stamford, Connecticut, U.S.A., who noted this as an unusual mineral and provided it for study.

Type willhendersonite conforms closely to $KCa[Al_3Si_3O_{12}] \cdot 5H_2O$. End-member $Ca_{1.5}[Al_3Si_3O_{12}] \cdot 5H_2O$ and intermediate compositions are now known (Vezzalini *et al.*, 1997a). $T_{Si} = 0.50, 0.51$.

Triclinic, $P\bar{1}$, $a = 9.206(2)$, $b = 9.216(2)$, $c = 9.500(4)$ Å, $\alpha = 92.34(3)^\circ$, $\beta = 92.70(3)^\circ$, $\gamma = 90.12(3)^\circ$ (Etrringer Bellerberg near Mayen, Eifel, Germany: Tillmanns *et al.*, 1984).

The framework is the same as for chabazite, which has idealized framework topological symmetry $R\bar{3}m$ but with much lower Si and with Si,Al fully ordered. This reduces the topochemical framework symmetry to $R\bar{3}$, and the nature and ordering of the extra-framework cations further reduce the framework symmetry to $P\bar{1}$. The low-K variants also have fully ordered Si,Al, but are less markedly triclinic (Vezzalini *et al.*, 1996).

Yugawaralite



Sakurai and Hayashi (1952). Type locality: Yugawara Hot Springs, Kanagawa Prefecture, Honshu, Japan. Named after the locality.

Reported compositions are close to the ideal stoichiometry with up to 0.2 atoms *pfu* of Na,K,Sr. T_{Si} in the range 0.74–0.76.

Monoclinic, Pc , $a = 6.700(1)$, $b = 13.972(2)$, $c = 10.039(5)$ Å, $\beta = 111.07^\circ$ (Kvick *et al.*, 1986).

Triclinic, $P1$, by symmetry reduction ascribed to local Si,Al order, has been reported on the basis of optical measurements (Akizuki, 1987b).

Si,Al are strictly ordered in samples from Iceland (Kerr and Williams, 1969; Kvick *et al.*, 1986).

The partial order reported for the Yugawara sample (Leimer and Slaughter, 1969) is doubtful (Gottardi and Galli, 1985).

Zeolites of doubtful status and a possible zeolite

Further work is recommended to clarify the status

of paranatrolite and tetranatrolite. Essential data for these minerals and for tvedalite, which is possibly a beryllsilicate zeolite, are as follows.

Paranatrolite




Chao (1980). Type locality, Mont Saint-Hilaire, Quebec, Canada. The name recognizes its association with and similarity in chemical composition to natrolite, $Na_2[Al_2Si_3O_{10}] \cdot 2H_2O$. Contains additional H_2O relative to natrolite, also minor Ca and K.

Pseudo-orthorhombic, F^{***} , probably monoclinic. $a = 19.07(1)$, $b = 19.13(1)$, $c = 6.580(3)$ Å. Gives very diffuse diffraction spots, and a powder pattern similar to that of gonnardite (Chao, 1980).

Dehydrates to tetranatrolite and could be regarded as over-hydrated natrolite, tetranatrolite, or gonnardite. Without further justification, separate species status is debatable according to Rule 4.

Tetranatrolite



Chen and Chao (1980). Type locality: Mont Saint-Hilaire, Quebec, Canada. The name indicates a tetragonal analogue of natrolite. First described as 'tetragonal natrolite', from Ilímaussaq, Greenland, by Krogh Andersen *et al.* (1969).


Extensive solid solution approximating $(Na_{16-x}Ca_x)[Al_{16+x}Si_{24-x}O_{80}] \cdot 16H_2O$, where x varies from about 0.4 to 4, is reported by Ross *et al.* (1992). Small amounts of Fe^{3+} , Sr, Ba, and K may replace Na and Ca. T_{Si} in the range 0.50–0.59.

Tetragonal, $I\bar{4}2d$. $a = 13.141$, $c = 6.617$ Å (Mont Saint-Hilaire, Quebec, Canada: Ross *et al.*, 1992).

The framework is of disordered natrolite type.

Tetranatrolite is considered to be a dehydration product of paranatrolite (Chen and Chao, 1980; Ross *et al.*, 1992). It differs from natrolite in CaAl substitution for NaSi, as well as in space-group symmetry. These, however, are also characteristics of gonnardite, to which its relationship is debatable.

Tvedalite



Larsen *et al.* (1992). Type locality: Vevya quarry, Tvedalen, Vestfold County, Norway. Named after the locality.

Spot analyses show a range from $(\text{Ca}_{3.20}\text{Mn}_{0.72}\text{Fe}_{0.08})_{\Sigma 4}$ to $(\text{Ca}_{2.00}\text{Mn}_{1.86}\text{Fe}_{0.14})_{\Sigma 4}$ for $\text{Be}_3\text{Si}_6\text{O}_{17}(\text{OH})_4 \cdot 3\text{H}_2\text{O}$, with about 0.1 to 0.21 Al and minor Be substituting for Si in the generalized formula.

Orthorhombic (*c*-centred), $a = 8.724(6)$, $b = 23.14(1)$, $c = 4.923(4)$ Å.

Considered to be structurally related to chiavenite, but in the absence of an adequate determination of its structure, it has not been listed here as an accepted zeolite species.

Discredited, obsolete, and other non-approved zeolite names

Herschelite, *leonhardtite*, *svetlozarite*, and *wellsite* are discredited as names of mineral species (Appendix 2).

Kehoeite was regarded by McConnell (1964) as a zinc phosphate analogue of analcime, but according to White and Erd (1992), type kehoeite is a heterogeneous mixture of quartz and sphalerite with other phases including gypsum and woodhouseite, or a very similar phase. No phase present bears any relationship to analcime. It is not accepted as a valid zeolite species.

Viséite is shown by Di Renzo and Gabelica (1995) not to be a zeolite, as had commonly been supposed. They regard it as a defective member of the crandallite group with composition $\text{CaAl}_3(\text{PO}_4, \text{SiO}_4)_2(\text{OH})_n \cdot m\text{H}_2\text{O}$. Kim and Kirkpatrick (1996) showed that a specimen examined by them is very disordered, with a structure similar to that of crandallite, but contains other phases including opal. *Viséite* is excluded from the list of accepted zeolites.

Obsolete and discredited names are listed below, followed by the correct names or identifications. The list is based on one compiled by the late G. Gottardi, using the following references: Hintze (1897), Dana (1914), Cocco and Garavelli (1958), Davis (1958), Hey (1960, 1962), Merlino (1972), and Strunz (1978). Numerous additions and amendments have been made in the light of more recently published work and of the notes below, and of listings in Clark (1993), in which much information on the history and usages of these names can be found.

abrazite = gismondine, phillipsite
 acadialite = chabazite
 achiardite = dachiardite
 adipite = chabazite?
 aedelforsite = laumontite?, stilbite?

aedelite (of Kirwan), aedilite = natrolite
 ameletite = mixtures of sodalite, analcime, phillipsite, and relict nepheline
 amphigène = leucite
 analcidite = analcime
 analcite = analcime
 analzim = analcime
 andreasbergolite = harmotome
 andreolite, andréolithe = harmotome
 antiédrite = edingtonite
 apoanalcite = natrolite
 arduinite = mordenite
 aricite = gismondine
 ashtonite = strontian mordenite
 bagotite = thomsonite
 barium-heulandite = barian heulandite
 barytkreuzstein = harmotome
 beaumontite = heulandite
 bergmannite = natrolite
 blätterzeolith = heulandite, stilbite
 brevicite = natrolite
 cabasite = chabazite
 caporcianite = laumontite
 carphostilbite = thomsonite
 chabasie, chabasite = chabazite
 christianite (of des Cloizeaux) = phillipsite
 cluthalite = analcime
 comptonite = thomsonite
 crocalite = natrolite
 cubicite, cubizit = analcime
 cubic zeolite = analcime?, chabazite
 cuboite = analcime
 cuboizite = chabazite
 desmine = stilbite
 diagonite = brewsterite
 dollanite = probably analcime
 doranite = analcime with thomsonite, natrolite, and Mg-rich clay minerals (Teertstra and Dyer, 1994)
 echellite = natrolite
 efflorescing zeolite = laumontite
 eisennatrolith = natrolite with other mineral inclusions
 ellagite = a ferrous natrolite or scolecite?
 epidesmine = stellerite
 epinatrolite = natrolite
 ercinite = harmotome
 eudnophite = analcime
 euthalite, euthallite = analcime
 euzeolith = heulandite
 falckenstenite = probably plagioclase (Raade, 1996)
 fargite = natrolite
 faröelite = thomsonite

NOMENCLATURE OF ZEOLITE MINERALS

fassaite (of Dolomieu) = probably stilbite	marburgite = phillipsite
feugasite = faujasite	mesole = thomsonite
flokite, flockit = mordenite	mesoline = levyne? chabazite?
foliated zeolite = heulandite, stilbite	mesolitine = thomsonite
foresite = stilbite + cookeite	mesotype = natrolite, mesolite, scolecite
galactite = natrolite	metachabazite = partially dehydrated chabazite
gibsonite = thomsonite	metadesmine = partially dehydrated stilbite
ginzburgite (of Voloshin <i>et al.</i>) = roggianite	metaepistilbite = partially dehydrated epistilbite
gismondite = gismondine	metaheulandite = partially dehydrated heulandite
glottalite = chabazite	metalaumontite = partially dehydrated laumontite
granatite = leucite	metaleonhardite = dehydrated 'leonhardite' (laumontite)
grenatite (of Daubenton) = leucite	metaleucite = leucite
grodeckite = gmelinite?	metamesolite = mesolite
hairzeolite (group name) = natrolite, thomsonite, mordenite	metanatrolite = partially dehydrated natrolite
harmotomite = harmotome	metascolecite, metaskolecit, metaskolezit = partially dehydrated scolecite
harringtonite = thomsonite, mesolite mixture	metathomsonite = partially dehydrated thomsonite
haydenite = chabazite	monophane = epistilbite
hegaut (högauite) = natrolite	mooraboolite = natrolite
hercynite (of Zappe) = harmotome	morvenite = harmotome
herschelite = chabazite-Na	natrochabazite = gmelinite
högauite = natrolite	natron-chabazit, natronchabazit (of Naumann) = gmelinite
hsiang-hua-shih = hsianghualite	natronite (in part) = natrolite
hydrocastorite = stilbite, mica, petalite mixture	needle zeolite, needle stone = natrolite, mesolite, scolecite
hydrolite (of Leman) = gmelinite	normalin = phillipsite
hydronatrolite = natrolite	orizite, oryzite = epistilbite
hydronephelite = a mixture, probably containing natrolite	ozarkite = thomsonite
hypodesmine = stilbite	parastilbite = epistilbite
hypostilbite = stilbite or laumontite	phacolite, phakolit(e) = chabazite
idrocastorite (hydrocastorite) = stilbite, mica, petalite mixture	picranalcime = analcime
kali-harmotome, kalkharmotome = phillipsite	microthomsonite = thomsonite
kalthomsonite = ashcroftine (not a zeolite)	pollux = pollucite
kalkkreuzstein = phillipsite	poonahlite, poonalite = mesolite
karphestilbite = thomsonite	portite = natrolite (Franzini and Perchiazzi, 1994)
kehoeite = a mixture including quartz, sphalerite, gypsum, and ?woodhouseite	potassium clinoptilolite = clinoptilolite-K
koodilite = thomsonite	pseudolaumontite = pseudomorphs after laumontite
krokalith = natrolite	pseudomesolite = mesolite
kubizit = analcime	pseudonatrolite = mordenite
kuboite = analcime	pseudophillipsite = phillipsite
laubanite = natrolite	ptilolite = mordenite
laumonite = laumontite	pufferite, pufferite = stilbite
ledererite, lederite (of Jackson) = gmelinite	punahlite = mesolite
lehuntite = natrolite	radiolite (of Esmark) = natrolite
leonhardite = H ₂ O-poor laumontite	ranite = gonnardite (Mason, 1957)
leuzit = leucite	reissite (of Fritsch) = epistilbite
levyine, levynite, levyite = levyne	retzite = stilbite?, laumontite?
lime-harmotome = phillipsite	sarcosite (of Vauquelin) = gmelinite
lime-soda mesotype = mesolite	sasbachite, saspachite = phillipsite?
lincolnine, lincolnite = heulandite	savite = natrolite
lintonite = thomsonite	schabazit = chabazite
lomonite = laumontite	schneiderite = laumontite (Franzini and

Perchiazzi, 1994)
 schol blanc = leucite
 scolesite, scolezit = scolecite
 scoulerite = thomsonite
 seebachite = chabazite
 skolezit = scolecite
 sloanite = laumontite?
 snaiderite (schneiderite) = laumontite
 soda-chabazite = gmelinite
 soda mesotype = natrolite
 sodium dachiardite = dachiardite-Na
 sommaite = leucite
 spangite = phillipsite
 sphaerodesmine, sphaerostilbite = thomsonite
 spreustein = natrolite (mostly)
 staurobaryte = harmotome
 steeleite, steelit = mordenite
 stellerycie = stellerite
 stilbite anamorphique = heulandite
 stilbite (of many German authors) = heulandite
 strontium-heulandite = strontian heulandite and
 heulandite-Sr
 svetlozarite = dachiardite-Ca
 syanhualite, syankhualite = hsianghualite
 syhadrite, syhedrite = impure stilbite?
 tetraedingtonite = edingtonite
 tonsonite = thomsonite
 triploclase, triploklase = thomsonite
 vanadio-laumontite = vanadian laumontite
 verrucite = mesolite
 Vesuvian garnet = leucite
 Vesuvian (of Kirwan) = leucite
 viséite = disordered crandallite and other phases
 weissian = scolecite
 wellsite = barian phillipsite-Ca and calcian
 harmotome
 white garnet = leucite
 winchellite = thomsonite
 Würfelzeolith = analcime, chabazite
 zeagonite = gismondine, phillipsite
 zeolite mimetica = dachiardite
 zéolithe efflorescente = laumontite

Acknowledgements

Members of the present Subcommittee, which commenced work in 1993, are grateful to a previous Subcommittee, established in 1979 under the Chairmanship of Professor W.S. Wise of the University of California, Santa Barbara, California, for work contained in a draft report completed in 1987. Members of the 1979 Subcommittee included L.P. van Reeuwijk and the late G. Gottardi and M.H. Hey, as well as

D.S.C. and H.M. of the present Subcommittee. J.V. Smith, W.M. Meier, R.W. Tschernich, and the late V.A. Frank-Kamenetskii were consultants. Although recommendations in the present report differ significantly from those in the 1987 report, the existence of that report has greatly facilitated our task. We thank J.V. Smith and L.B. McCusker for advice, C.E.S. Arps and W.D. Birch, successive secretaries of CNMMN, for much help, and many other colleagues for contributions of time, advice, and specimens. Staff of the Science Library, University of Otago, and others, helped trace obscure references.

References

- Akizuki, M. (1985) The origin of sector twinning in harmotome. *Amer. Mineral.*, **70**, 822–8.
- Akizuki, M. (1986) Al-Si ordering and twinning in edingtonite. *Amer. Mineral.*, **71**, 1510–4.
- Akizuki, M. (1987a) Crystal symmetry and order-disorder structure of brewsterite. *Amer. Mineral.*, **72**, 645–8.
- Akizuki, M. (1987b) An explanation of optical variation in yugawaralite. *Mineral. Mag.*, **51**, 615–20.
- Akizuki, M. and Konno, H. (1985) Order-disorder structure and the internal texture of stilbite. *Amer. Mineral.*, **70**, 814–21.
- Akizuki, M., Kudoh, Y. and Satoh, Y. (1993) Crystal structure of the orthorhombic {001} growth sector of stilbite. *Eur. J. Mineral.*, **5**, 839–43.
- Akizuki, M., Kudoh, Y. and Kuribayashi, T. (1996) Crystal structures of the {011}, {610}, and {010} growth sectors in brewsterite. *Amer. Mineral.*, **81**, 1501–6.
- Alberti, A. (1972) On the crystal structure of the zeolite heulandite. *Tschermaks Min. Petr. Mitt.*, **18**, 129–46.
- Alberti, A. (1975a) The crystal structure of two clinoptilolites. *Tschermaks Min. Petr. Mitt.*, **22**, 25–37.
- Alberti, A. (1975b) Sodium-rich dachiardite from Alpe di Siusi, Italy. *Contrib. Mineral. Petrol.*, **49**, 63–6.
- Alberti, A. and Sabelli, C. (1987) Statistical and true symmetry of ferrierite: possible absence of straight T–O–T bridging bonds. *Zeits. Kristallogr.*, **178**, 249–56.
- Alberti, A. and Vezzalini, G. (1979) The crystal structure of amicitte, a zeolite. *Acta Crystallogr.*, **B35**, 2866–9.
- Alberti, A. and Vezzalini, G. (1981a) A partially disordered natrolite: relationships between cell parameters and Si–Al distribution. *Acta Crystallogr.*, **B37**, 781–8.
- Alberti, A. and Vezzalini, G. (1981b) Crystal energies

NOMENCLATURE OF ZEOLITE MINERALS

- and coordination of ions in partially occupied sites: dehydrated mazzite. *Bull. Minéral.*, **104**, 5–9.
- Alberti, A., Hentschel, G. and Vezzalini, G. (1979) Amicite, a new natural zeolite. *Neues Jahrb. Mineral. Mh.*, 481–8.
- Alberti, A., Vezzalini, G. and Tazzoli, V. (1981) Thomsonite: a detailed refinement with cross checking by crystal energy calculations. *Zeolites*, **1**, 91–7.
- Alberti, A., Galli, E., Vezzalini, G., Passaglia, E. and Zanazzi, P.F. (1982a) Position of cations and water molecules in hydrated chabazite. Natural and Na-, Ca-, Sr- and K-exchanged chabazites. *Zeolites*, **2**, 303–9.
- Alberti, A., Pongiluppi, D. and Vezzalini, G. (1982b) The crystal chemistry of natrolite, mesolite and scolecite. *Neues Jahrb. Mineral. Abh.*, **143**, 231–48.
- Alberti, A., Galli, E., and Vezzalini, G. (1985) Epistilbite: an acentric zeolite with domain structure. *Zeits. Kristallogr.*, **173**, 257–65.
- Alberti, A., Cruciani, G. and Dauru', I. (1995) Order-disorder in natrolite-group minerals. *Eur. J. Mineral.*, **7**, 501–8.
- Alberti, A., Vezzalini, G., Galli, E. and Quartieri, S. (1996) The crystal structure of gottardiite, a new natural zeolite. *Eur. J. Mineral.*, **8**, 69–75.
- Alietti, A. (1972) Polymorphism and crystal-chemistry of heulandites and clinoptilolites. *Amer. Mineral.*, **57**, 1448–62.
- Armbruster, T. (1993) Dehydration mechanism of clinoptilolite and heulandite: Single-crystal X-ray study of Na-poor, Ca-, K-, Mg-rich clinoptilolite at 100 K. *Amer. Mineral.*, **78**, 260–4.
- Armbruster, T. and Kohler, T. (1992) Re- and dehydration of laumontite: a single-crystal X-ray study at 100 K. *Neues Jahrb. Mineral. Mh.*, 385–97.
- Artioli, G. (1992) The crystal structure of garronite. *Amer. Mineral.*, **77**, 189–96.
- Artioli, G. and Foy, H. (1994) Gobbinsite from Magheramome Quarry, Northern Ireland. *Mineral. Mag.*, **58**, 615–20.
- Artioli, G. and Kvik, Å. (1990) Synchrotron X-ray Rietveld study of perialite, the natural counterpart of synthetic zeolite-L. *Eur. J. Mineral.*, **2**, 749–59.
- Artioli, G. and Ståhl, K. (1993) Fully hydrated laumontite: A structure study by flat-plate and capillary powder diffraction techniques. *Zeolites*, **13**, 249–55.
- Artioli, G. and Torres Salvador, M.R. (1991) Characterization of the natural zeolite gonnardite. Structure analysis of natural and cation exchanged species by the Rietveld method. *Material Science Forum*, **79–82**, 845–50.
- Artioli, G., Smith, J.V. and Kvik, Å. (1984) Neutron diffraction study of natrolite, $\text{Na}_2\text{Al}_2\text{Si}_3\text{O}_{10}\cdot 2\text{H}_2\text{O}$, at 20 K. *Acta Crystallogr.*, **C40**, 1658–62.
- Artioli, G., Smith, J.V. and Pluth, J.J. (1986a) X-ray structure refinement of mesolite. *Acta Crystallogr.*, **C42**, 937–42.
- Artioli, G., Rinaldi, R., Kvik, Å. and Smith, J.V. (1986b) Neutron diffraction structure refinement of the zeolite gismondine at 15 K. *Zeolites*, **6**, 361–6.
- Artioli, G., Gottardi, G., Rinaldi, R., Satow Y., Horiuchi H., Ye J., Sawada H., Tanaka M. and Tokonami, M. (1987) A single crystal diffraction study of the natural zeolite cowlesite. *Photon Factory, National Laboratory for High Energy Physics, Activity Report 1987*, 316.
- Bartl, H. (1970) Strukturverfeinerung von Leonhardit, $\text{Ca}[\text{Al}_2\text{Si}_4\text{O}_{12}]\cdot 3\text{H}_2\text{O}$, mittels Neutronenbeugung. *Neues Jahrb. Mineral. Mh.*, 298–310.
- Baur, W.H. (1964) On the cation and water positions in faujasite. *Amer. Mineral.*, **49**, 697–704.
- Beger, R.M. (1969) The crystal structure and chemical composition of pollucite. *Zeits. Kristallogr.*, **129**, 280–302.
- Bergerhoff, G., Baur, W.H. and Nowacki, W. (1958) Über die Kristallstruktur des Faujasits. *Neues Jahrb. Mineral. Mh.*, 193–200.
- Beus, A.A. (1960). Geochemistry of Beryllium and the Genetic Types of Beryllium Deposits. *Akademi Nauk, SSSR, Inst. mineral., geokhim., i kristallochim. redkikh elementov*, 1–329 (in Russian). Abstract in *Amer. Mineral.*, **46**, 244.
- Bierniok, A., Joswig, W. and Baur, W. H. (1996). A study of paulingites: pore filling by cations and water molecules. *Neues Jahrb. Mineral. Abh.*, **171**, 119–34.
- Bissert, G. and Liebau, F. (1986) The crystal structure of a triclinic bikitaite, $\text{Li}[\text{AlSi}_2\text{O}_6]\cdot \text{H}_2\text{O}$, with ordered Al/Si distribution. *Neues Jahrb. Mineral. Mh.*, 241–52.
- Blackburn, W.H. and Dennen, W.H. (1997) Encyclopedia of Mineral Names. *Canad. Mineral., Spec. Pub.* **1**.
- Blumenbachs, J.F. (1791) Auszüge und Kezensioneit bergmanischer und mineralogischer Schriften. *Bergmannisches Journal*, **2**, 489–500.
- Boggs, R.C., Howard, D.G., Smith, J.V. and Klein, G.L. (1993) Tschernichite, a new zeolite from Goble, Columbia County, Oregon. *Amer. Mineral.*, **78**, 822–6.
- Boles, J.R. (1972) Composition, optical properties, cell dimensions, and thermal stability of some heulandite group zeolites. *Amer. Mineral.*, **57**, 1463–93.
- Bonardi, M. (1979) Composition of type dachiardite from Elba: a re-examination. *Mineral. Mag.*, **43**, 548–9.
- Bonardi, M., Roberts, A.C. and Sabina, A.P. (1981) Sodium-rich dachiardite from the Francon Quarry, Montreal Island, Quebec. *Canad. Mineral.*, **19**, 285–9.

- Bondi, M., Griffin, W.L., Mattioli, V. and Mottana, A. (1983) Chiavennite, $\text{CaMnBe}_2\text{Si}_5\text{O}_{13}(\text{OH})_2 \cdot 2\text{H}_2\text{O}$, a new mineral from Chiavenna (Italy). *Amer. Mineral.*, **68**, 623–7.
- Bosc D'Antic, L. (1792) Mémoire sur la chabazite. *Journal d'Histoire Naturelle*, **2**, 181–4.
- Breithaupt, A. (1846) Pollux. (Poggendorff's) *Annalen der Physik und Chemie* (Leipzig), **69**, 439.
- Brewster, D. (1825a) Description of gmelinite, a new mineral species. *Edinburgh J. Sci.*, **2**, 262–7.
- Brewster, D. (1825b) Description of levyne, a new mineral species. *Edinburgh J. Sci.*, **2**, 332–4.
- Brooke, H.J. (1820) On mesotype, needlestone, and thomsonite. *Ann. Phil.*, **16**, 193–4.
- Brooke, H.J. (1822) On the comptonite of Vesuvius, the brewsterite of Scotland, the stilbite and the heulandite. *Edinburgh Phil. J.*, **6**, 112–5.
- Cabella, R., Lucchetti, G., Palenzona, A., Quartieri, S. and Vezzalini, G. (1993) First occurrence of a Ba-dominant brewsterite: structural features. *Eur. J. Mineral.*, **5**, 353–60.
- Černý, P. (1974) The present status of the analcime-pollucite series. *Canad. Mineral.*, **12**, 334–41.
- Černý, P. and Simpson, F.M. (1978) The Tanco pegmatite at Bernic Lake, Manitoba. X. Pollucite. *Canad. Mineral.*, **16**, 325–33.
- Černý, P., Rinaldi, R. and Surdam, R.C. (1977) Wellsite and its status in the phillipsite-harmotome group. *Neues Jahrb. Mineral. Abh.*, **128**, 312–20.
- Chao, G.Y. (1980) Paranatrolite, a new zeolite from Mont St-Hilaire, Québec. *Canad. Mineral.*, **18**, 85–8.
- Chen, T.T. and Chao, G.Y. (1980) Tetrantrolite from Mont St-Hilaire, Québec. *Canad. Mineral.*, **18**, 77–84.
- Cho, M. and Liou, J.G. (1987) Prehnite-pumpellyite to greenschist facies transition in the Karmutsen metabasites, Vancouver Island, B. C. *J. Petrol.*, **28**, 417–43.
- Clark, A.M. (1993) *Hey's Mineral Index*. Chapman & Hall, London. 852 pp.
- Cocco, G. and Garavelli, C. (1958) Riesame di alcune zeoliti elbane. *Atti Soc. Toscana Scienze Naturali*, **65**, 262–83.
- Coombs, D.S. (1955) X-ray observations on wairakite and non-cubic analcime. *Mineral. Mag.*, **30**, 699–708.
- Coombs, D.S. and Whetten, J.T. (1967) Composition of analcime from sedimentary and burial metamorphic rocks. *Geol. Soc. Amer. Bull.*, **78**, 269–82.
- Cronstedt, A.F. (1756) Observation and description of an unknown kind of rock to be named zeolites (in Swedish). *Kongl. Vetenskaps Acad. Handl. Stockholm*, **17**, 120–3.
- D'Achiardi, G. (1906) Zeoliti del filone della Speranza presso S. Piero in Campo (Elba). *Atti Soc. Toscana Scienze Naturali*, **22**: 150–65.
- Damour, M. (1842) Description de la faujasite, nouvelle espèce minérale. *Annales des Mines*, series 4, **1**, 395–9.
- Dana, E.S. (1914) *A System of Mineralogy of J.D. Dana with Appendices I and II*, 6th ed., Wiley, New York.
- Dana, J.D. (1868) *A System of Mineralogy*, 5th ed. John Wiley & Sons, New York; 827 pp.
- Davis, R.J. (1958) Mordenite, ptilolite, flokite, and arduinite. *Mineral. Mag.*, **31**, 887–8.
- De Gennaro, M. and Franco, E. (1976) La K-chabazite di alcuni "Tufo del Vesuvio". *Rend. Acad. Naz. Lincei*, **40**, 490–7.
- Delamétherie, J.-C. de (1795) *Théorie de la Terre*, 1. Chez Maradan, Paris. 422 pp.
- Della Ventura, G., Parodi, G.C. and Burrigato, F. (1993) New data on merlinoite and related zeolites. *Rend. Lincei Sci. Fisiche e Naturali*, Series 9, **4**, 303–12.
- Di Franco, S. (1942) *Mineralogia Etnea*. Zuccarello & Izzi, Catania. p 158–61.
- Di Renzo, F. and Gabelica, Z. (1995) New data on the structure and composition of the silicoaluminophosphate viséite and a discreditation of its status as a zeolite. In *Natural Zeolites '93: Occurrence, Properties, Use*, (D.W. Ming and F.A. Mumpton, eds.), International Committee on Natural Zeolites, Brockport, New York, pp. 173–85.
- Di Renzo, F. and Gabelica, Z. (1997) Barrerite and other zeolites from Kuiu and Kupreanof islands, Alaska. *Canad. Mineral.*, **35**, 691–8.
- Dunn, P.J., Peacor, D.R., Newberry, N. and Ramik, R.A. (1980) Goosecreekite, a new calcium aluminum silicate hydrate possibly related to brewsterite and epistilbite. *Canad. Mineral.*, **18**, 323–7.
- Eakle, A.S. (1898) Erionite, a new zeolite. *Amer. J. Sci.*, series 4, **6**, 66–8.
- Eberly, P.E., Jr. (1964) Adsorption properties of naturally occurring erionite and its cationic-exchanged forms. *Amer. Mineral.*, **49**, 30–40.
- Effenberger, H., Giester, G. Krause, W. and Bernhardt, H.-J. (1998) Tschörnerite, a copper-bearing zeolite from the Bellberg volcano, Eifel, Germany. *Amer. Mineral.*, **83**, 607–17.
- Engel, N. and Yvon, K. (1984) The crystal structure of parthéite. *Zeits. Kristallogr.*, **169**, 165–75.
- England, B.M. and Ostwald, J. (1979) Levyne-offretite intergrowths from Tertiary basalts in the Merriwa district, Hunter Valley, New South Wales, Australia. *Australian Mineral.*, **25**, 117–9.
- Ercit, T.S. and Van Velthuizen, J. (1994) Gaultite, a new zeolite-like mineral species from Mont Saint-Hilaire, Quebec, and its crystal structure. *Canad. Mineral.*, **32**, 855–63.
- Fersman, A.E. (1908) Materialien zur Untersuchung der Zeolithe Russlands. I. Leonhardt und Laumontit aus der Umgebung von Simferopol (Krim). *Trav. de*

- Musée géol. Pierre le Grand pr. l'Acad. Imp. de Science St Pétersbourg*, **2**, 103–50. (Abstract in *Zeits. Kristallogr.*, **50**, 75–6.)
- Fischer, K. (1966) Untersuchung der Kristallstruktur von Gmelinit. *Neues Jahrb. Mineral. Mh.*, 1–13.
- Fischer K.F. and Schramm V. (1970) Crystal structure of gismondite, a detailed refinement. In *Molecular Sieve Zeolites. Amer. Chem. Soc. Advances in Chemistry Series*, **101**, 250–8.
- Franzini, M. and Perchiazzi, N. (1994) Portite discredited = natrolite and new data on "schneiderite" (= laumontite). *Eur. J. Mineral.*, **6**, 351–3.
- Fuchs, J.N. (1816) Ueber die Zeolithe. (*Schweigger's*) *Journ. für Chem. und Phys.*, **18**, 1–29.
- Galli, E. (1971) Refinement of the crystal structure of stilbite. *Acta Crystallogr.*, **B27**, 833–41.
- Galli, E. (1975) Crystal structure refinement of mazzite. *Rend. Soc. Ital. Mineral. Petrol.*, **31**, 599–612.
- Galli, E. (1976) Crystal structure refinement of edingtonite. *Acta Crystallogr.*, **B32**, 1623–7.
- Galli, E. (1980) The crystal structure of roggianite, a zeolite-like silicate. In *Proc. 5th Int. Conf. on Zeolites* (L.V.C. Rees, ed.) Heyden, London, 205–13.
- Galli, E. and Alberti, A. (1975a) The crystal structure of stellerite. *Bull. Soc. fr. Minéral. Cristallogr.*, **98**, 11–18.
- Galli, E. and Alberti, A. (1975b) The crystal structure of barrerite. *Bull. Soc. fr. Minéral. Cristallogr.*, **98**, 331–40.
- Galli, E. and Gottardi, G. (1966) The crystal structure of stilbite. *Mineral. Petrog. Acta (Bologna)*, **12**, 1–10.
- Galli, E. and Loschi Ghittoni, A.G. (1972) The crystal chemistry of phillipsites. *Amer. Mineral.*, **57**, 1125–45.
- Galli, E. and Rinaldi, R. (1974) The crystal chemistry of epistilbites. *Amer. Mineral.*, **59**, 1055–61.
- Galli, E., Passaglia, E., Pongiluppi, D. and Rinaldi, R. (1974) Mazzite, a new mineral, the natural counterpart of the synthetic zeolite Ω . *Contrib. Mineral. Petrol.*, **45**, 99–105.
- Galli, E., Gottardi, G. and Pongiluppi, D. (1979) The crystal structure of the zeolite merlinoite. *Neues Jahrb. Mineral. Mh.*, 1–9.
- Galli, E., Rinaldi, R. and Modena, C. (1981) Crystal chemistry of levynes. *Zeolites*, **1**, 157–60.
- Galli, E., Passaglia, E. and Zanazzi, P.F. (1982) Gmelinite: structural refinements of sodium-rich and calcium-rich natural crystals. *Neues Jahrb. Mineral. Mh.*, 145–55.
- Galli, E., Quartieri, S., Vezzalini, G. and Alberti, A. (1995) Boggsite and tschernichite-type zeolites from Mt. Adamson, Northern Victoria Land (Antarctica). *Eur. J. Mineral.*, **7**, 1029–32.
- Galli, E., Quartieri, S., Vezzalini, G. and Alberti, A. (1996) Gottardiite, a new high-silica zeolite from Antarctica: the natural counterpart of synthetic NU-87. *Eur. J. Mineral.*, **8**, 687–93.
- Galli, E., Quartieri, S., Vezzalini, G., Alberti, A. and Franzini, M., (1997a) Terranovaite from Antarctica: a new 'pentasil' zeolite. *Amer. Mineral.*, **82**, 423–9.
- Galli, E., Vezzalini, G., Quartieri, S., Alberti, A. and Franzini, M., (1997b) Mutinaite, a new zeolite from Antarctica: the natural counterpart of ZSM-5. *Zeolites*, **19**, 318–22.
- Gard, J.A. and Tait, J.M. (1972) The crystal structure of the zeolite offretite, $K_{1.1}Ca_{1.1}Mg_{0.7}[Si_{12.8}Al_{5.2}O_{36}] \cdot 15.2H_2O$. *Acta Crystallogr.*, **B28**, 825–34.
- Gehlen, A.F. and Fuchs, J.N. (1813) Ueber Werner's Zeolith, Haüy's Mesotype und Stilbite. (*Schweigger's*) *Journ. für Chem. und Phys.*, **8**, 353–66.
- Gismondi C.G. (1817) Osservazioni sopra alcuni fossili particolari de' contorni di Roma. *Giornale Enciclopedico di Napoli*, Anno XI, **2**, 3–15.
- Giuseppetti, G., Mazzi, F., Tadini, C., Galli, E. (1991) The revised crystal structure of roggianite: $Ca_2[Be(OH)_2Al_2Si_4O_{13}] < 2.5H_2O$. *Neues Jahrb. Mineral. Mh.*, 307–14.
- Gonnard, F. (1890) Sur l'offrétite, espèce minérale nouvelle. *C. R. Acad. Sci., Paris*, **111**, 1002–3.
- Gordon, E.K., Samson, S. and Kamb, W.B. (1966) Crystal structure of the zeolite paulingite. *Science*, **154**, 1004–7.
- Gottardi, G. and Alberti, A. (1974) Domain structure in garronite: a hypothesis. *Mineral. Mag.*, **39**, 898–9.
- Gottardi, G. and Galli, E. (1985) *Natural Zeolites*. Springer-Verlag, Berlin, Heidelberg, New York, Tokyo, 409 pp.
- Gottardi, G. and Meier, W.M. (1963) The crystal structure of dachiardite. *Zeits. Kristallogr.*, **119**, 53–64.
- Graham, R.P.D. (1918) On ferrierite, a new zeolitic mineral, from British Columbia; with notes on some other Canadian minerals. *Trans. Roy. Soc. Canada*, Series 3, **12**, 185–201.
- Gramlich-Meier, R., Gramlich, V. and Meier, W.M. (1985) The crystal structure of the monoclinic variety of ferrierite. *Amer. Mineral.*, **70**, 619–23.
- Haidinger, W. (1825) Description of edingtonite, a new mineral species. *Edinburgh J. Sci.*, **3**, 316–20.
- Harada, K., Iwamoto, S. and Kihara, K. (1967) Erionite, phillipsite and gonnardite in the amygdales of altered basalt from Mazé, Niigata Prefecture, Japan. *Amer. Mineral.*, **52**, 1785–94.
- Hassan, I. (1997) Feldspathoids and their relationships to zeolites. *Kuwait Journal of Science and Engineering*, **24**, 163–87.
- Haüy, R.J. (1797) Analcime. *Journal des Mines*, **5**, 278–9.
- Haüy, R.J. (1801) *Traité de minéralogie*, **3**. Chez Louis, Paris.

- Haüy, R.J. (1809) *Tableau comparatif des résultats de cristallographie et de l'analyse chimique relative à la classification des minéraux*. Courcier, Paris.
- Hazen, R.M. and Finger, L.W. (1979) Polyhedral tilting: a common type of pure displacive phase transition and its relationship to analcite at high pressure. *Phase Transitions*, **1**, 1–22.
- Heaney, P.J. and Veblen, D.R. (1990) A high-temperature study of the low-high leucite phase transition using the transmission electron microscope. *Amer. Mineral.*, **75**, 464–76.
- Hesse, K.-F. (1983) Refinement of a partially disordered natrolite, $\text{Na}_2\text{Al}_2\text{Si}_3\text{O}_{10}\cdot 2\text{H}_2\text{O}$. *Zeits. Kristallogr.*, **163**, 69–74.
- Hey, M.H. (1930) Studies on the zeolites. Part I. General review. *Mineral. Mag.*, **22**, 422–37.
- Hey, M.H. (1960) Glottalite is chabazite. *Mineral. Mag.*, **32**, 421–2.
- Hey, M.H. (1962) *An Index of Mineral Species and Varieties Arranged Chemically*. 2nd ed. (and Appendices: 1963, 135 pp., and 1974, 168 pp.), British Museum, London. 728 pp.
- Hintze, C. (1897) *Handbuch der Mineralogie*, **2**, Von Veit, Leipzig.
- Hori, H., Nagashima, K., Yamada, M., Miyawaki, R. and Marubashi, T. (1986) Ammonioleucite, a new mineral from Tatarazawa, Fujioka, Japan. *Amer. Mineral.*, **71**, 1022–7.
- How, H. (1864) On mordenite, a new mineral from the trap of Nova Scotia. *J. Chem. Soc.*, 17 (new series), 17, 100–4.
- Howard D.G. (1994) Crystal habit and twinning of garronite from Fara Vicentina, Vicenza (Italy). *Neues Jahrb. Mineral. Mh.*, 91–6.
- Howard, D.G., Tschernich, R.W., Smith, J.V. and Klein, G.L. (1990) Boggsite, a new high-silica zeolite from Goble, Columbia County, Oregon. *Amer. Mineral.*, **75**, 1200–4.
- Huang, Wen-Hui, Tu, Shao-Hua, Wang, K'ung-Hai, Chao, Chun-Lin and Yu, Cheng-Chi (1958). Hsiang-hua-shih, a new beryllium mineral. Ti-chih-yueh-k'an, **7**, 35. (Abstracts in *Amer. Mineral.*, **44**, 1327–8; **46**, 244).
- Hurlbut, C.S., Jr. (1957) Bikitaite $\text{LiAlSi}_2\text{O}_6\cdot\text{H}_2\text{O}$, a new mineral from Southern Rhodesia. *Amer. Mineral.*, **42**, 792–7.
- Ibrahim, K. and Hall, A. (1995) New occurrences of diagenetic faujasite in the Quaternary tuffs of north-east Jordan. *Eur. J. Mineral.*, **7**, 1129–35.
- Iijima, A. and Harada, K. (1969) Authigenic zeolites in zeolitic palagonite tuffs on Oahu, Hawaii. *Amer. Mineral.*, **54**, 182–97.
- Jameson, R. (1805) *System of Mineralogy*, **2**, Bell and Bradfute, Edinburgh, U.K. (p. 539).
- Joswig, W., Bartl, H. and Fuess, H. (1984) Structure refinement of scolecite by neutron diffraction. *Zeits. Kristallogr.*, **166**, 219–23.
- Kamb, W.B. and Oke, W.C. (1960) Paulingite, a new zeolite, in association with erionite and filiform pyrite. *Amer. Mineral.*, **45**, 79–91.
- Kawahara, A. and Curien, H. (1969) La structure cristalline de l'érieronite. *Bull. Soc. fr. Minéral. Cristallog.*, **92**, 250–6.
- Kerr, I.S. and Williams, D.J. (1969) The crystal structure of yugawaralite. *Acta Crystallogr.*, **B25**, 1183–90.
- Khomyakov, A.P., Sandomirskaya, S.M. and Malinovskii, Yu.A. (1980) Kalborsite, $\text{K}_6\text{BaAl}_4\text{Si}_6\text{O}_{20}(\text{OH})_4\text{Cl}$, a new mineral. *Dokl. Acad. Nauk SSSR*, **252**, 1465–8 (in Russian).
- Khomyakov, A.P., Cherepivskaya, G. Ye., Kurova, T.A. and Kaptsov, V.V. (1982) Amichit, $\text{K}_2\text{Na}_2\text{Al}_4\text{Si}_4\text{O}_{16}\cdot 5\text{H}_2\text{O}$, first find in the USSR. *Dokl. Acad. Nauk SSSR*, **263**, 978–80 (in Russian).
- Kim, Y. and Kirkpatrick, R.J. (1996) Application of MAS NMR spectroscopy to poorly crystalline materials: viséite. *Mineral. Mag.*, **60**, 957–62.
- Klaproth, M.H. (1803) Chemische Untersuchung des Natroliths. *Ges. Naturforschender Freunde zu Berlin, Neue Schriften*, **4**, 243–8.
- Kocman, V., Gait, R.I. and Rucklidge, J. (1974) The crystal structure of bikitaite, $\text{Li}[\text{AlSi}_2\text{O}_6]\cdot\text{H}_2\text{O}$. *Amer. Mineral.*, **59**, 71–8.
- Koyama, K. and Takéuchi, Y. (1977) Clinoptilolite: the distribution of potassium atoms and its role in thermal stability. *Zeits. Kristallogr.*, **145**, 216–39.
- Krause, W., Bernhardt, H.-J., Effenberger, H. and Giester, G. (1997) Tschörtnerite, a copper-bearing zeolite from the Bellberg volcano, Eifel, Germany. (Abstract) *Ber. Deutsch. Mineral. Ges.*, **1**, 205.
- Krogh Andersen, E., Danø, M. and Petersen, O.V. (1969) A tetragonal natrolite. *Med. om Grønland*, **181**, 1–19.
- Kvick, Å., Ståhl, K. and Smith, J.V. (1985) A neutron diffraction study of the bonding of zeolitic water in scolecite at 20 K. *Zeits. Kristallogr.*, **171**, 141–54.
- Kvick A., Artioli G. and Smith J.V. (1986) Neutron diffraction study of the zeolite yugawaralite at 13 K. *Zeits. Kristallogr.*, **174**, 265–81.
- Lacroix, A. (1896) Sur la gonnardite. *Bull. Soc. fr. Minéral.*, **19**: 426–9.
- Langhof, J. and Holstam, D. (1994) Boron-bearing chivannite and other late-stage minerals of the Proterozoic lithium-pegmatites of Utö, Stockholm, Sweden. *Int. Mineral. Ass., 16th Gen. Meet., Pisa, Italy. Abstr.*, 232.
- Larsen, A. O., Åsheim, A., Raade, G. and Taftø, J. (1992) Tvedalite, $(\text{Ca},\text{Mn})_4\text{Be}_3\text{Si}_6\text{O}_{17}(\text{OH})_4\cdot 3\text{H}_2\text{O}$, a new mineral from syenite pegmatite in the Oslo Region, Norway. *Amer. Mineral.*, **77**, 438–43.
- Leimer H.W. and Slaughter M. (1969) The determination and refinement of the crystal structure of

NOMENCLATURE OF ZEOLITE MINERALS

- yugawaralite. *Zeits. Kristallogr.*, **130**, 88–111.
- Lengauer, C.L., Giester, G. and Tillmanns, E. (1997) Mineralogical characterization of paulingite from Vinarická Hora, Czech Republic. *Mineral. Mag.*, **61**, 591–606.
- Leonhard K. C. von (1817) Die Zeagonit ein neues Mineral vom Capo do Bove bei Rom. *Taschenbuch für die gesammte Mineralogie mit Hinsicht auf die neuesten Entdeckungen*, **11**, 164–8. (Extracted from Gismondi, 1817, with footnotes added).
- Leonhard K. C. von (1821) *Handbuch der Oryktognosie*. Mohr & Winter, Heidelberg. p. 448.
- Levinson, A. A. (1966) A system of nomenclature for rare-earth minerals. *Amer. Mineral.*, **51**, 152–8.
- Lévy, A. (1825) Descriptions of two new minerals. *Annals of Philosophy*, new ser., **10**, 361–3.
- Lo, H.-J. and Hsieh, Y.-L. (1991) High potassium natural mordenite and the chemical variation of mordenite. *Proc. Geol. Soc. China* (Taiwan), **34**, 305–12.
- Lo, H.-J., Song, S.-R. and Wen, S.-B. (1991) High potassium mordenite in the andesite from the Coastal Range, Eastern Taiwan. *Proc. Geol. Soc. China* (Taiwan), **34**, 293–304.
- Lucchetti, G., Massa, B. and Penco, A.M. (1982) Strontian heulandite from Campegli (Eastern Ligurian ophiolites, Italy). *Neues Jahrb. Mineral. Mh.*, 541–50.
- Malinovskii, Yu.A. (1984) The crystal structure of K-gmelinite. *Kristallografiya*, **29**, 426–30 (in Russian).
- Malinovskii, Yu.A. and Belov, N.V. (1980) Crystal structure of kalborsite. *Dokl. Acad. Nauk SSSR*, **252**, 611–5 (in Russian).
- Mason, B.H. (1957) Gonnardite (ranite) from Langesundsfjord. *Norsk geol. Tidsskr.*, **37**, 435–7.
- Mazzi, F. and Galli, E. (1978) Is each analcime different? *Amer. Mineral.*, **63**, 448–60.
- Mazzi, F. and Galli, E. (1983) The tetrahedral framework of chabazite. *Neues Jahrb. Mineral. Mh.*, 461–80.
- Mazzi, F., Galli, E. and Gottardi, G. (1976) The crystal structure of tetragonal leucite. *Amer. Mineral.*, **61**, 108–15.
- Mazzi, F., Galli, E. and Gottardi, G. (1984) Crystal structure refinement of two tetragonal edingtonites. *Neues Jahrb. Mineral. Mh.*, 373–82.
- Mazzi, F., Larsen, A.O., Gottardi, G. and Galli, E. (1986) Gonnardite has the tetrahedral framework of natrolite: experimental proof with a sample from Norway. *Neues Jahrb. Mineral. Mh.*, 219–28.
- McConnell, D. (1964) A zinc phosphate analogue of analcime: kehoeite. *Mineral. Mag.*, **33**, 799–803.
- McCusker, L.B., Baerlocher, C. and Nawaz, R. (1985) Rietveld refinement of the crystal structure of the new zeolite mineral gobbinsite. *Zeits. Kristallogr.*, **171**, 281–9.
- Meier, W.M. (1961) The crystal structure of mordenite (ptilolite). *Zeits. Kristallogr.*, **115**, 439–50.
- Meier, W.M., Olson, D.H. and Baerlocher, C. (1996) Atlas of zeolite structure types. *Zeolites*, **17**, 1–230.
- Men'shikov Yu.P. (1984) Perllialite, $K_9Na(Ca,Sr)[Al_{12}Si_{24}O_{72}] \cdot 15H_2O$, a new potassian zeolite from the Khibina Massif. *Zap. Vses. Mineral. Obshch.*, **113**, 607–12 (in Russian).
- Men'shikov, Yu.P., Denisov, A.P., Uspenskaya, E.I. and Lipatova, E.A. (1973) Lovdarite, a new hydrous beryllsilicate of alkalies. *Doklady Akademii Nauk SSSR*, **213**, 429–32 (in Russian).
- Merkle, A.B. and Slaughter, M. (1968) Determination and refinement of the structure of heulandite. *Amer. Mineral.*, **53**, 1120–38.
- Merlino, S. (1972) Orizite discredited (= epistilbite). *Amer. Mineral.*, **57**, 592–3.
- Merlino, S. (1974) The crystal structure of wenkite. *Acta Crystallogr.*, **B30**, 1262–8.
- Merlino, S. (1990) Lovdarite, $K_4Na_{12}(Be_8Si_{28}O_{72}) \cdot 18H_2O$, a zeolite-like mineral: structural features and OD character. *Eur. J. Mineral.*, **2**, 809–17.
- Merlino, S., Galli, E. and Alberti, A. (1975) The crystal structure of levyne. *Tschermaks Min. Petr. Mitt.*, **22**, 117–29.
- Minato, H. and Takano, T. (1964) An occurrence of potassium clinoptilolite from Itaya, Yamagata Prefecture, Japan. *J. Clay Sci. Soc. Japan*, **4**, 12–22 (in Japanese with English abstract).
- Mizota, T., Shibuya, G., Shimazu, M. and Takeshita, Y. (1974) Mineralogical studies on levyne and erionite from Japan. *Mem. Geol. Soc. Japan*, **11**, 283–90.
- Morozewicz, J. (1909) Über Stellerit, ein neues Zeolithmineral. *Bull. International de l'Académie des Sciences de Cracovie*, 1909, 344–59.
- Mumpton, F.A. (1960) Clinoptilolite redefined. *Amer. Mineral.*, **45**, 351–69.
- Nakajima, W. (1983) Disordered wairakite from Hikihara, Haga Town, Hyōgo Prefecture. *Bull. Faculty of Education, Kobe University*, **70**, 39–46.
- Nawaz R. (1983) New data on gobbinsite and garronite. *Mineral. Mag.*, **47**, 567–8.
- Nawaz, R. (1984) New data on cowlesite from Northern Ireland. *Mineral. Mag.*, **48**, 565–6.
- Nawaz R. and Malone J.F. (1982) Gobbinsite, a new zeolite mineral from Co. Antrim, N. Ireland. *Mineral. Mag.*, **46**, 365–9.
- Nickel, E.H. and Mandarino, J.A. (1987) Procedures involving the IMA Commission on New Minerals and Mineral Names, and guidelines on mineral nomenclature. *Amer. Mineral.*, **72**, 1031–42.
- Nørnberg, P. (1990) A potassium-rich zeolite in soil development on Danian chert. *Mineral. Mag.*, **54**, 91–4.
- Ogihara, S. and Iijima, A. (1990) Exceptionally K-rich

- clinoptilolite – heulandite group zeolites from three offshore boreholes off northern Japan. *Eur. J. Mineral.*, **2**, 819–26.
- Passaglia, E. (1969a) Le zeoliti di Albergo Bassi (Vicenza). *Periodico Mineral.* **38**, 237–43.
- Passaglia, E. (1969b) Roggianite, a new silicate mineral. *Clay Minerals*, **8**, 107–11.
- Passaglia, E. (1970) The crystal chemistry of chabazites. *Amer. Mineral.*, **55**, 1278–301.
- Passaglia, E. (1975) The crystal chemistry of mordenites. *Contrib. Mineral. Petrol.*, **50**, 65–77.
- Passaglia, E. and Pongiluppi, D. (1974) Sodian stellerite from Capo Pula, Sardegna. *Lithos*, **7**, 69–73.
- Passaglia, E. and Pongiluppi, D. (1975) Barrerite, a new natural zeolite. *Mineral. Mag.*, **40**, 208.
- Passaglia, E. and Sacerdoti, M. (1982) Crystal structural refinement of Na-exchanged stellerite. *Bull. Minéral.*, **105**, 338–42.
- Passaglia, E. and Tagliavini, A. (1994) Chabazite-offretite epitaxial overgrowths in cornubianite from Passo Forcel Rosso, Adamello, Italy. *Eur. J. Mineral.*, **6**, 397–405.
- Passaglia, E. and Vezzalini, G. (1985) Crystal chemistry of diagenetic zeolites in volcanoclastic deposits of Italy. *Contrib. Mineral. Petrol.*, **90**, 190–8.
- Passaglia, E. and Vezzalini, G. (1988) Roggianite: revised chemical formula and zeolitic properties. *Mineral. Mag.*, **52**, 201–6.
- Passaglia, E., Galli, E. and Rinaldi, R. (1974) Levynes and erionites from Sardinia, Italy. *Contrib. Mineral. Petrol.*, **43**, 253–9.
- Passaglia, E., Pongiluppi, D. and Rinaldi, R. (1977) Merlinoite, a new mineral of the zeolite group. *Neues Jahrb. Mineral. Mh.*, 355–64.
- Passaglia, E., Pongiluppi, D. and Vezzalini, G. (1978a) The crystal chemistry of gmelinites. *Neues Jahrb. Mineral. Mh.*, 310–24.
- Passaglia, E., Galli, E., Leoni, L. and Rossi, G. (1978b) The crystal chemistry of stilbites and stellerites. *Bull. Minéral.*, **101**, 368–75.
- Passaglia, E., Vezzalini, G. and Carnevali, R. (1990) Diagenetic chabazites and phillipsites in Italy: crystal chemistry and genesis. *Eur. J. Mineral.*, **2**, 827–39.
- Passaglia, E., Artioli, G., Gualtieri, A. and Carnevali, R. (1995) Diagenetic mordenite from Ponza, Italy. *Eur. J. Mineral.*, **7**, 429–38.
- Passaglia, E., Artioli, G. and Gualtieri, A. (1998) The crystal chemistry of the zeolites erionite and offretite. *Amer. Mineral.*, **83**, 577–89.
- Peacor, D.R. (1968) A high temperature single crystal diffractometer study of leucite, (K,Na)AlSi₂O₆. *Zeits. Kristallogr.*, **127**, 213–24.
- Peacor, D.R., Dunn, P.J., Simmons, W.B., Tillmanns, E. and Fischer, R.X. (1984) Willhendersonite, a new zeolite isostructural with chabazite. *Amer. Mineral.*, **69**, 186–9.
- Peacor, D.R., Dunn, P.J., Simmons, W.B., Wicks, F.J. and Raudsepp, M. (1988) Maricopaite, a new hydrated Ca-Pb, zeolite-like silicate from Arizona. *Canad. Mineral.*, **26**, 309–13.
- Pekov, I.V. and Chukanov, N.V. (1996) New data on kalborsite. *Zap. Vses. Mineral. Obshch.*, **125**(4), 55–9 (in Russian).
- Perrotta, A.J. (1967) The crystal structure of epistilbite. *Mineral. Mag.*, **36**, 480–90.
- Perrotta, A.J. and Smith, J.V. (1964) The crystal structure of brewsterite, (Sr,Ba,Ca)₂(Al₄Si₁₂O₃₂)·10H₂O. *Acta Crystallogr.*, **17**, 857–62.
- Pirsson, L. V. (1890) On mordenite. *Amer. J. Sci.*, series 3, **40**, 232–7.
- Pluth, J.J. and Smith, J.V. (1990) Crystal structure of boggsite, a new high-silica zeolite with the first three-dimensional channel system bounded by both 12- and 10-rings. *Amer. Mineral.*, **75**, 501–7.
- Pluth, J.J., Smith, J.V., Howard, D.G. and Tschernich, R.W. (1989) Boggsite; the first three-dimensional channel system with both 12-and 10-rings. In *Zeolites for the Nineties, Recent Research Reports* (J.C. Jansen, L. Moscou and M.F.M. Post, eds.), 8th Int. Zeolite Conf., Amsterdam, p. 111–2.
- Quartieri, S. and Vezzalini, G. (1987) Crystal chemistry of stilbites: structure refinements of one normal and four chemically anomalous samples. *Zeolites*, **7**, 163–70.
- Quartieri, S., Vezzalini, G. and Alberti, A. (1990) Dachardite from Hokiya-dake: evidence of a new topology. *Eur. J. Mineral.*, **2**, 187–93.
- Raade, G. (1996) Minerals originally described from Norway. Including notes on type material. *Norsk Bergverksmuseums Skriftserie*, **11**, 107 pp.
- Raade, G., Åmli, R., Mladeck, M.H., Din, V.K., Larsen, A.O. and Åsheim, A. (1983) Chiavennite from syenite pegmatites in the Oslo region, Norway. *Amer. Mineral.*, **68**, 628–33.
- Rastsvetaeva, R.K., Rekhlova, O.Y., Andrianov, V. and Malinovskii, Y.A. (1991) Crystal structure of hsianghualite. *Doklady Akademii Nauk SSSR*, **316**, 624–8 (in Russian).
- Rinaldi, R. (1976) Crystal chemistry and structural epitaxy of offretite-erionite from Sasbach, Kaiserstuhl. *Neues Jahrb. Mineral. Mh.*, 145–56.
- Rinaldi, R. and Vezzalini, G. (1985) Gismondine; the detailed x-ray structure refinement of two natural samples. In *Zeolites; synthesis, structure, technology and application* (B. Držaj, S. Hočevár and S. Pejovnik, eds.), Elsevier, p. 481–92.
- Rinaldi, R., Pluth, J.J. and Smith, J.V. (1974) Zeolites of the phillipsite family. Refinement of the crystal structures of phillipsite and harmotome. *Acta Crystallogr.*, **B30**, 2426–33.
- Rinaldi, R., Smith, J.V. and Jung, G. (1975a) Chemistry

NOMENCLATURE OF ZEOLITE MINERALS

- and paragenesis of faujasite, phillipsite and offretite from Sasbach, Kaiserstuhl, Germany. *Neues Jahrb. Mineral. Mh.*, 433–43.
- Rinaldi, R., Pluth, J.J. and Smith, J.V. (1975b) Crystal structure of mazzite dehydrated at 600°C. *Acta Crystallogr.*, **B31**, 1603–8.
- Robinson, G.W. and Grice, J.D. (1993) The barium analog of brewsterite from Harrisville, New York. *Canad. Mineral.*, **31**, 687–90.
- Rose, G. (1826). Ueber den Epistilbit, eine neue zur Familie der Zeolithe gehörige Mineralgattung. (*Poggendorff's*) *Annalen der Physik und Chemie* (Leipzig), **6**, 183–90.
- Ross, C.S. and Shannon, E.V. (1924) Mordenite and associated minerals from near Challis, Custer County, Idaho. *Proc. US Nat. Museum*, **64** (19), 1–19.
- Ross, M., Flohr, M.J.K. and Ross, D.R. (1992) Crystalline solution series and order-disorder within the natrolite mineral group. *Amer. Mineral.*, **77**, 685–703.
- Rouse, R.C. and Peacor, D.R. (1986) Crystal structure of the zeolite mineral goosecreekite, $\text{CaAl}_2\text{Si}_6\text{O}_{16}\cdot 5\text{H}_2\text{O}$. *Amer. Mineral.*, **71**, 1494–501.
- Rouse, R.C. and Peacor, D.R. (1994) Maricopaite, an unusual lead calcium zeolite with an interrupted mordenite-like framework and intrachannel Pb_4 tetrahedral clusters. *Amer. Mineral.*, **79**, 175–84.
- Rouse, R.C., Peacor, D.R., Dunn, P.J., Campbell, T.J., Roberts, W.L., Wicks, F. and Newbury, D. (1987) Pahasapaite, a berylllophosphate zeolite related to synthetic zeolite rho, from the Tip Top Pegmatite of South Dakota. *Neues Jahrb. Mineral. Mh.*, 433–40.
- Rouse, R.C., Peacor, D.R. and Merlino, S. (1989) Crystal structure of pahasapaite, a berylllophosphate mineral with a distorted zeolite rho framework. *Amer. Mineral.*, **74**, 1195–202.
- Rouse, R.C., Dunn, P.J., Grice, J.D., Schlenker, J.L. and Higgins, J.B. (1990) Montesommaite, $(\text{K},\text{Na})_9\text{Al}_9\text{Si}_{23}\text{O}_{64}\cdot 10\text{H}_2\text{O}$, a new zeolite related to merlinoite and the gismondine group. *Amer. Mineral.*, **75**, 1415–20.
- Rüdinger, B., Tillmanns, E. and Hentschel, G. (1993) Bellbergite – a new mineral with the zeolite structure type EAB. *Mineral. Petrol.*, **48**, 147–52.
- Sakurai K. and Hayashi A. (1952) "Yugawaralite", a new zeolite. *Sci. Rep. Yokohama Nat. Univ., Ser. II*, **1**, 69–77.
- Sarp, H., Deferne, J., Bizouard, H. and Liebich, B.W. (1979) La parthéite, $\text{CaAl}_2\text{Si}_2\text{O}_8\cdot 2\text{H}_2\text{O}$, un nouveau silicate naturel d'aluminium et de calcium. *Schweiz. mineral. petrog. Mitt.*, **59**, 5–13.
- Schaller, W.T. (1923) Ptilolite and related zeolites. In: *Proceedings of Societies* (E.T. Wherry, ed.). *Amer. Mineral.*, **8**, 93–4.
- Schaller, W.T. (1932) The mordenite-ptilolite group; clinoptilolite, a new species. *Amer. Mineral.*, **17**, 128–34.
- Schlenker, J.L., Pluth, J.J. and Smith, J.V. (1977a) Refinement of the crystal structure of brewsterite, $\text{Ba}_{0.5}\text{Sr}_{1.5}\text{Al}_4\text{Si}_{12}\text{O}_{32}\cdot 10\text{H}_2\text{O}$. *Acta Crystallogr.*, **B33**, 2907–10.
- Schlenker, J.L., Pluth, J.J. and Smith, J.V. (1977b) Dehydrated natural erionite with stacking faults of the offretite type. *Acta Crystallogr.*, **B33**, 3265–8.
- Schröpfer, L. and Joswig, W. (1997) Structure analyses of a partially dehydrated synthetic Ca-garronite single crystal under different T, $\text{P}_{\text{H}_2\text{O}}$ conditions. *Eur. J. Mineral.*, **9**, 53–65.
- Seki, Y. (1971) Wairakite-analcime solid solution as an indicator of water pressures in low-grade metamorphism. *J. Geol. Soc. Japan*, **77**, 667–74.
- Seki, Y. and Oki, Y. (1969) Wairakite-analcime solid solutions from low-grade metamorphic rocks of the Tanzawa Mountains, Central Japan. *Mineral. J.*, **6**, 36–45.
- Sheppard, R.A. and Fitzpatrick, J.J. (1989) Phillipsite from silicic tuffs in saline, alkaline-lake deposits. *Clays and Clay Minerals*, **37**, 243–7.
- Sheppard, R.A. and Gude, A.J., 3d (1969a) Diagenesis of tuffs in the Barstow Formation, Mud Hills, San Bernardino County, California. *US Geol. Surv. Prof. Paper* **634**, 1–35.
- Sheppard, R.A. and Gude, A.J., 3d (1969b) Chemical composition and physical properties of the related zeolites offretite and erionite. *Amer. Mineral.*, **54**, 875–86.
- Sheppard, R.A., Gude, A.J., 3d and Munson, E.L. (1965) Chemical composition of diagenetic zeolites from tuffaceous rocks of the Mojave Desert and vicinity, California. *Amer. Mineral.*, **50**, 244–9.
- Sheppard, R.A., Gude, A.J., 3d and Griffin, J.J. (1970) Chemical composition and physical properties of phillipsite from the Pacific and Indian Oceans. *Amer. Mineral.*, **55**, 2053–62.
- Smith, J.V. (1988) Topochemistry of zeolites and related materials. 1. Topology and geometry. *Chem. Rev.*, **88**, 149–82.
- Smith, J.V., Knowles, C.R. and Rinaldi, R. (1964) Crystal structures with a chabazite framework. III Hydrated Ca-chabazite at +20 and -150°C. *Acta Crystallogr.*, **17**, 374–84.
- Smith, J. V., Pluth, J. J., Boggs, R. C. and Howard, D. G. (1991) Tschernichite, the mineral analogue of zeolite Beta. *J. Chem. Soc., Chem. Communications*, 363–4.
- Ståhl, K., Kvik, Å. and Smith, J.V. (1990) Thomsonite, a neutron diffraction study at 13 K. *Acta Crystallogr.*, **C46**, 1370–3.
- Steiner, A. (1955) Wairakite, the calcium analogue of analcime, a new zeolite mineral. *Mineral. Mag.*, **30**, 691–8.

- Strunz, H. (1956) Die Zeolithe Gmelinit, Chabasit, Levyn (Phakolith, Herschelit, Seebachit, Offretit). *Neues Jahrb. Mineral. Mh.*, 250–9.
- Strunz, H. (1978) *Mineralogische Tabellen*, 7th edition. Akademische Verlagges., Leipzig.
- Stuckenschmidt, E., Fuess, H. and Kvik, Å. (1990) Investigation of the structure of harmotome by X-ray (293 K, 100 K) and neutron diffraction (15 K). *Eur. J. Mineral.*, **2**, 861–74.
- Takéuchi, Y., Mazzi, F., Haga, N. and Galli, E. (1979) The crystal structure of wairakite. *Amer. Mineral.*, **64**, 993–1001.
- Taylor, W.H. (1930) The structure of analcite (NaAlSi₂O₆·H₂O). *Zeits. Kristallogr.*, **74**, 1–19.
- Taylor, W.H. and Jackson, R. (1933) The structure of edingtonite. *Zeits. Kristallogr.*, **86**, 53–64.
- Tazzoli, V., Domeneghetti, M.C., Mazzi, F. and Cannillo, E. (1995) The crystal structure of chiavennite. *Eur. J. Mineral.*, **7**, 1339–44.
- Teertstra, D.K. and Černý, P. (1995) First natural occurrences of end-member pollucite: A product of low-temperature reequilibration. *Eur. J. Mineral.*, **7**, 1137–48.
- Teertstra, D.K. and Dyer, A. (1994) The informal discreditation of "doranite" as the magnesium analogue of analcime. *Zeolites*, **14**, 411–3.
- Teertstra, D. K., Sherriff, B. L., Xu, Z. and Černý, P. (1994) MAS and DOR NMR study of Al–Si order in the analcime–pollucite series. *Canad. Mineral.*, **32**, 69–80.
- Thugutt, S.J. (1933) O ptylocie z Mydzka na Wolyniu – Sur la ptilolite de Mydzk en Volhynie. *Arch. Mineral. Soc. Sci. Varsovie*, **9**, 99–102 (Polish), 103–4 (French résumé). (*Mineral. Abstr.*, **6**, 129).
- Tillmanns, E., Fischer, R.X. and Baur, W.H. (1984) Chabazite-type framework in the new zeolite willhendersonite, KCaAl₃Si₃O₁₂·5H₂O. *Neues Jahrb. Mineral. Mh.*, 547–58.
- Tschernich, R.D. and Wise, W.S. (1982) Paulingite: variations in composition. *Amer. Mineral.*, **67**, 799–803.
- Ueno, T. and Hanada, K. (1982) Chemical compositions and geneses of zeolites from Tsuyazaki, Fukuoka Prefecture, Japan. *J. Mineral. Soc. Japan*, **15**, 259–72. (In Japanese with English abstract).
- Vaughan, P.A. (1966) The crystal structure of the zeolite ferrierite. *Acta Crystallogr.*, **21**, 983–90.
- Vezzalini, G. (1984) A refinement of Elba dachiardite: opposite acentric domains simulating a centric structure. *Zeits. Kristallogr.*, **166**, 63–71.
- Vezzalini G. and Oberti, R. (1984) The crystal chemistry of gismondines: the non-existence of K-rich gismondines. *Bull. Minéral.*, **107**, 805–12.
- Vezzalini, G., Quartieri, S. and Passaglia, E. (1990) Crystal structure of a K-rich natural gmelinite and comparison with the other refined gmelinite samples. *Neues Jahrb. Mineral. Mh.*, 504–16.
- Vezzalini, G., Artioli, G. and Quartieri, S. (1992) The crystal chemistry of cowlesite. *Mineral. Mag.*, **56**, 575–9.
- Vezzalini, G., Quartieri, S. and Galli, E. (1996) Relazioni strutturali nelle zeoliti con topologia CHA alla luce del ritrovamento di una Ca-willhendersonite. *Programma XXVI Congresso Nazionale della Associazione Italiana di Cristallografia. Alessandria*, p. 91.
- Vezzalini, G., Quartieri, S. and Galli, E. (1997a) Occurrence and crystal structure of a Ca-pure willhendersonite. *Zeolites*, **19**, 75–9.
- Vezzalini, G., Quartieri, S., Galli, E., Alberti, A., Cruciani, G. and Kvik, A. (1997b) Crystal structure of the zeolite mutinaite, the natural analogue of ZSM-5. *Zeolites*, **19**, 323–5.
- Villarroel, H.S. (1983) Sobre la existencia de otras variedades de estellerita y una forma de reconocerlas. *Anais Academia Brasileira de Ciencias*, **55**, 87–91.
- Walker, G.P.L. (1962) Garronite, a new zeolite, from Ireland and Iceland. *Mineral. Mag.*, **33**, 173–86.
- Walter, F. (1992) Weinebeneite, CaBe₃(PO₄)₂(OH)₂·4H₂O, a new mineral species: mineral data and crystal structure. *Eur. J. Mineral.*, **4**, 1275–83.
- Wenk, H.-R. (1973) The structure of wenkite. *Zeits. Kristallogr.*, **137**, 113–26.
- White, J.S. and Erd, R.C. (1992) Kehoeite is not a valid species. *Mineral. Mag.*, **56**, 256–8.
- Wise, W.S. (1982) New occurrence of faujasite in southeastern California. *Amer. Mineral.*, **67**, 794–8.
- Wise W.S. and Tschernich R.W. (1975) Cowlesite, a new Ca-zeolite. *Amer. Mineral.*, **60**, 951–6.
- Wise, W.S. and Tschernich, R.W. (1976) Chemical composition of ferrierite. *Amer. Mineral.*, **61**, 60–6.
- Wyart, J. (1938) Étude sur la leucite. *Bull. Soc. fr. Minéral.*, **61**, 228–38.
- Yang, P. and Armbruster, T. (1996) (010) disorder, partial Si,Al ordering, and Ca distribution in triclinic (C1) epistilbite. *Eur. J. Mineral.*, **8**, 263–71.

Appendix I. Notes on the definition of a zeolite

Is more than 50% substitution of elements other than Si and Al permissible in tetrahedral sites?

There was complete agreement in the Subcommittee that some substitution of elements such as P and Be for Si and Al in tetrahedral sites must be permitted in the definition. Discussion in this context focussed on whether a 50% rule should be applied. The so-called 50% rule (Nickel, 1992) is normally applied to split a binary solid-solution series into two species at the half-way point according to the predominant cations concerned, but not to separate members of a solid-solution series into two separate classes of minerals, as could happen if applied in the present context. Proponents of a 50% rule argued that the definition of zeolites should be on grounds of both structure and composition, zeolites being aluminosilicates or possibly Al-free silicates. The contrary opinion is that where structures are topologically equivalent and other essentially identical zeolitic characteristics prevail, irrespective of Si and Al contents in tetrahedral sites, any restrictions based on specific Si and Al contents would be arbitrary and undesirable. The Subcommittee voted by a substantial majority for this view. The beryllsilicates lovdarite and chiavennite, like the zincosilicate gaultite, have more than 50% tetrahedral sites occupied by Si, and are here accepted as zeolites in spite of having little if any Al. Also included are the beryllphosphates pahasapaite and weinebeneite which have neither Si nor Al, but have typically zeolitic structures and other zeolitic characteristics. They can be regarded as end-member examples of Si-free zeolites or zeolite phosphates.

A compositional factor is included in the adopted definition in that the framework consists essentially of oxygen atoms together with cations that enter into tetrahedral co-ordination with oxygen.

Is the presence of H₂O and of extra-framework cations essential?

Reversible dehydration is a characteristic feature of zeolitic behaviour, but how much H₂O must be present for a mineral to be considered a zeolite? Pollucite forms a continuous series with analcime, the H₂O content declining progressively with increasing Cs content such that the Na-free, Cs member is essentially anhydrous. It seems unnecessary, impractical, and illogical to prescribe some arbitrary H₂O content below which pollucite (or other mineral) would be defined as anhydrous, and no longer a zeolite. Furthermore, it is not inconceivable that some typical zeolite might be reversibly dehydrated under natural conditions without essential loss of structure. If so, it has not ceased to be a zeolite. Although zeolites typically are hydrous, it is inexpedient to specify the presence of H₂O in the definition.

Natural zeolites are known with up to 88% of tetrahedral sites occupied by Si, as in mutinaite, and there is no theoretical reason why this figure cannot be exceeded. If the site occupancy of tetrahedra by Si approaches 100%, the extra-framework cation content will approach zero, even though the structure and other characteristics may remain typically zeolitic. It is again considered inexpedient to word the definition so as to exclude such a hypothetical end-member case from the zeolite category. Melanophlogite, a low-density SiO₂ phase with large cages in its framework, would be a possible example, but is otherwise excluded by the adopted definition because it lacks appropriate channels for the passage of guest species.

Reference

- Nickel, E. H. (1992) Solid solutions in mineral nomenclature. *Mineral. Mag.*, 56, 127–30.

Appendix 2. Discreditations

Herschelite is chabazite-Na

Herschelite, $\text{Na}[\text{AlSi}_2\text{O}_6]\cdot 3\text{H}_2\text{O}$, was named by Lévy (1825) from material brought to him by Herschel from "Aci Reale" (now Acireale) on the flanks of Mt. Etna in Sicily. Contemporary literature and present-day exposures suggest that the actual occurrence may have been in basaltic lavas at Aci Castello, nearby. Lévy described herschelite as tabular crystals of hexagonal outline that contain 'silic, alumina, and potash'. It was later identified with chabazite (e.g. Hausmann, 1847) and relegated to synonymy, although shown to be Na-rich, not K-rich. Strunz (1956) confirmed that herschelite and chabazite give essentially identical X-ray powder patterns. Mason (1962) proposed revalidation on the bases of a supposed compositional gap between herschelite and 'normal' Ca-rich chabazite, the distinctive habit, and lower refractive indices.

Passaglia (1970) demonstrated a continuum of compositions from Ca- to Na-dominant types, extending into the field of K-dominance in a ternary series; there is no discernible gap in composition. The lower refractive indices reflect the Na-rich composition. Variant crystal habit is not an accepted basis for species status for minerals, and some examples of strongly Na-dominant chabazite have rhombohedral, not tabular habit, as in the case of micrometre-scale crystals aggregated into thin ragged plates illustrated by Sheppard *et al.* (1978).

In view of its chequered history and the above considerations, the name *herschelite* is suppressed and the name *chabazite-Na* is to be applied to those members of the chabazite series in which Na is the most abundant extra-framework cation. Herschelite may retain some use as a term for a distinctive habit.

Leonhardite is H₂O-poor laumontite

Leonhardite $\text{Ca}_4[\text{Al}_8\text{Si}_{16}\text{O}_{48}]\sim 14\text{H}_2\text{O}$ was described by Blum (1843) for a mineral closely related to laumontite $\text{Ca}_4[\text{Al}_8\text{Si}_{16}\text{O}_{48}]\cdot 18\text{H}_2\text{O}$, but with different morphology. The type locality was near Schemnitz, nowadays Banska Stiavnica, then in Hungary, now in Slovakia. Delffs (1843)

showed that type locality leonhardite has less H_2O (c. 13 molecules of H_2O *pfu*) than laumontite. Doelter (1921) agreed that leonhardite is identical in composition to laumontite apart from its lower content of H_2O . The name has continued to be used widely for a material that forms rapidly and reversibly by partial dehydration of laumontite under ambient conditions. This happens upon exposure in the field and in the laboratory as a function of H_2O vapour pressure or by soaking in water, giving a readily observable change in extinction angle and cell dimensions (e.g. Coombs, 1952; Armbruster and Kohler, 1992).

Fersman (1908) introduced the term 'primary leonhardite' for a variety from Kurtsy (nowadays Ukrainka), Crimea, with 14 molecules of H_2O , which neither dehydrates nor rehydrates under ambient conditions. In it, $(\text{Na},\text{K})_2$ substitutes for Ca, although Ca is still dominant (Pipping, 1966).

Type leonhardite of Blum from Schemnitz catalogued in the Museum of Natural History, Vienna, in 1843 and type 'primary leonhardite' of Fersman obtained from the Fersman Mineralogical Museum in Moscow are shown by Wuest and Armbruster (1997) and Stolz and Armbruster (1997), respectively, to have the same Si,Al ordered framework of tetrahedra as laumontite. The low H_2O content of 'primary leonhardite' is attributed to space limitations resulting from the introduction of additional cations of larger size.

In conformity with Rule 4, leonhardite is discredited as the name of a separate species. It is an H_2O -poor variety of laumontite. 'Primary leonhardite' is H_2O -poor sodian potassian laumontite.

Svetlozarite is dachiardite-Ca

Svetlozarite was described by Maleev (1976) as a high-silica zeolite occurring as spherulites in chalcedony veinlets in brecciated andesites west of Zvesdel, eastern Rhodopes, Bulgaria. Analysis showed $\text{Ca} > \text{Na} > \text{K}$, and minor Fe and Mg. From X-ray powder diffraction studies, Maleev suggested an orthorhombic symmetry, with a *c*-axis repeat of 7.5 Å, which is characteristic of the

mordenite group, to which he attributed the mineral.

Gellens *et al.* (1982) concluded from powder and single-crystal X-ray and transmission electron microscopy (TEM) studies, that svetlozarite, space group *Ccma* (?), is related to the ideal dachiardite structure by irregular periodic twinning and stacking faults, and that it is not a topologically distinct member of the mordenite family. Its composition is within the range of other samples of dachiardite. It is regarded as a multiply twinned and highly faulted dachiardite (dachiardite-Ca), and is discredited as a separate species.

Wellsite is barian phillipsite-Ca and calcian harmotome

The mineral named *wellsite* by Pratt and Foote (1897) has been shown by Galli (1972) and Galli and Loschi Ghittoni (1972) to be isostructural with phillipsite and harmotome, and Černý *et al.* (1977) have shown that zoning in crystals of wellsite covers most of the range from Ca-rich phillipsite to potassian calcian harmotome. Wellsite is discredited. Most examples of wellsite are barian phillipsite-Ca, and others are calcian harmotome.

References

Armbruster, T. and Kohler, T. (1992) Re- and dehydration of laumontite: a single-crystal X-ray study at 100 K. *Neues Jahrb. Mineral. Mh.*, 385–97.
 Blum, J.R. (1843) Leonhardit, ein neues Mineral. (*Poggendorff's Annalen der Physik und Chemie* (Leipzig), **59**, 336–9.
 Černý, P., Rinaldi, R. and Surdam, R.C. (1977) Wellsite and its status in the phillipsite-harmotome group. *Neues Jahrb. Mineral. Abh.*, **128**, 312–20.
 Coombs, D.S. (1952) Cell size, optical properties and chemical composition of laumontite and leonhardite. *Amer. Mineral.*, **37**, 812–30.
 Delffs, W. (1843) Analyse des Leonhardits. (*Poggendorff's Annalen der Physik und Chemie* (Leipzig), **59**, 339–42.
 Doelter, C. (1921) *Handbuch der Mineralchemie*, **II**, **3**.

Verlag Theodor Steinkopff; Dresden, Leipzig; 472 pp.
 Fersman, A.E. (1908) Materialien zur Untersuchung der Zeolithe Russlands. I. Leonhardit und Laumontit aus der Umgebung von Simferopol (Krim). *Trav. du Musée géol. Pierre le Grand pr. l'Acad. Imp. de Science St Pétersbourg*, **2**: 103–50. (Abstract in *Zeits. Kristallogr.*, **50**, 75–6.)
 Galli, E. (1972) La phillipsite barifera ("wellsite") di M. Calvarina (Verona). *Per. Mineral.*, **41**, 23–33.
 Gellens, R.L., Price, G.D. and Smith, J.V. (1982) The structural relation between svetlozarite and dachiardite. *Mineral. Mag.*, **45**, 157–61.
 Hausmann, J.F.L. (1847) *Handbuch der Mineralogie*, 2nd ed., **2**, 1600.
 Lévy, A. (1825) Descriptions of two new minerals. *Annals of Philosophy*, new ser., **10**, 361–3.
 Maleev, M.N. (1976) Svetlozarite, a new high-silica zeolite. *Zap. Vses. Mineral. Obshch.*, **105**, 449–53 (in Russian).
 Mason, B. (1962) Herschelite – a valid species? *Amer. Mineral.*, **47**, 985–7.
 Passaglia, E. (1970) The crystal chemistry of chabazites. *Amer. Mineral.*, **55**, 1278–301.
 Pipping, F. (1966) The dehydration and chemical composition of laumontite. *Min. Soc. India, IMA Volume*, 159–66.
 Pratt, J.H. and Foote, H.W. (1897) On wellsite, a new mineral. *Amer. J. Sci.*, Ser. 4, **3** (153), 443–8.
 Sheppard, R.A., Gude, A.J. and Edson, G.M. (1978) Bowie zeolite deposit, Cochise and Graham Counties, Arizona. In *Natural Zeolites* (L.B. Sand and F.A. Mumpton, eds.), Pergamon, Oxford, pp. 319–28.
 Stolz, J., and Armbruster, T. (1997) X-ray single-crystal structure refinement of a Na,K-rich laumontite, originally designated 'primary leonhardite'. *Neues Jahrb. Mineral. Mh.*, 131–4.
 Strunz, H. (1956) Die Zeolithe Gmelinit, Chabasit, Levyn (Phakolith, Herschelit, Seebachit, Offretit). *Neues Jahrb. Mineral. Mh.*, 250–9.
 Wuest, T. and Armbruster, T. (1997) Type locality leonhardite: a single-crystal X-ray study at 100K. *Program and Abstracts, Zeolite '97, 5th Int. Conference on the Occurrence, Properties, and Utilization of Natural Zeolites, Ischia, Italy*, p. 327–8.
 [Manuscript received 21 November 1997: revised 4 February 1998]