

Crystal Data: Monoclinic or triclinic. *Point Group:* $2/m$ or $\bar{1}$. Crystals tabular || {100} or {001}, or short to long prismatic, to 20 cm. Commonly cleavable, parallel fibrous, or compact, massive. *Twinning:* Common; twin axis [010], composition plane {100}.

Physical Properties: *Cleavage:* {100} perfect; {001} and $\{\bar{1}02\}$, good; $(100) \wedge (001) = 84.5^\circ$. *Fracture:* Uneven. *Tenacity:* Brittle. *Hardness* = 4.5–5. $D(\text{meas.}) = 2.86\text{--}3.09$ $D(\text{calc.}) = 2.90$ May exhibit yellow catholuminescence.

Optical Properties: Transparent to translucent. *Color:* White, colorless, brown, red, yellow, pale green; colorless in thin section. *Streak:* White. *Luster:* Vitreous, pearly on cleavage. *Optical Class:* Biaxial (-). *Orientation:* $X \wedge c = 30^\circ\text{--}44^\circ$; $Y \wedge b = 0^\circ\text{--}5^\circ$; $Z \wedge a = 37^\circ\text{--}50^\circ$. *Dispersion:* $r > v$, weak. $\alpha = 1.616\text{--}1.640$ $\beta = 1.628\text{--}1.650$ $\gamma = 1.631\text{--}1.653$ $2V(\text{meas.}) = 36^\circ\text{--}60^\circ$

Cell Data: *Space Group:* $P2_1/a$. $a = 15.409(3)$ $b = 7.322(1)$ $c = 7.063(1)$ $\beta = 95.30(2)^\circ$ $Z = 12$, or *Space Group:* $P\bar{1}$. $a = 7.94$ $b = 7.32$ $c = 7.07$ $\alpha = 90^\circ 2'$ $\beta = 95^\circ 22'$ $\gamma = 103^\circ 26'$ $Z = 6$

X-ray Powder Pattern: Sampo mine, Okayama Prefecture, Japan (1A). 3.314 (100), 3.83 (84), 3.51 (77), 3.086 (58), 2.302 (52), 2.556 (44), 1.759 (35)

Chemistry:	(1)	(2)	(1)	(2)
SiO ₂	50.82	50.24	CaO	48.16
Al ₂ O ₃		0.46	Na ₂ O	0.12
Fe ₂ O ₃		trace	K ₂ O	0.07
FeO	0.18	5.54	H ₂ O ⁺	0.08
MnO	0.03	8.16	S	0.14
MgO	0.22	0.07	Total	99.68
				100.54

(1) Remonmaki, Finland; corresponds to $(\text{Ca}_{1.01}\text{Mg}_{0.01})_{\Sigma=1.02}\text{Si}_{0.99}\text{O}_3$. (2) North mine, Broken Hill, New South Wales, Australia; corresponds to $(\text{Ca}_{0.76}\text{Mn}_{0.14}\text{Fe}_{0.09})_{\Sigma=0.99}(\text{Si}_{1.00}\text{Al}_{0.01})_{\Sigma=1.01}\text{O}_3$.

Polymorphism & Series: 1A, 2M, 3A, 4A, 5A, 7A polytypes.

Occurrence: Common in thermally metamorphosed siliceous carbonates, the intruding igneous rock, and skarn deposits along their contact; also in some alkalic igneous rocks and carbonatites.

Association: Calcite, grossular, diopside, vesuvianite, åkermanite, merwinite, larnite, spurrite.

Distribution: A widely distributed mineral; some prominent localities are: in Romania, at Dognecea (Dognăczka) and Csiklova, Banat. In Italy, at Sarrabus, Sardinia, and from Monte Somma and Vesuvius, Campania. In Ireland, at Dunmorehead, Mourne Mountains, and Scawt Hill, near Larne, Co. Antrim. From Kongsberg, Norway. At Göckum, Sweden. In Germany, at Harzburg, Harz Mountains, and Auerbach, Odenwald, Hesse. In the USA, at Natural Bridge and Diana, Lewis Co., New York; from Crestmore, Riverside Co., and Darwin, Inyo Co., California; in a large deposit two miles southeast of Gilbert, Esmeralda Co., Nevada. In Canada, at Oka and Asbestos, Quebec; at Outlet Post, Leeds Co., Ontario. From Pichucalo, Chiapas, and in the Pilares deposit, 55 km north of Hermosillo, Sonora, Mexico. At Hiiagiya, Ibaragi Prefecture; Ishiyamadera, Shiga Prefecture; and Kushiro, Hiroshima Prefecture, Japan. Large crystals from Belafa, Madagascar.

Name: For William Hyde Wollaston (1766–1828), English chemist and mineralogist.

References: (1) Dana, E.S. (1892) Dana's system of mineralogy, (6th edition), 371–373.

(2) Deer, W.A., R.A. Howie, and J. Zussman (1978) Rock-forming minerals, (2nd edition),

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise without the prior written permission of Mineral Data Publishing.

v. 2A, single-chain silicates, 547–563. (3) Buerger, M.J. and C.T. Prewitt (1961) The crystal structures of wollastonite and pectolite. *Proc. Natl. Acad. Sci.*, 47, 1884–1888. (4) Matsueda, H. (1973) Iron-wollastonite from the Sampo mine showing properties distinct from those of wollastonite. *Mineral. J. (Japan)*, 7, 180–201. (5) Henmi, C., A. Kawahara, K. Henmi, I. Kusachi, and Y. Takéuchi (1983) The 3T, 4T and 5T polytypes of wollastonite from Kushiro, Hiroshima Prefecture, Japan. *Amer. Mineral.*, 68, 156–163. (6) Hesse, K.-F. (1984) Refinement of the crystal structure of wollastonite-2M (parawollastonite). *Zeits. Krist.*, 168, 93–98.