

## Chrysoberyl, BeAl<sub>2</sub>O<sub>4</sub>

Chrysoberyl

Weber S U, Grodzicki M, Lottermoser W, Redhammer G J, Tippelt G, Ponahlo J, Amthauer G

Physics and Chemistry of Minerals 34 (2007) 507-515

<sup>57</sup>Fe Mossbauer spectroscopy, X-ray single-crystal diffractometry, and electronic structure calculations on natural alexandrite

9.4082 5.4790 4.4288 90 90 90 Pnma

atom	x	y	z	Wyckoff
Al1	0	0	0	4a
Al2	0.27282	0.25	-0.00503	4c
Be	0.09289	0.25	0.43360	4c
O1	0.09022	0.25	0.78822	4c
O2	0.43316	0.25	0.24167	4c
O3	0.16324	0.01554	0.25728	8d

$$(1 \times 8d) + (4 \times 4c) + (1 \times 4a)$$

### Raman Active Modes

WP	A <sub>g</sub>	A <sub>u</sub>	B <sub>1g</sub>	B <sub>1u</sub>	B <sub>2g</sub>	B <sub>2u</sub>	B <sub>3g</sub>	B <sub>3u</sub>
8d	3	-	3	-	3	-	3	-
4c	2	-	1	-	2	-	1	-
4a	-	-	-	-	-	-	-	-

Total number of modes:

$$11A_g + 7B_{1g} + 11B_{2g} + 7B_{3g} = 36$$