Vorläufige Mitteilungen — Preliminary notices

Unit cell and space group of gaylussite, $CaCO_3 \cdot Na_2CO_3 \cdot 5H_2O$

By E. A. MONROE

Department of Ceramic Science, State University of New York Alfred, New York*

(Received March 17, 1967)

The space group and unit cell of gaylussite have been determined from crystals from Searles Lake, California. Zero, first, and second levels of the a^*b^* and the a^*c^* nets were photographed with the Buerger precession camera. These patterns, along with morphological crystal-class information, have lead to an unequivocal determination of the space group. The aspect of the space group reported here is in keeping with the selection of the morphological axes as reported by Palache et al.¹. A very small crystal, $0.26 \times 0.16 \times 0.16$ mm, was chosen for the determination of the unit-cell constants so as to maximize accuracy. Calibration of the camera with an equally small quartz crystal indicates that the errors of the cell dimensions do not exceed $0.3^0/_0$, and the angle β is accurate to 5 minutes of arc. The new data are: Space group, I2/a; unit-cell dimensions:

$$\begin{split} a &= 11.59 \text{ Å}, & b &= 7.77 \text{ Å}, & c &= 11.19 \text{ Å}, & \beta &= 101°55'; \\ a:b:c &= 1.4916:1:1.4401; \text{ density} &= 1.995 \text{ (calculated)}; \\ Z &= 4 \text{ CaCO}_3 \cdot \text{Na}_2\text{CO}_3 \cdot 5\text{H}_2\text{O}. \end{split}$$

Morphological measurements¹: $\beta = 101^{\circ}33'$; a:b:c = 1.4897:1:1.4441; density = 1.991

L. D. Oshiganova² reports: (a, not given), b = 7.2 Å, c = 10.6 Å, $\beta = 103^{\circ}15'$; a:b:c = 1.4340:1:1.479.

Further x-ray structure work is planned.

^{*} Alfred University, Alfred, N.Y. 14802.

 $^{^{1}}$ Charles Palache *et al.*, The system of mineralogy. John Wiley and Sons, New York, 1951, p. 234.

² L. D. OSHIGANOVA, [Gaylussite crystals from the Kulunda Steppe.] Zapiski Vsesojuzn. mineral. Obsč. (Ber. UdSSR.-min. Ges.) 82 (1953) 220—224 [Russian; Abstract in Zentralblatt für Mineralogie 1954, 133—134].