

NOTES AND NEWS

EFFECTS OF GAMMA IRRADIATION ON PHYSICAL PROPERTIES OF MINERALS

MANUEL N. BASS,* *Princeton University, Princeton, New Jersey.*

In connection with studies of radiation damage in zircons it became of interest to know the effects of various types of radiation on crystals. The present study sought to determine the effects of intense gamma irradiation on a number of minerals.

Homogeneous-appearing mineral samples were selected and examined under the binocular and petrographic microscope in the search for pure specimens. Inclusions and bubbles could not be entirely avoided, especially in quartz, fluorite and halite. Of the materials finally selected, a portion was powdered or otherwise prepared for measurement of physical properties. Parts of both bulk samples and powders were packed with glass wool in glass vials, corked and sent to Brookhaven National Laboratory. There they received 1.5×10^8 Roentgens of Co^{60} gamma irradiation. Density of irradiated and non-irradiated portions of all minerals tested and refractive index of most of them were measured. In addition, the $2V$'s of the micas and the d_{001} dimension of lepidolite were measured.

Densities were measured by a flotation method. After flotation of an 80- 120-mesh powder of a mineral in a $\text{CCl}_4\text{-C}_2\text{H}_2\text{Br}_4$ mixture or Clerici solution, the density of the liquid was measured with a Christian Becker liquid-density balance which gives direct density measurements to 0.0001 gm./cc.

Refractive indices were measured in immersion liquids using a temperature-variation and a half-shadow method. Illumination was supplied by a sodium vapor lamp. The $2V$'s of the micas were measured on a universal stage, and the d_{001} dimension of lepidolite was measured with a North American Philips high-angle spectrometer using $\text{Fe K}\alpha$ radiation.

Experimental conditions were kept as constant as possible throughout all measurements in order to minimize systematic differences between measurements on irradiated and non-irradiated materials.

Except for difference in color, no significant differences were detected between irradiated and non-irradiated samples (see Tables 1-4).

Precision measurements by Frondel and Hurlbut (1955, p. 1216) showed that decolorization of smoky quartz by heating at 350° was attended by an increase in the indices of refraction. They (1955, p. 1217)

* Present address: Dept. of Geology, Northwestern University, Evanston, Illinois.

stated that density changes attendant on decolorization of smoky quartz were unknown, but that Frondel had found earlier that the elastic constants of a particular sample had changed appreciably upon decolorization. The color of all glass specimens and all except one quartz specimen (amethyst) in the present study changed to brown or smoky (smoky quartz became smokier) as a result of gamma irradiation. These results suggest that changes in the physical properties of the samples used in the present study may have been induced by the irradiation, but that these changes were too small to detect with the techniques used.

For each type of fluorite the apparent change of density was within the assigned experimental uncertainty, but in each case the density decreased slightly between 0.001 and 0.003 gm./cc.

Muscovite showed an apparent increase in density and the overlap of the ranges of error of the two measurements was very small. The results on biotite and lepidolite suggest that the result on muscovite was not significant.

Lepidolite showed a significant apparent increase in density (questioned value in Table 1). However, after remeasurement of densities of irradiated and non-irradiated lepidolite, the two values on non-irradiated material and the second on irradiated material lay within a range of

TABLE 1. DENSITY AND REFRACTIVE INDEX MEASUREMENTS

Mineral	Non-irradiated		Irradiated	
	Density	Refractive index (± 0.0003)	Density	Refractive index (± 0.0003)
Colorless fluorite	3.187 ± 0.005	1.4337	3.183 ± 0.0035	1.4337
Blue fluorite	3.185 ± 0.003	1.4336	3.184 ± 0.002	1.4337
Blue-green fluorite	3.186 ± 0.003	1.4339	3.183 ± 0.0035	1.4336
Pink fluorite	3.187 ± 0.0005	1.4336 1.4337	3.184 ± 0.002	1.4338
Halite	2.164 ± 0.004	1.5439	2.162 ± 0.001	1.5440
Colorless quartz	2.655 ± 0.0055	1.5440*	2.650 ± 0.0035	1.5442*
Amethyst	2.651 ± 0.0035	1.5441*	2.651 ± 0.002	1.5441*
Rose quartz	2.650 ± 0.002	1.5441*	2.650 ± 0.003	1.5442*
Epidote	3.467 ± 0.005		3.465 ± 0.004	
Allanite	3.618 ± 0.013		3.606 ± 0.007	
Muscovite	2.847 ± 0.005	ca. 1.596	2.854 ± 0.003	
Biotite	2.884 ± 0.0035	ca. 1.600	2.884 ± 0.002	
Lepidolite	2.846 ± 0.006	ca. 1.560	$2.860 \pm 0.001?$	ca. 1.5595
	2.844 ± 0.004		2.845 ± 0.004	

* Omega index.

TABLE 2. 2V MEASUREMENTS

Mineral	Non-irradiated	Irradiated
Muscovite	$43.1^\circ \pm 0.4^\circ$	$43.6^\circ \pm 0.4^\circ$
Biotite	ca. 5°	$8.8^\circ \pm 0.5^\circ$ $7.3^\circ \pm 0.6^\circ$
Lepidolite	$47.2^\circ \pm 0.1^\circ$ $44.9^\circ \pm 0.4^\circ$ $43.4^\circ \pm 0.1^\circ$ $32.2^\circ \pm 0.4^\circ$	$44.3^\circ \pm 0.2^\circ$ $44.4^\circ \pm 0.1^\circ$ $44.5^\circ \pm 0.2^\circ$

0.002 gm./cc. As a further check, 2V's of several specimens of irradiated and non-irradiated lepidolite were measured (Table 2). Those of irradiated specimens were consistently about 44° ; the non-irradiated lepidolite exhibited 2V's ranging generally from 43° to 47° , but one flake showed a quite different 2V of about 32° (in some portions the flake showed a 2V of more than 43°). The d_{001} spacing of three specimens each of irradiated and non-irradiated lepidolite was measured on the assumption that a change in density would likely be reflected in this lattice dimension. All values lay in the range 9.93 to 9.94 Å (see Table 3; note that, among non-irradiated specimens, that with a 2V of 32° showed the most anomalous value). It was concluded that no significant change occurred in the lepidolite.

Observed color changes in those minerals in which it was discernible are presented in Table 4. Only the micas and the initially deeply colored allanite and epidote failed to show a noticeable change.

CONCLUSION

1.5×10^8 Roentgens of Co^{60} gamma irradiation are insufficient to induce, within the limits of experimental error of the present study, significant changes in the density and refractive index of halite, fluorite,

TABLE 3. LEPIDOLITE, d_{001} (Å)

Non-irradiated	9.930
	9.939 (2V ca. 32°)
	9.934
Irradiated	9.936
	9.936
	9.941

TABLE 4. COLOR CHANGES UPON IRRADIATION

Mineral	Non-irradiated	Irradiated (bulk)	Irradiated (powder)
Colorless fluorite	colorless	"pure" blue, moderate intensity	very light blue
Blue fluorite	light purplish blue	bluish purple, moderate intensity	very lightly colored
Blue-green fluorite	light blue-green	deep blue-green	deep blue-green
Pink fluorite	very light pink	purple with patches of blue like that of irradiated colorless fluorite; moderate intensity	(powder lost)
Halite	colorless	deep brown	brownish gray
Colorless quartz*	colorless	brown (between irradiation smoky and irradiated rose in intensity)	smoky (between irradiated smoky and irradiated rose in intensity)
Amethyst	purple, somewhat variegated, light intensity	purple, variegated, moderate intensity	no visible change
Rose quartz*	light pink	brown (smoky), very intense	gray-brown (smoky), intense
Smoky quartz*	light gray-brown	no change	intensification of smoky color
Epidote	moderate to dark green	no change	no change
Allanite	dark brown or black	no change	no change
Muscovite	colorless	no change	—
Biotite	dark brown to black	no change	—
Lepidolite	pink	no change	—
Vial glass	colorless	deep brown	—
Glass slide	colorless	deep brown	—
Pyrex(?) tubing	colorless	moderate brown	—
Cover glass	colorless	light brown	—

* Relative intensities of brown color or smokiness in those quartzes showing it, from most to least intense: irradiated rose, irradiated colorless, irradiated smoky, non-irradiated smoky.

quartz, epidote, allanite, muscovite, biotite and lepidolite; in the 2V's of the three micas; and in the d_{001} spacing of lepidolite. Color changes are quite striking in many colorless and light-colored minerals and glasses.

ACKNOWLEDGMENTS

This study was supported by Office of Naval Research contract *Nonr-250 (00)*, *NR-081-149* with Princeton University. The problem was

suggested by Dr. H. D. Holland, and was carried out at Princeton University during 1951 and 1952. Dr. Holland and Dr. H. H. Hess showed a continued interest during the course of the work. The writer is indebted to them for many helpful suggestions and for critically reading the manuscript.

REFERENCE

- FRONDEL, C., AND HURLBUT, C. S., JR. (1955), Determination of the atomic weight of silicon by physical measurements on quartz: *Jour. Chem. Phys.*, **23**, 1215-1219.

URANOTHORITE NEAR FOREST HOME, SAN BERNARDINO COUNTY,
CALIFORNIA*

D. F. HEWETT AND JEROME STONE, *U. S. Geological Survey,*
Washington, D. C.

The intensive search for uranium in southern California during recent years is yielding discoveries of some uncommon uranium and thorium minerals, some of which occur under unusual or unique geologic environments. The presence of uranium minerals near Forest Home, San Bernardino County, was brought to the attention of D. F. Hewett early in 1955 by Pierre George, an amateur collector of minerals, of San Gabriel. After some preliminary tests of the materials collected by Mr. George, the area was visited by D. F. Hewett in April. Laboratory work by Jerome Stone and others of the U. S. Geological Survey has confirmed the presence of uranothorite and several other thorium-bearing minerals at several localities near Forest Home.

Forest Home P. O. is on the south side of Mill Creek, due south of San Bernardino Mountain, in the principal valley that drains the south slopes of San Bernardino Mountain (Fig. 1). Eastward from Forest Home, the successive tributaries of Mill Creek from the north are Lost Creek, Alger Creek, and Falls Creek. The uranothorite locality is an opencut on the east slope of Alger Creek valley about 300 feet above the creek and about 3,000 feet north of the point where Alger Creek joins Mill Creek. A rough road follows Alger Creek to an ore bin, and a chute extends up the slope to the opencut. The opencut is about 30 feet long and it is limited by a vertical wall about 15 feet high. During 1954, a few tons of material, probably less than 10 tons, were sorted and shipped for its content of uranium. The names of the owners or shippers are not known.

At another locality, higher on the ridge west of Alger Creek, several

* Publication authorized by the Director, U. S. Geological Survey.