

Phenakite, Be_2SiO_4

Phenakite

Downs J W, Gibbs G V

American Mineralogist 72 (1987) 769-777

An exploratory examination of the electron density and electrostatic potential of phenakite

12.472 12.472 8.251 90 90 120 R-3

atom	x	y	z	Wyckoff
Si	0.19562	0.98402	0.74990	18f
Be1	0.1943	0.9841	0.4156	18f
Be2	0.1941	0.9822	0.0846	18f
O1	0.20975	0.12125	0.7503	18f
O2	0.33382	0.00040	0.74991	18f
O3	0.12223	0.91217	0.91497	18f
O4	0.12228	0.91342	0.58495	18f

(7 × 18f)

Raman Active Modes

WP	A_g	A_u	E_g^1	E_u^1	E_g^2	E_u^2
18f	3	.	3	.	3	.

Total number of modes:

$$21A_g + 21E_g^1 + 21E_u^2 = 63$$