

Spectrum processing :

Peak possibly omitted : 13.490 keV

Processing option : Oxygen by stoichiometry (Normalised)

Number of iterations = 5

Standard :

C CaCO3 1-Jun-1999 12:00 AM


Al Al2O3 1-Jun-1999 12:00 AM

Si SiO2 1-Jun-1999 12:00 AM


S FeS2 1-Jun-1999 12:00 AM

Ca Wollastonite 1-Jun-1999 12:00 AM

Fe Fe 1-Jun-1999 12:00 AM



Element	Weight%	Atomic%	Compd%	Formula
C K	19.32	26.33	70.80	CO2
Al K	5.82	3.53	11.01	Al2O3
Si K	3.08	1.80	6.60	SiO2



Comment:



S K	0.05	0.03	0.14	SO3
Ca K	8.07	3.29	11.29	CaO
Fe K	0.14	0.04	0.18	FeO
O	63.51	64.98		
Totals	100.00			
