

Spectrum processing :

Peak possibly omitted : 4.655 keV

Processing option : Oxygen by stoichiometry (Normalised)

Number of iterations = 3

Standard :

Al Al₂O₃ 1-Jun-1999 12:00 AM

Si SiO₂ 1-Jun-1999 12:00 AM

S FeS₂ 1-Jun-1999 12:00 AM


K MAD-10 Feldspar 1-Jun-1999 12:00 AM

Ca Wollastonite 1-Jun-1999 12:00 AM


Cu Cu 1-Jun-1999 12:00 AM

Mo Mo 1-Jun-1999 12:00 AM

Pt Pt 1-Jun-1999 12:00 AM



Element	Weight%	Atomic%	Compd%	Formula
Al K	0.22	0.22	0.41	Al ₂ O ₃



Comment:

Si K	0.32	0.32	0.69	SiO2
S K	14.73	12.69	36.77	SO3
K K	0.09	0.07	0.11	K2O
Ca K	0.13	0.09	0.18	CaO
Cu K	0.20	0.09	0.25	CuO
Mo L	41.05	11.82	61.58	MoO3
Pt L	0.00	0.00	0.00	PtO2
O	43.26	74.71		
Totals	100.00			
