# FLUORAPOPHYLLITE-(Cs), CsCa<sub>4</sub>(Si<sub>8</sub>O<sub>20</sub>)F(H<sub>2</sub>O)<sub>8</sub>, A NEW APOPHYLLITE-GROUP MINERAL FROM THE DARAI-PIOZ MASSIF, TIEN-SHAN, NORTHERN TAJIKISTAN

ATALI A. AGAKHANOV, LEONID A. PAUTOV, ANATOLY V. KASATKIN, AND VLADIMIR YU. KARPENKO

Fersman Mineralogical Museum, Russian Academy of Sciences, Leninskii Prospekt, 18-2, 119071 Moscow, Russia

ELENA SOKOLOVA<sup>§</sup>, MAXWELL C. DAY, AND FRANK C. HAWTHORNE

Department of Geological Sciences, University of Manitoba, Winnipeg, Manitoba R3T 2N2 Canada

VYACHESLAV A. MUFTAKHOV

Institute of Mineralogy, Ural branch, Russian Academy of Sciences, Ilmen State Nature Reserve, 456317 Miass, Russia Faculty of Geology, National Research South Ural State University, Miass branch, 8 July Str., 10, 456304 Miass, Russia

IGOR V. PEKOV

Department of Mineralogy, Moscow State University, Vorobievy Gory, 119991 Moscow, Russia

FERNANDO CÁMARA

Dipartimento di Scienze della Terra "Ardito Desio", Università degli Studi di Milano, Via Mangiagalli 34, 20133, Milano, Italy

SERGEY N. BRITVIN

Department of Crystallography, St. Petersburg State University, University Emb. 7/9, 199034 St. Petersburg, Russia

### Abstract

Fluorapophyllite-(Cs) (IMA 2018-108a), ideally  $CsCa_4(Si_8O_{20})F(H_2O)_8$ , is an apophyllite-group mineral from the moraine of the Darai-Pioz glacier, Tien-Shan, Northern Tajikistan. Associated minerals are quartz, pectolite, baratovite, aegirine, leucosphenite, pyrochlore, neptunite, fluorapophyllite-(K), and reedmergnerite. Fluorapophyllite-(Cs) is a hydrothermal mineral. It is colorless and has a vitreous luster and a white streak. Cleavage is perfect; it is brittle and has a stepped fracture. Mohs hardness is 4.5–5.  $D_{\text{meas.}} = 2.54(2) \text{ g/cm}^3$ ,  $D_{\text{calc.}} = 2.513 \text{ g/cm}^3$ . Fluorapophyllite-(Cs) is unixial (+) with refractive indices  $(\lambda = 589 \text{ nm}) \omega = 1.540(2), \varepsilon = 1.544(2)$ . It is non-pleochroic. Chemical analysis by electron microprobe gave SiO<sub>2</sub> 48.78, Al<sub>2</sub>O<sub>3</sub> 0.05, CaO 22.69, Cs<sub>2</sub>O 10.71, K<sub>2</sub>O 1.13, Na<sub>2</sub>O 0.04, F 1.86, H<sub>2</sub>O<sub>calc</sub>, 14.61, -O=F<sub>2</sub> -0.78, sum 99.09 wt.%; H<sub>2</sub>O was calculated from crystal-structure analysis. The empirical formula based on 29 (O + F) apfu,  $H_2O = 8 pfu$ , is  $(Cs_{0.75}K_{0.24})_{\Sigma 0.99}(Ca_{3.99}Na_{0.01})_{\Sigma 4}(Si_{8.01}Al_{0.01})_{\Sigma 8.02}O_{20.03}F_{0.97}(H_2O)_8, Z = 2. The simplified formula is (Cs,K)(Ca,Na)_4(Si,Al)_8 (Cs,A)_4(Si,Al)_8 (Cs,A)_4 (Cs,$  $O_{20}F(H_2O)_8$ . Fluorapophyllite-(Cs) is tetragonal, space group P4/mnc, a 9.060(6), c 15.741(11) Å, V 1292.10(19) Å<sup>3</sup>. The crystal structure has been refined to  $R_1 = 4.31\%$  based on 498 unique ( $F_0 > 4\sigma F$ ) reflections. In the crystal structure of fluorapophyllite-(Cs), there is one <sup>[4]</sup>T site occupied solely by Si,  $\langle T-O \rangle = 1.615$  Å. SiO<sub>4</sub> tetrahedra link to form a (Si<sub>8</sub>O<sub>20</sub>)<sup>8–</sup> sheet perpendicular to [001]. Between the Si-O sheets, there are two cation sites: A and B. The A site is coordinated by eight H<sub>2</sub>O groups [O(4) site], A–O(4) = 3.152(4) Å; the A site contains  $Cs_{0.75}K_{0.24}\Box_{0.01}$ , ideally Cs apple. The Cs–O bond length of 3.152 Å is definitely larger than the K–O bond length of 2.966–2.971 Å in fluorapophyllite-(K),  $KCa_4(Si_8O_{20})F(H_2O)_8$ . The <sup>[7]</sup>B site contains Ca<sub>3.99</sub>Na<sub>0.01</sub>, ideally Ca<sub>4</sub> apfu;  $\langle B-\phi \rangle = 2.417$  Å ( $\phi = O$ , F, H<sub>2</sub>O). The Si–O sheets connect via A and B polyhedra and hydrogen bonding; two H atoms have been included in the refinement. Fluorapophyllite-(Cs) is isostructural with fluorapophyllite-(K). Fluorapophyllite-(Cs) is a Cs-analogue of fluorapophyllite-(K).

*Keywords*: fluorapophyllite-(Cs), new mineral, apophyllite group, Darai-Pioz, Tien-Shan, Northern Tajikistan, electron microprobe analysis, crystal structure.

<sup>&</sup>lt;sup>§</sup> Corresponding author e-mail address: elena\_sokolova@umanitoba.ca

Downloaded from https://pubs.geoscienceworld.org/canmin/article-pdf/doi/10.3749/canmin.1900038/4912649/cami-57-06-02.pdf?casa\_token=PdFwfYtV7UAAAAAA:m91G6c9h8xVR2 by University of Arizona user

#### INTRODUCTION

Fluorapophyllite-(Cs), ideally CsCa<sub>4</sub>(Si<sub>8</sub>O<sub>20</sub>)F  $(H_2O)_8$ , is a new mineral of the apophyllite group (Dunn & Wilson 1978, Hatert et al. 2013) from the moraine of the Darai-Pioz glacier, Tien-Shan, Northern Tajikistan. This locality is well-known for Csbearing minerals. Fluorapophyllite-(Cs) is named in accord with the current nomenclature of the apophyllite-group minerals (Hatert et al. 2013). The new mineral species and its name were approved by the Commission on New Minerals, Nomenclature and Classification, International Mineralogical Association (IMA 2018-108a). The holotype specimen of fluorapophyllite-(Cs) has been deposited in the collections of the Fersman Mineralogical Museum, Russian Academy of Sciences, Moscow, Russia, registration number 5280/1. Here we report the description and crystal structure of fluorapophyllite-(Cs), a new mineral.

# OCCURRENCE AND MINERAL ASSOCIATION

Fluorapophyllite-(Cs) was found in the moraine of the Darai-Pioz glacier ( $39^{\circ} 30'$  N and  $70^{\circ} 40'$  E), the Alai mountain range, Tien-Shan, Rashtskii district, north Tajikistan. The multiphase Darai-Pioz massif belongs to the Upper Paleozoic Alaisky (Matchaisky) intrusive complex. The area of outcrop of the massif is about 16 km<sup>2</sup>. Most of the massif rocks are covered by moraine or glaciers and/or are difficult to access. In the north, the massif intrudes Silurian limestones and slates; in the south, it intrudes terrigenous slates of Late Carboniferous age. The outer zone of the massif



FIG. 1. Backscattered electron image of fluorapophyllite-(Cs) (1) in quartz (2) - pectolite (3) aggregate.

TABLE 1. CHEMICAL COMPOSITION AND UNIT
FORMULA* FOR FLUORAPOPHYLLITE-(Cs)

Constituent	wt.%	Range		apfu
SiO <sub>2</sub>	48.78	48.25-49.08	Si	8.01
Al <sub>2</sub> O <sub>3</sub>	0.05	0.00-0.12	AI	0.01
CaO	22.69	22.32-22.83	Ca	3.99
Cs <sub>2</sub> O	10.71	9.67-11.81	Cs	0.75
K <sub>2</sub> O	1.13	0.72-1.46	K	0.24
Na <sub>2</sub> O	0.04	0.00-0.09	Na	0.01
H <sub>2</sub> O	14.61**			
F	1.86	1.65-2.18	F	0.97
F = O	-0.78		H <sub>2</sub> O	8.00
Total	99.09			

\* Formula unit calculated on 29 (O + F) pfu; \*\* calculated from crystal-structure analysis:  $H_2O = 8 pfu$ .

consists of subalkaline biotite granite, often tourmalinized (300-290 Ma), surrounding a discontinuous ring of biotite granites and granosyenites. The central part of the massif comprises quartz and aegirine syenites. In the northeast part of the massif, there is a stock of cancrinite and nepheline foyaite (247  $\pm$  6 Ma). There are veins of syenite pegmatites and aegirine-potassium feldspar-quartz rocks containing polylithionite (286  $\pm$ 7 Ma) and rare-metal and boron mineralization. Veins of calcite carbonatites and syenite carbonatites (Faiziev et al. 2010) are widespread. Much of the rock is fenitized to different degrees. Detailed descriptions of the petrography and mineralogy of the Darai-Pioz massif can be found in Moskvin (1937), Dusmatov (1968, 1971), Semenov & Dusmatov (1975), Belakovskiy (1991), and Reguir et al. (1999).

This locality is known for Cs-bearing minerals. Kupletskite-(Cs) was the first Cs-bearing mineral described from Darai-Pioz (Yefimov *et al.* 1971, Cámara *et al.* 2010). In the last five years, five Cs-bearing minerals have been described from Darai-Pioz: odigitriaite, CsNa<sub>5</sub>Ca<sub>5</sub>[Si<sub>14</sub>B<sub>2</sub>O<sub>38</sub>]F<sub>2</sub> (IMA 2015-028, Agakhanov *et al.* 2017a); mendeleevite-(Nd), (Cs, $\square$ )<sub>6</sub>( $\square$ ,Cs)<sub>6</sub>( $\square$ ,K)<sub>6</sub>(*REE*,Ca)<sub>30</sub>(Si<sub>70</sub>O<sub>175</sub>)(OH, H<sub>2</sub>O,F)<sub>35</sub> (IMA 2015-031, Agakhanov *et al.* 2017b); two Cs-micas: garmite, CsLiMg<sub>2</sub>(Si<sub>4</sub>O<sub>10</sub>)F<sub>2</sub> (IMA 2017-008, Pautov *et al.* 2017) and gorbunovite, CsLi<sub>2</sub>(Ti,Fe)(Si<sub>4</sub>O<sub>10</sub>)(F,OH,O)<sub>2</sub> (IMA 2017-040, Agakhanov *et al.* 2017c); and fluorapophyllite-(Cs), CsCa<sub>4</sub>(Si<sub>8</sub>O<sub>20</sub>)F(H<sub>2</sub>O)<sub>8</sub> (IMA 2018-108a, this work).

Fluorapophyllite-(Cs) is a hydrothermal mineral. It was found in a quartz-pectolite aggregate in quartzolite boulders. Associated minerals are quartz, pectolite, baratovite, aegirine, leucosphenite, pyrochlore, neptunite, fluorapophyllite-(K), and reedmergnerite.

# TABLE 2. X-RAY POWDER DIFFRACTION DATA\* FOR FLUORAPOPHYLLITE-(Cs)

\* Powder data were obtained by collapsing experimental single-crystal data into two dimensions. The most intense reflection (101) was covered by the beam stop. Therefore, intensity of (101) was calculated from the refined crystal structure and all intensities rescaled accordingly. Reflections with  $I_{\rm est} < 5$  are not listed.

#### APPEARANCE AND PHYSICAL PROPERTIES

In the quartz-pectolite aggregate, fluorapophyllite-(Cs) occurs as separate grains up to 0.08 mm across (Fig. 1) and as zones in grains of fluorapophyllite-(K) [grains of fluorapophyllite-(K) are up to 0.2 mm across]. Individual grains of fluorapophyllite-(Cs) are irregular in shape.

Fluorapophyllite-(Cs) is colorless and has a vitreous luster and a white streak. Cleavage is perfect; it is brittle and has a stepped fracture. The microhardness of fluorapophyllite-(Cs) is VHN<sub>100</sub> = 480 kg/mm<sup>2</sup> (with the range of 468–502), which corresponds to a Mohs hardness of 4.5–5.  $D_{\text{meas.}} = 2.54(2)$  g/cm<sup>3</sup> as determined by flotation in Clerici liquid;  $D_{\text{calc.}} = 2.513$ 

TABLE 3. MISCELLANEOUS REFINEMENT DATA FOR FLUORAPOPHYLLITE-(Cs)

a (Å)	9.060(6)
С	15.741(11)
<i>V</i> (Å <sup>3</sup> )	1292.10(19)
Space group	P4/mnc
Ζ	2
Reflections ( $l > 10\sigma l$ )	5962
Absorption coefficient (mm <sup>-1</sup> )	2.41
<i>F</i> (000)	973.9
D <sub>calc.</sub> (g/cm <sup>3</sup> )	2.513
Crystal size (mm)	0.045 imes 0.040 imes 0.030
Radiation/monochromator	Mo <i>K</i> a/graphite
20-range for data	60.00, 47.95*
collection (°)	
h*	$-10 \leq h \leq 10$
<i>k</i> *	$-10 \le k \le 10$
<i>l*</i>	–18 ≤ <i>l</i> ≤ 18
<i>R</i> (int)	0.0564*
Reflections collected	10527*
Independent reflections	539*
$F_{\rm o} > 4\sigma F$	498*
Refinement method	Full-matrix least squares
	on F <sup>2</sup> , fixed weights
	proportional to $1/\sigma F_0^2$
Final <i>R</i> (obs)	
$R_1(F_o > 4\sigma F)$	0.0431
$R_1$	0.0487
wR <sub>2</sub>	0.0851
Highest peak, deepest hole (e Å <sup>-3</sup> )	0.42, -0.52
Goodness of fit on $F^2$	1.276

\* Structure refinement (see text).

g/cm<sup>3</sup> (from the empirical formula). Fluorapophyllite-(Cs) is unixial (+) with refractive indices ( $\lambda = 589$  nm)  $\omega = 1.540(2)$ ,  $\varepsilon = 1.544(2)$ . It is non-pleochroic. The compatibility index (1 – Kp/Kc) = -0.002 (for  $D_{calc.}$ ) and 0.010 (for  $D_{meas.}$ ) and is rated as superior (Mandarino 1981).

#### CHEMICAL COMPOSITION

A grain of fluorapophyllite-(Cs) was analyzed with a JEOL 773 electron microprobe operating in wavelength-dispersive mode with an accelerating voltage of 20 kV, a specimen current of 20 nA, and a beam diameter of 3  $\mu$ m. The following standards were used: Si, Al, K: microcline USNM 143966; Na: omphacite USNM 110607; Ca: anorthite USNM 110607; Cs: Cs<sub>2</sub>Nb<sub>4</sub>O<sub>11</sub>; F: fluorophlogopite. The data were reduced and corrected by the PAP method of Pouchou & Pichoir (1985). Table 1 gives the chemical composition of fluorapophyllite-(Cs), (mean of 10 points). The empirical formula based on 29 (O + F)





FIG. 2. General view of the crystal structure of fluorapophyllite-(Cs). SiO<sub>4</sub> tetrahedra and Ca-dominant polyhedra are orange and pale blue; the Cs atom (*A* site) is shown as a large pink sphere; the F atom is shown as a small yellow sphere; the O atom of the H<sub>2</sub>O group at the O(4) site is shown as a medium red sphere; and H atoms are shown as small gray spheres. Bonds O(4)–H and H-acceptor are shown as black solid and dashed lines, respectively. Thin black lines show the unit cell.

*apfu* (H<sub>2</sub>O = 8 *pfu* was calculated from crystalstructure refinement) is  $(C_{s_{0.75}K_{0.24}})_{\Sigma_{0.99}}(Ca_{3.99}$  $Na_{0.01})_{\Sigma_4}(Si_{8.01}Al_{0.01})_{\Sigma_{8.02}}O_{20.03}F_{0.97}(H_2O)_8$ , Z = 2. The simplified formula is  $(C_{s,K})(Ca,Na)_4(Si,Al)_8$  $O_{20}F(H_2O)_8$ . The ideal formula is  $CsCa_4Si_8O_{20}$  $F(H_2O)_8$ , which requires  $SiO_2$  48.03, CaO 22.41,  $Cs_2O$  14.07, H<sub>2</sub>O 14.40, F 1.90,  $-O=F_2$  –0.80, total 100 wt.%.

TABLE 5. SELECTED INTERATOMIC DISTANCES (Å)
AND ANGLES (°) FOR FLUORAPOPHYLLITE-(Cs)

A–O(4)a ×8	3.152(4)	T–O(3)	1.587(3)
B–O(3) ×2	2.384(4)	T–O(1)	1.616(2)
B–O(3) <sub>C</sub> ×2	2.395(3)	T–O(2)b	1.626(3)
B–F	2.415(2)	T–O(2)	1.631(3)
B–O(4) ×2	2.473(4)	<t–o></t–o>	1.615
<b-< td=""><td>2.417</td><td></td><td></td></b-<>	2.417		
		T–O(1)–Tc	141.5(3)
		T–O(2)–Tc	140.1(2)
		<t-0-t></t-0-t>	140.8

\*  $\phi = 0$ , F, H<sub>2</sub>O. Symmetry operators: a:  $-x + \frac{1}{2}$ ,  $y - \frac{1}{2}$ ,  $-z + \frac{1}{2}$ ; b: *y*, -x, *z*; c: -y, *x*, *z*.

Site*	Refined site-scattering ( <i>epfu</i> )	Site population ( <i>apfu</i> )	Calculated site-scattering ( <i>epfu</i> )	<ct–φ><sub>obs.</sub> (Å)*</ct–φ>	Ideal composition ( <i>apfu</i> )
		Cat	ions		
<sup>[8]</sup> A	45.0(3)	Cs <sub>0.75</sub> K <sub>0.24</sub> □ <sub>0.01</sub>	45.81	3.152	Cs
<sup>[7]</sup> B	80.0	Ca <sub>3.99</sub> Na <sub>0.01</sub>	79.91	2.417	Ca₄
<sup>[4]</sup> <i>T</i>	112.0	Si <sub>8.00</sub>	112.00	1.615	Si <sub>8</sub>
		Anions and	H <sub>2</sub> O groups		
<sup>[2,2,4]</sup> O(1,2,3)		O <sub>20</sub>			O <sub>20</sub>
<sup>[4]</sup> F		F <sub>0.97</sub> □ <sub>0.03</sub>			F
O(4)		(H <sub>2</sub> O) <sub>8</sub>			(H <sub>2</sub> O) <sub>8</sub>

TABLE 6. REFINED SITE-SCATTERING VALUES AND ASSIGNED SITE-POPULATIONS FOR FLUORAPOPHYLLITE-(Cs)

\* Ct = cation,  $\phi = 0$ , F, H<sub>2</sub>O.

TABLE 7. HYDROGEN BONDING IN FLUORAPOPHYLLITE-(Cs)

D–H···A	D–H (Å)	H⊷A (Å)	D· · ·A (Å)	∠DHA (°)	∠HDH (°)
O(4)–H(1)· · · O(2)a	0.98(1)	2.23(1)	3.186(5)	167(4)	111(4)
O(4)–H(1)· · · O(3)b	0.98(1)	1.81(1)	2.769(5)	167(4)	

a:  $x - \frac{1}{2}$ ,  $-y + \frac{1}{2}$ ,  $z + \frac{1}{2}$ ; b: y, -x + 1, z.

#### DATA COLLECTION AND STRUCTURE REFINEMENT

Single-crystal X-ray data for fluorapophyllite-(Cs) were collected with a Bruker D8 QUEST ECO CMOS diffractometer equipped with a fine-focus tube (Mo $K\alpha$ ) and a PHOTON 50 detector. The crystal does not diffract very well and that is why we cut the data at  $2\Theta$ = 47.95° (collected up to  $2\Theta = 60.00^{\circ}$ ). X-ray powder diffraction data were obtained by collapsing the experimental single-crystal data into two dimensions (Table 2). Unit-cell parameters from the single-crystal data were determined by least-squares refinement of 5962 reflections with  $I > 10\sigma I$  and are given in Table 3, together with miscellaneous information on data collection and structure refinement. For fluorapophyllite-(Cs), the intensities of 10,527 reflections were measured using 60 s per 0.5° frame. An absorption correction was done using the SADABS program (Sheldrick 2015). All calculations were done with the Bruker SHELXTL-2014/3 (version 3) system of programs (Sheldrick 2015).

The crystal structure of fluorapophyllite-(Cs) was refined using the atom coordinates of fluorapophyllite-

Final atom coordinates and anisotropic displacement parameters are listed in Table 4, selected interatomic distances and Si–O–Si angles are given in Table 5, refined site-scattering and assigned sitepopulations for selected cation and anion sites are given in Table 6, details of hydrogen bonding are given in Table 7, and bond-valence values in Table 8. A Crystallography Information File (CIF) may be obtained from The Depository of Unpublished Data on the MAC website [documents Fluorapophyllite-(Cs) CM57, 19-00038]<sup>1</sup>.

<sup>(</sup>K) (Ståhl *et al.* 1987) as a starting model. The crystal structure of fluorapophyllite-(Cs) was refined to  $R_1 = 4.31\%$  based on 498 unique reflections with ( $F_o > 4\sigma F$ ). Scattering curves for neutral atoms were taken from the International Tables for Crystallography (Wilson 1992). Site-scattering values were refined for the *A* and *B* sites with the scattering curves of Cs and Ca, respectively. For the final refinement, the D(donor)–H(1,2) distances were softly constrained to 0.98 Å.

<sup>&</sup>lt;sup>1</sup> http://mineralogicalassociation.ca

TABLE 8. BOND-VALENCE VALUES\* FOR FLUORAPOPHYLLITE-(Cs)

Atom**	А	В	Т	H(1)	H(2)	Σ
O(1)			$1.02^{x2 \rightarrow}$			2.04
O(2)			0.99	0.09		2.06
			0.98			
O(3)		0.30 <sup>x2↓</sup>	1.10		0.19	1.88
		0.29 <sup>x2↓</sup>				
O(4)	0.14 <sup>x8↓</sup>	0.25 <sup>x2↓</sup>		0.91	0.81	2.11
F		0.23 <sup>x4→</sup>				0.92
Σ	1.10	1.91	4.09	1.00	1.00	

\* Bond-valence parameters (*vu*) are from Brown (1981), except Brown & Altermatt (1985) for H–O; \*\* A = Cs; B = Ca; T = Si; O(4) = O atom of an H<sub>2</sub>O group.

## STRUCTURE DESCRIPTION

In the crystal structure of fluorapophyllite-(Cs), there is one *T* site occupied solely by Si and tetrahedrally coordinated by O atoms,  $\langle T-O \rangle =$ 1.615 Å. SiO<sub>4</sub> tetrahedra link to form a  $(Si_8O_{20})^{8-}$ sheet perpendicular to [001]; in a sheet, SiO<sub>4</sub> tetrahedra form 4- and 8-membered rings (Fig. 2). Between the Si–O sheets, there are two cation sites: *A* and *B*. The Cs-dominant *A* site is coordinated by eight H<sub>2</sub>O groups [O(4) site], with A–O(4) = 3.152(4) Å (Table 5); the *A* site contains Cs<sub>0.75</sub>K<sub>0.24</sub> $\square_{0.01}$ , ideally Cs<sub>1</sub> *apfu* (Table 6). The Cs–O bond length of 3.152 Å is definitely larger than the K–O bond length of 2.966– 2.971 Å in fluorapophyllite-(K) (Table 9). The Cadominant <sup>[7]</sup>*B* site contains Ca<sub>3.99</sub>Na<sub>0.01</sub>, ideally Ca<sub>4</sub> *apfu*; the *B* site is coordinated by four O atoms, two H<sub>2</sub>O groups, and one F atom, with  $\langle B-\phi \rangle = 2.417$  Å ( $\phi = O$ , F, H<sub>2</sub>O) (Tables 5 and 6). The Si–O sheets connect *via* A and B polyhedra and hydrogen bonding (Fig. 2). The geometry of hydrogen bonding is in accord with the geometry of hydrogen bonding in fluorapophyllite-(K) (Chao 1971, Ståhl *et al.* 1987).

We write the ideal formula of fluorapophyllite-(Cs) as the sum of cation and anion sites (Table 6),  $CsCa_4(Si_8O_{20})F(H_2O)_8$ , Z=2. Fluorapophyllite-(Cs) is isostructural with fluorapophyllite-(K) and is a Cs-analogue of fluorapophyllite-(K) (Table 9).

## ACKNOWLEDGMENTS

We thank Associate Editor Jim Evans and an anonymous reviewer for the comments which helped to improve the manuscript. We thank David Herbert (Department of Chemistry, University of Manitoba) for use of the Bruker D8 QUEST ECO CMOS diffractometer for collection of the single-crystal Xray data for fluorapophyllite-(Cs) and Mark A. Cooper for processing the single-crystal data. This work was supported by a Graduate Fellowship from the University of Manitoba to Maxwell C. Day and by a Discovery Grant from the Natural Sciences and Engineering Research Council of Canada and by Innovation Grants from the Canada Foundation for Innovation to Frank C. Hawthorne.

Mineral	Fluorapophyllite-(Cs)	Fluorapophyllite-(K)		Fluorapophyllite-(Na)	
Endmember formula, $Z = 2$ Crystal system Space group	CsCa <sub>4</sub> (Si <sub>8</sub> O <sub>20</sub> )F(H <sub>2</sub> O) <sub>8</sub> Tetragonal <i>P</i> 4/mnc	KCa₄(Si <sub>8</sub> O <sub>20</sub> )F Tetragonal <i>P</i> 4/mnc	F(H <sub>2</sub> O) <sub>8</sub>	NaCa <sub>4</sub> (Si <sub>8</sub> O <sub>20</sub> )F(H <sub>2</sub> O) <sub>8</sub> Orthorhombic Pnnm	
a (Å) b	9.060 9.060	8.965* 8.965*	8.970** 8.970**	8.875 8.881	
с V (Å <sup>3</sup> )	15.741 1292.1	15.767* 1267.2*	15.792** 1270.6**	15.79 1236.9	
A-site dominant cation $A-H_2O$ (Å)	Cs 3.152 $ imes$ 8	K 2.971* × 8	K 2.966** × 8	Na 2.763 $ imes$ 4; 2.854 $ imes$ 4	
Optical data	Uniaxial (+)         Uniaxial (+) $\omega = 1.540$ $\omega = 1.530-1.536$ $\omega = 1.544$ $\omega = 1.520.1528$		536	Biaxial (-) $\alpha = 1.536$	
$D_{1}$ (a cm <sup>-3</sup> )	2 54	$\epsilon = 1.002 - 1.0$	30	$\gamma = 1.556$ $\gamma = 1.544$	
$D_{\text{meas.}}$ (g cm <sup>-3</sup> )	2.54 2.513	2.33-2.37		2.30	
Reterences	I his work	** Ståhl <i>et al.</i> (1987) Anthony <i>et al.</i> (1985)		Matsueda <i>et al.</i> (1981)	

TABLE 9. COMPARISON OF F-MEMBERS OF THE APOPHYLLITE GROUP

#### References

- AGAKHANOV, A.A., PAUTOV, L.A., SOKOLOVA, E., HAWTHORNE, F.C., KARPENKO, V.YU., SIIDRA, O.I., & MUFTAKHOV, V.A. (2017a) Odigitriaite, CsNa<sub>5</sub>Ca<sub>5</sub>[Si<sub>14</sub>B<sub>2</sub>O<sub>38</sub>]F<sub>2</sub>, a new cesium borosilicate mineral from the Darai-Pioz alkaline massif, Tajikistan: Description and crystal structure. *Mineralogical Magazine* **81**, 113–122.
- AGAKHANOV, A.A., PAUTOV L.A., SOKOLOVA, E., HAWTHORNE, F.C., KARPENKO, V.YU., SIIDRA, O.I., & GARANIN, V.K. (2017b) Mendeleevite-(Nd), (Cs,□)<sub>6</sub>(□,Cs)<sub>6</sub>(□,K)<sub>6</sub>(REE, Ca)<sub>30</sub>(Si<sub>70</sub>O<sub>175</sub>) (OH,H<sub>2</sub>O,F)<sub>35</sub>, a new mineral from the Darai-Pioz alkaline massif, Tajikistan. *Mineralogical Magazine* 81, 135–141.
- AGAKHANOV, A.A., PAUTOV, L.A., PEKOV, I.V., KARPENKO, V.Y., SIIDRA, O.I., SOKOLOVA, E., HAWTHORNE, F.C., MUFTAKHOV, V.A., & KASATKIN, A.V. (2017c) Gorbunovite, IMA 2017-040. *Mineralogical Magazine* 81, 1280.
- ANTHONY, J.W., BIDEAUX, R.A., BLADH, K.W., & NICHOLS, M.C. (1995) Handbook of Mineralogy. II. Silica, Silicates. Part 1, Mineral Data Publishing, Tucson, Arizona, United States, p. 259.
- BELAKOVSKIY, D.I. (1991) Die seltenen Mineralien von Dara-i-Pioz im Hochgebirge Tadshikistans. Lapis 16(12), 42–48.
- BROWN, I.D. (1981) The bond valence method: an empirical approach to chemical structure and bonding. *In* Structure and Bonding in Crystals II (M. O'Keeffe & A. Navrotsky, eds.). Academic Press, New York, New York, United States (1–30).
- BROWN, I.D. & ALTERMATT, D. (1985) Bond–valence parameters obtained from a systematic analysis of the inorganic crystal structure database. *Acta Crystallographica* B41, 244–247.
- CÁMARA, F., SOKOLOVA, E., ABDU, Y., & HAWTHORNE, F.C. (2010) The crystal structures of niobophyllite, kupletskite-(Cs) and Sn-rich astrophyllite; revisions to the crystal chemistry of the astrophyllite-group minerals. *Canadian Mineralogist* 48, 1–16.
- CHAO, G.Y. (1971) The refinement of the crystal structure of apophyllite. II Determination of the hydrogen positions by X-ray diffraction. *American Mineralogist* 56, 1234–1242.
- DUNN, P.J. & WILSON, W.E. (1978) Nomenclature revisions in the apophyllite group: hydroxyapophyllite, apophyllite, fluorapophyllite. *Mineralogical Record* 3, 95–98.
- DUSMATOV, V.D. (1968) On mineralogy of one alkaline massif. In Alkaline Rocks of Kirgizia and Kazakhstan. Ilym, Frunze, Russia (134–135) [in Russian].
- DUSMATOV, V.D. (1971) Mineralogy of the Darai-Pioz Alkaline Massif (Southern Tien-Shan). Ph.D. dissertation, Institute of Mineralogy, Geochemistry and Crystal Chemistry of Rare Elements, Moscow, 171 pp. [in Russian].
- FAIZIEV, A.R., GAFUROV, F.G., & SHARIPOV, B.N. (2010) Carbonatites of the Darai-Pioz alkaline massif, Central

Tadjikistan, and their compositional features. *Geochemistry International* **48(11)**, 1084–1096.

- HATERT, F., MILLS, S.J., PASERO, M., & WILLIAMS, P.A. (2013) CNMNC guidelines for the use of suffixes and prefixes in mineral nomenclature, and for the preservation of historical names. *European Journal of Mineralogy* 25, 113–115.
- MANDARINO, J.A. (1981) The Gladstone-Dale relationship. IV. The compatibility concept and its application. *Canadian Mineralogist* 41, 989–1002.
- MATSUEDA, H., MIURA, Y., & RUCKLIDGE, J. (1981) Natroapophyllite, a new orthorhombic sodium analog of apophyllite. Description, occurrence and nomenclature. *American Mineralogist* 66, 410–423.
- MOSKVIN, A.V. (1937) Geography and Geology of East Karategin. In Tajik-Pamir expedition of 1935. Academy of Sciences of USSR, Moscow–Leningrad, Russia (682– 739) [in Russian].
- PAUTOV, L.A., AGAKHANOV, A.A., PEKOV, I.V., KARPENKO, V.Y., SIIDRA, O.I., SOKOLOVA, E., HAWTHORNE, F.C., & FAIZIEV, A.R. (2017) Garmite, IMA 2017-008. *Mineralogical Magazine* 81, 740.
- POUCHOU, J.L. & PICHOIR, F. (1985) 'PAP' φ(ρZ) procedure for improved quantitative microanalysis. *In* Microbeam Analysis (J.T. Armstrong, ed.). San Francisco Press, San Francisco, California, United States (104–106).
- REGUIR, E.P., CHAKHMOURADIAN, A.R., & EVDOKIMOV, M.D. (1999) The mineralogy of a unique baratovite- and miserite-bearing quartz – albite – aegirine rock from the Dara-i-Pioz complex, northern Tajikistan. *Canadian Min*eralogist **37**, 1369–1384.
- SEMENOV, E.I. & DUSMATOV, V.D. (1975) On mineralogy of the Darai-Pioz alkaline massif (Central Tajikistan). *Doklady Akademii nauk Tadzhikskoi SSR* XVIII(11), 39–41 [in Russian].
- SHELDRICK, G.M. (2015) Crystal Structure refinement with SHELX. Acta Crystallographica C71, 3–8.
- STÅHL, K., KVICK, Å., & GHOSE, S. (1987) A neutron diffraction and thermogravimetric study of the hydrogen bonding and dehydration behaviour in fluorapophyllite, KCa<sub>4</sub> (Si<sub>8</sub>O<sub>20</sub>)F·8H<sub>2</sub>O, and its partially dehydrated form. *Acta Crystallographica* B43, 517–523.
- WILSON, A.J.C., Ed. (1992) International Tables for Crystallography. Volume C: Mathematical, physical and chemical tables. Kluwer Academic Publishers, Dordrecht, Netherlands.
- YEFIMOV, A.F., DUSMATOV, V.D., GANZEYEV, A.A., & KATAYEVA, Z.T. (1971) Cesium kupletskite, a new mineral. Doklady of the Academy of Sciences U.S.S.R., Earth Sciences 197, 140–143.
- Received May 9, 2019. Revised manuscript accepted August 10, 2019.