Article



Acmonidesite, a new ammonium sulfate chloride from La Fossa crater, Vulcano, Aeolian Islands, Italy

Francesco Demartin, Carlo Castellano and Italo Campostrini

Università degli Studi di Milano, Dipartimento di Chimica, via Golgi 19, I-20133 Milano, Italy

Abstract

The new mineral acmonidesite, $(NH_4,K,Pb^{2+},Na)_9Fe_4^{2+}(SO_4)_5Cl_8$, was found in an active fumarole (fumarole FA, temperature ~250°C) at La Fossa crater, Vulcano, Aeolian Islands, Sicily, Italy. It occurs on a pyroclastic breccia as brown prismatic crystals up to 0.10 mm long, in association with salammoniac, alunite and adranosite. The mineral is orthorhombic, space group C222₁ (no. 20) with *a* = 9.841(1), *b* = 19.448(3) *c* = 17.847(3) Å, *V* = 3415.7(9) Å³ and *Z* = 4. The six strongest reflections in the powder X-ray diffraction pattern are: $[d_{obs} \text{ in } Å(I)(hkl)]$ 8.766(100)(110), 1.805(88)(390), 5.178(45)(131), 4.250(42)(221), 2.926(42)(330) and 2.684(32)(261). The empirical formula (based on 28 anions per formula unit [pfu]) is $(NH_4)_{5.77}K_{1.42}Pb_{0.62}Na_{1.24}Fe_{3.96}Mn_{0.08}S_{5.04}O_{20.16}Cl_{7.97}Br_{0.08}$. The idealised formula is $(NH_4,K,Pb^{2+},Na)_9Fe_4^{2+}(SO_4)_5Cl_8$. The calculated density is 2.551 g cm⁻³. Using single-crystal diffraction data, the structure was refined to a final *R*(*F*) = 0.0363 for 4614 independent observed reflections [*I* > 2 σ (*I*)]. The structure contains two independent, distorted octahedral iron sites, Fe1 and Fe2, with the iron atoms in the 2+ oxidation state, as confirmed by the interatomic distances and bond-valence calculations (2.06 and 1.94 vu, respectively). Fe1 is surrounded by two chlorine atoms and four oxygens of the sulfate ions, with the following average distances (Å): Fe1-O 2.125 and Fe1-Cl 2.472; and Fe2 is surrounded by three chlorine atoms and three oxygens of the sulfate ions, with the iron polyhedra to form a three-dimensional structure containing voids occupied by four independent ammonium ions (two of them partially replaced by K⁺), one Na⁺/Pb²⁺ site and one Cl⁻ ion.

Keywords: acmonidesite, new mineral species, volcanic sublimate, crystal structure, Vulcano Island, Italy

(Received 22 December 2017; accepted 7 February 2018)

Introduction

Ammonium sulfate chlorides are quite rare (see for instance rruff.info/ima/), the only examples known to date seem to have been found as sublimates at Vulcano Island, Aeolian Islands, Sicily, Italy (Campostrini *et al.*, 2011), i.e. adranosite (Demartin *et al.*, 2010), adranosite-(Fe) (Mitolo *et al.*, 2013) and therasiaite (Demartin *et al.*, 2014). Acmonidesite (NH₄,K,Pb²⁺,Na)₉Fe₄²⁺ (SO₄)₅Cl₈, is an additional new mineral of this kind recently found in the fumaroles at the same locality. This mineral was approved as a new species by the International Mineralogical Association Commission on New Minerals, Nomenclature and Classification (IMA2013-068, Demartin *et al.*, 2013). The name is from Acmonides (from the Greek Aκμωνυδης), cited by Ovidius as one of the Cyclops, who were helpers of Hephaistos, the mythological god of fire whose forge was alleged to be located at Vulcano.

This paper deals with the description of the new mineral, together with its crystal structure determination.

Occurrence, chemical data and physical properties

Acmonidesite is a volcanic sublimate found at La Fossa crater, Vulcano, Aeolian Islands, Sicily, Italy, in an active fumarole [fumarole FA, reported in Borodaev et al. (2000) and Pinto et al. (2006)] that occurs on a pyroclastic breccia as brown prismatic crystals up to 0.10 mm long, in association with salammoniac NH₄Cl, alunite KAl₃(SO₄)₂(OH)₆ and adranosite $(NH_4)_4NaAl_2(SO_4)_4Cl(OH)_2$, (Fig. 1). The most commonly observed forms are: {1 0 0}, {1 2 0}, {0 1 1}, {0 1 0} and {1 0 2}; such an indexing has been obtained by comparison of computergenerated drawings of the crystals. No twinning is apparent. The a:b:c ratio calculated from the unit-cell parameters is 0.5060:1:0.9177 (single-crystal data). The streak is light brown and the lustre is vitreous. Cleavage and fracture were not observed. No fluorescence was observed under both shortwave and longwave ultraviolet radiation. A measurement of the density, obtained by flotation in a diiodomethane-benzene solution, gives the value of 2.56(1) g cm⁻³. The density calculated using the empirical formula and single-crystal unit-cell data is 2.551 g cm^{-3} .

Acmonidesite is biaxial (+) with α = 1.580(2), β = 1.590(2) and γ = 1.635(2) (white light), measured with a spindle stage. 2V (meas) = 53(3)° and 2V(calc) = 51.6°. Orientation is *X* = *c*, *Y* = *b*, *Z* = *a*. Taking into account the empirical chemical formula and the density based on it, the calculated mean refractive index is

Author for correspondence: Francesco Demartin, Email: francesco.demartin@unimi.it Associate Editor: Giancarlo Della Ventura

Cite this article: Demartin F., Castellano C. and Campostrini I. (2019) Acmonidesite, a new ammonium sulfate chloride from La Fossa crater, Vulcano, Aeolian Islands, Italy. *Mineralogical Magazine*, **83**, 137–142. https://doi.org/10.1180/mgm.2018.115

[©] Mineralogical Society of Great Britain and Ireland 2018



Fig. 1. Back-scattered electron image of crystals of acmonidesite with alunite and a crystal drawing with indexing of the faces.

1.602, using the Gladstone-Dale constants of Mandarino (1976, 1981). The compatibility index $1-(K_p/K_c) = 0.033$ is rated as excellent. Dispersion could not be observed because of the intense brown colour of the mineral.

Quantitative chemical analyses (8) were carried out in energydispersive spectroscopy (EDS) mode using a JEOL JSM 5500 LV scanning electron microscope equipped with an IXRF EDS 2000 microprobe (20 kV excitation voltage, 10 pA beam current and 2 µm beam diameter). The analytical method was chosen because it was impossible to prepare a flat polished sample and the crystal is severely damaged by using the wavelength-dispersive spectroscopy technique, even with a low voltage and current and a large diameter beam. Element concentrations were measured using the $K\alpha$ lines for S, K, Na, Fe, Mn and Cl, the $L\alpha$ line for Br and the $M\alpha$ line for Pb. The presence of ammonium was established from crystal-structure analysis, confirmed by the Fourier-transform infrared (FTIR) spectrum (Fig. 2) as well as by the EDS spectrum (Fig. 3). The IR spectrum was recorded on a Jasco IRT-3000 spectrometer and shows strong absorption bands related to the presence of ammonium at 3214 (broad),



X-ray data

Powder X-ray diffraction data (Table 2) have been obtained using a Rigaku DMAX II diffractometer, with graphite monochromatised CuK α radiation. The indexing of the powder-diffraction pattern was made by comparison with the pattern calculated after the structure determination. The following unit-cell parameters a =9.840(1), b = 19.455(2), c = 17.847(2) Å and V= 3416.6(5) Å³



Fig. 2. FTIR spectrum of acmonidesite.



 $\ensuremath{\textit{Fig. 3.}}$ A portion of the EDS spectrum, where the presence of the ammonium nitrogen is evident.

Table 1. Analytical data for acmonidesite (average of 8 analyses).*

Constituent	Wt.%	Range	S.D.	Probe standard
(NH ₄) ₂ O**	11.05			
K ₂ 0	4.91	4.28-6.14	0.27	KBr
Na ₂ O	2.82	2.28-3.54	0.22	Natural albite
FeO	20.93	19.51-21.88	0.25	Natural almandine garnet
MnO	0.42	0.15-1.24	0.10	Natural almandine garnet
PbO	10.25	7.03-12.23	0.99	Phosgenite
SO3	29.67	27.46-32.51	0.37	Synthetic anhydrite
Cl	20.80	18.42-23.46	0.50	Phosgenite
Br	0.45	0.36-0.51	0.20	KBr
O=Cl	-4.75			
Total	96.55			

*The empirical formula (based on 28 anions pfu) is $(NH_4)_{5.77}K_{1.42}Pb_{0.62}Na_{1.24}Fe_{3.96}Mn_{0.08}S_{5.04}O_{20.16}Cl_{7.97}Br_{0.08}$. The simplified formula is $(NH_4,K,Pb^{2+},Na)_5Fe_4^{2+}(SO_4)_5Cl_8$. S.D. – standard deviation; **from structure solution.

were derived from least-squares refinement from the above data using the program *UNITCELL* (Holland and Redfern, 1997).

Single-crystal diffraction data were collected using a Bruker Apex II diffractometer with MoK α radiation ($\lambda = 0.71073$ Å). Some 17,663 intensities were measured up to $2\theta = 63.03^{\circ}$, of which 5336 were unique ($R_{int} = 0.0501$). A SADABS absorption correction was applied (Sheldrick, 2000) ($\mu = 5.95 \text{ mm}^{-1}$). On the basis of systematic absences the space group $C222_1$ (no. 20) was selected unambiguously, in agreement also with statistical tests on the distribution of the *E* values $[|E^2-1| = 0.781]$ and confirmed by satisfactory structure solution and refinement. The structure was solved by direct methods and refined using the SHELXL-2017 program (Sheldrick, 2008) implemented in the WinGX suite (Farrugia, 1999) to a final R = 0.0363 for 4614 observed reflections $[I > 2\sigma(I)]$ (Table 3). A refinement of the occupancies of the N and Na sites revealed in two of them a significant substitution of the ammonium ions by K^+ and of Na^+ by Pb^{2+} , as shown in Table 4, whereas no occupancy was refined for the Fe and Cl sites, due to only small amounts of Mn and Br replacing Fe and Cl, respectively. The formula resulting from the structure refinement is (NH₄)_{5.77}K_{1.22}Pb_{0.64}Na_{1.36}Fe₄(SO₄)₅Cl₈ (corresponding to 17.63 positive charges for the cations and 18 negative charges for the anions). It seems satisfactory in view of the approximations introduced for the atomic scattering factors of mixed sites. The positions of all the hydrogen atoms of the ammonium ion could not be detected from a difference-Fourier map due to local

Table 2. X-ray powder diffraction data for acmonidesite.

Crystal data Chemical formula Cl₈H_{23.08}Fe₄K_{1.23}N_{5.77}Na_{1.37}O₂₀Pb_{0.63}S₅ Orthorhombic, C222₁ (no. 20) Crystal system, space group Temperature (K) 294 a (Å) 9.841(1) b (Å) 19,448(3) c (Å) 17.847(3) V (Å³) 3415.7(9) 7 4 D_{calc} (g cm⁻³) 2.551 Data collection Instrument APEX II CCD diffractometer Absorption correction Empirical (SADABS, Sheldrick, 2008) Radiation, wavelength (Å) ΜοΚα, 0.71073 u (mm⁻¹) 5.95 Measured reflections 17,663 0.0501 R_{int} Independent reflections 5336 Observed reflections $[I > 2\sigma(I)]$ 4614 Refinement Parameters refined 214 Final $R [I > 2\sigma(I)]$ and wR2 (all data) 0.0363, 0.0945 GoF 1.037

Table 3. Single-crystal diffraction data and refinement parameters for

acmonidesite.

 $\Delta \rho_{max}$, $\Delta \rho_{min}$ (e Å⁻³)

Notes: $R = \Sigma ||Fo|-|Fc|| / \Sigma |Fo|$; wR2 = { $\Sigma [w(Fo^2 - Fc^2)^2] / \Sigma [w(Fo^2)^2]$ }^{1/2}; w = 1/[$\sigma^2(Fo^2) + (0.0563q)^2$] where $q = [max(0, Fo^2) + 2Fc^2]/3$; GoF = { $\Sigma [w(Fo^2 - Fc^2)] / (n - p)$ }^{1/2} where n is the number of reflections and p is the number of refined parameters.

1.44. - 0.86

disorder. The value of the Flack parameter, 0.228(8), confirms the correctness of the absolute structure, considering the fact that the crystal is partially twinned and a *TWIN* refinement was carried out (twin matrix $[\bar{1} \ 0 \ 0], [0 \ \bar{1} \ 0], [0 \ 0 \ \bar{1}]$ and components ratio 0.772 (8)/0.228(8)). The coordinates and displacement parameters of the atoms are reported in Table 4; selected interatomic distances are listed in Table 5. The crystallographic files have been deposited with the Principal Editor of *Mineralogical Magazine* and are available as Supplementary material (see below).

Description of the structure and discussion

The structure of acmonidesite (Fig. 4) contains two independent, distorted octahedral iron sites, Fe1 and Fe2, with the iron atoms in the 2+ oxidation state, as confirmed by the range of interatomic distances and bond-valence calculations (2.06 and 1.94 valence

I _{obs}	I_{calc}	$d_{ m obs}$ (Å)	$d_{\rm calc}$ (Å)*	h k l	I _{obs}	I_{calc}	$d_{ m obs}$ (Å)	$d_{\rm calc}$ (Å)*	h k l	I _{obs}	I_{calc}	$d_{ m obs}$ (Å)	$d_{\rm calc}$ (Å)*	h k l
12	10	9.704	9.727	020	26	25	3.346	3.351	025	9	3	2.175	2.174	028
37	40	9.049	8.924	002	9	10	3.275	3.288	044	2	2	2.136	2.135	084
100	88	8.766	8.781	110	23	20	3.230	3.234	310	3	3	2.023	2.026	405
1	18	8.544	8.541	021	29	1	3.203	3.190	061	2	5	1.992	1.989	228
14	100	7.860	7.879	111	21	20	3.085	3.091	153	13	10	1.858	1.856	267
22	38	6.570	6.576	022	18	20	2.983	2.980	135	10	8	1.814	1.817	195
45	38	5.178	5.182	131	24	39	2.969	2.975	006	88	10	1.805	1.805	390
9	4	4.850	4.864	040	42	60	2.926	2.927	330	24	20	1.797	1.796	391
42	30	4.250	4.263	221	10	19	2.833	2.842	313	2	3	1.768	1.766	446
13	3	4.044	4.056	024	13	50	2.804	2.810	154	4	5	1.683	1.684	553
1	1	3.776	3.765	043	32	20	2.684	2.677	261	9	7	1.662	1.661	483
25	3	3.605	3.618	150	5	20	2.444	2.447	334	2	1	1.615	1.613	602
14	2	3.449	3.443	134	2	8	2.304	2.304	422					
8	2	3.407	3.396	241	27	5	2.266	2.264	207					

*Calculated from the unit cell a = 9.840(1), b = 19.455(2), c = 17.847(2) Å and V = 3416.6(5) Å³, obtained from least-squares refinement of the above data using the program UNITCELL (Holland and Redfern, 1997).

Table 4. Final atom coordinates and equivalent isotropic displacement parameters (Å^2).*

Atom	Wyck.	Occupancy	x/a	y/b	z/c	U _{eq}	U^{11}	U ²²	U ³³	U ²³	U ¹³	U ¹²
Fe1	8 <i>c</i>	1	0.06089(8)	0.09769(4)	0.14882(4)	0.01876(18)	0.0211(4)	0.0192(4)	0.0159(3)	0.0004(3)	0.0005(3)	0.0014(3)
Fe2	8 <i>c</i>	1	0.32631(7)	0.15792(4)	-0.00614(5)	0.01962(17)	0.0188(3)	0.0135(3)	0.0265(4)	0.0005(3)	0.0002(3)	-0.0024(2)
S1	8 <i>c</i>	1	0.19697(12)	0.00302(8)	0.28715(7)	0.0218(3)	0.0175(5)	0.0299(7)	0.0180(5)	0.0047(6)	0.0000(4)	0.0030(6)
S2	8 <i>c</i>	1	-0.01601(12)	0.18634(6)	-0.00283(7)	0.0165(2)	0.0197(5)	0.0120(5)	0.0179(5)	0.0015(5)	-0.0001(5)	0.0030(4)
S3	4 <i>a</i>	1	0.16498(15)	0	0	0.0138(3)	0.0144(6)	0.0115(6)	0.0154(6)	-0.0010(7)	0	0
01	8 <i>c</i>	1	0.3439(5)	0.0072(4)	0.2850(3)	0.0652(19)	0.019(2)	0.135(6)	0.041(3)	-0.015(4)	-0.005(2)	0.002(4)
02	8 <i>c</i>	1	0.1430(5)	0.0169(2)	0.2111(2)	0.0314(10)	0.043(2)	0.032(2)	0.0191(18)	-0.0001(16)	-0.0069(17)	0.0071(19)
03	8 <i>c</i>	1	0.1508(6)	-0.0668(3)	0.3071(3)	0.0521(15)	0.058(3)	0.028(3)	0.070(4)	0.016(3)	0.022(3)	0.007(2)
04	8 <i>c</i>	1	0.1425(4)	0.0534(2)	0.3402(2)	0.0309(9)	0.027(2)	0.040(3)	0.025(2)	-0.0069(18)	-0.0004(17)	0.0030(19)
05	8 <i>c</i>	1	0.1255(4)	0.2045(3)	-0.0185(3)	0.0431(13)	0.022(2)	0.041(3)	0.065(4)	0.027(2)	0.009(2)	0.0043(19)
06	8 <i>c</i>	1	-0.1040(5)	0.2458(2)	-0.0174(3)	0.0373(11)	0.036(2)	0.020(2)	0.057(3)	0.0018(19)	-0.007(2)	0.0120(18)
07	8 <i>c</i>	1	-0.0601(7)	0.1307(3)	-0.0515(3)	0.0499(14)	0.078(4)	0.025(2)	0.047(3)	-0.013(2)	-0.021(3)	0.003(3)
08	8c	1	-0.0306(5)	0.1659(3)	0.0756(3)	0.0403(12)	0.038(2)	0.056(3)	0.027(2)	0.021(2)	0.0080(19)	0.017(2)
09	8c	1	0.2498(5)	0.0580(2)	-0.0234(3)	0.0445(14)	0.053(3)	0.026(2)	0.055(3)	-0.015(2)	0.029(2)	-0.025(2)
010	8c	1	0.0781(4)	0.0199(2)	0.0631(2)	0.0266(8)	0.029(2)	0.031(2)	0.0197(17)	-0.0094(15)	0.0048(16)	-0.0067(17)
Cl1	8 <i>c</i>	1	0.29077(14)	0.14689(7)	0.13413(8)	0.0259(3)	0.0251(6)	0.0237(6)	0.0289(7)	-0.0002(5)	-0.0012(5)	-0.0023(5)
Cl2	4 <i>b</i>	1	0	0.17900(10)	1/4	0.0295(4)	0.0455(12)	0.0206(9)	0.0225(9)	0	0.0078(8)	0
Cl3	8 <i>c</i>	1	0.3433(2)	0.16197(9)	-0.14856(9)	0.0400(4)	0.0568(11)	0.0327(8)	0.0304(8)	0.0040(6)	-0.0020(7)	0.0097(8)
Cl4	8 <i>c</i>	1	0.55827(13)	0.10510(7)	0.00109(9)	0.0299(3)	0.0226(5)	0.0294(7)	0.0375(7)	-0.0006(7)	-0.0006(6)	0.0043(5)
Cl5	4 <i>b</i>	1	0	-0.21271(12)	1/4	0.0408(5)	0.0432(13)	0.0323(12)	0.0469(13)	0	0.0120(10)	0
Na/Pb	8 <i>c</i>	0.68(1)/0.32(1)	0.07476(6)	-0.10348(3)	0.15782(3)	0.0251(2)	0.0262(3)	0.0234(3)	0.0256(3)	-0.0053(2)	-0.0012(2)	0.0006(2)
N1/K1	4 <i>a</i>	0.74(1)/0.26(1)	-0.1854(4)	0	0	0.0304(14)	0.0213(19)	0.033(2)	0.037(2)	-0.007(2)	0	0
N2/K2	8 <i>c</i>	0.52(1)/0.48(1)	0.43348(19)	0.00093(12)	-0.13237(11)	0.0288(7)	0.0265(10)	0.0298(11)	0.0302(11)	-0.0014(9)	0.0049(7)	0.0018(10)
N3	8 <i>c</i>	1	0.1904(6)	0.3092(3)	0.1455(3)	0.0367(13)	0.037(3)	0.027(3)	0.046(3)	0.003(2)	-0.005(3)	0.002(2)
N4	8c	1	-0.3063(6)	0.1870(3)	0.1444(3)	0.0348(12)	0.039(3)	0.025(3)	0.040(3)	-0.006(2)	-0.001(2)	0.002(2)

The anisotropic displacement factor exponent takes the form: $-2\pi^2 (U^{11}h^2(a^)^2+...+2U^{12}hka^*b^*+...); U_{eq}$ according to Fischer and Tillmans (1988). Wyck. – Wyckoff site.

Table 5. Selected interatomic distances (Å) and bond valences* (BV, vu) in acmonidesite.

Table 5. (Continued.)

	Distance (Å)	BV (vu)		Distance (Å)	BV (vu)
Fe1-02	2.086(4)	0.386	Fe2-05	2.185(4)	0.296
Fe1–O4 ^a	2.188(4)	0.293	Fe2–O6 ^b	2.039(4)	0.438
Fe1-08	2.068(4)	0.405	Fe2-09	2.107(4)	0.365
Fe1-010	2.158(4)	0.318	Fe2–Cl1	2.537(2)	0.275
Fe1–Cl1	2.470(2)	0.330	Fe2–Cl3	2.549(2)	0.267
Fe1–Cl2	2.474(2)	0.327	Fe2–Cl4	2.507(1)	0.299
<fe1-φ></fe1-φ>	2.241	$\Sigma = 2.059$	<fe2-φ></fe2-φ>	2.321	$\Sigma = 1.940$
N1/K1-07	2.970(6)	0.122	Na/Pb-O2	2.615(4)	0.160
N1/K1-07 ^c	2.970(6)	0.122	Na/Pb-O3	2.857(6)	0.091
N1/K1–O4 ^f	3.064(4)	0.095	Na/Pb-O10	2.935(4)	0.076
$N1/K1-O4^{g}$	3.064(4)	0.095	Na/Pb–O3 ^a	2.414(6)	0.258
N1/K1-O10	2.853(5)	0.166	Na/Pb–O5 ^c	3.207(6)	0.040
N1/K1-O10 ^c	2.853(5)	0.166	Na/Pb–07 ^c	2.375(6)	0.282
N1/K1-08 ^c	3.814(6)	0.013	Na/Pb–O9 ^c	3.084(6)	0.053
N1/K1–Cl4 ^d	3.247(3)	0.167	Na/Pb–Cl3 ^c	2.882(2)	0.259
N1/K1–Cl4 ^e	3.247(3)	0.167	Na/Pb–Cl5	2.786(2)	0.202
<n1 k1-φ=""></n1>	3.120	$\Sigma = 1.113$	<na pb-φ=""></na>	2.795	Σ = 1.421
N2/K2-01 ^h	2.646(5)	0.261	N3-03 ⁱ	2.996(8)	0.123
N2/K2-O1 ^c	2.868(5)	0.147	N3-05	3.623(8)	0.023
N2/K2-O2 ^c	3.204(5)	0.062	N3-06 ^b	3.235(8)	0.064
N2/K2-O9	2.878(5)	0.143	N3–07 ^b	3.195(8)	0.072
N2/K2-O9 ^c	3.508(6)	0.029	N3-08	3.749(8)	0.016
N2/K2-Cl3	3.268(3)	0.146	N3-Cl1	3.313(6)	0.153
N2/K2-Cl4	3.359(3)	0.118	N3-Cl2	3.661(6)	0.060
N2/K2-Cl1 ^c	3.200(3)	0.171	N3-Cl3 ^m	3.733(6)	0.049
N2/K2–Cl4 ^c	3.354(3)	0.119	N3–Cl3 ^j	3.462(6)	0.103
<n2 k2-φ=""></n2>	3.143	$\Sigma = 1.196$	N3–Cl4 ^j	3.363(6)	0.134
			N3-Cl5 ⁿ	3.598(6)	0.071
N4-01 ^a	3.736(10)	0.017	N3-Cl5 ⁱ	3.598(6)	0.071
N4-04 ^a	3.071(7)	0.100	<n3-φ></n3-φ>	3.460	$\Sigma = 0.939$
N4–05 ^j	3.153(7)	0.080			
					(Continued)

	Distance (Å)	BV (vu)		Distance (Å)	BV (vu)
N4-06	3.688(8)	0.019	S1-01	1.448(5)	1.609
N4-08	3.006(7)	0.120	S1-02	1.483(4)	1.464
N4–Cl3 ^j	3.286(6)	0.165	S1-03	1.475(5)	1.492
N4–Cl4 ^d	3.294(6)	0.162	S1-04	1.464(4)	1.541
N4–Cl5 ^k	3.315(6)	0.153	<\$1-0>	1.468	$\Sigma = 6.106$
N4–Cl5 ^l	3.315(6)	0.153			
<Ν4-φ>	3.318	$\Sigma = 0.969$	S2-05	1.464(4)	1.541
			S2-06	1.467(4)	1.529
S3-09	1.463(4)	1.545	S2-07	1.455(5)	1.579
S3-010	1.466(4)	1.533	S2-08	1.462(4)	1.549
S3-09 ^c	1.463(4)	1.545	<s2-0></s2-0>	1.462	$\Sigma = 6.198$
S3-010 ^c	1.466(4)	1.533			
<s3-0></s3-0>	1.465	$\Sigma = 6.156$			

Symmetry codes: a = -x, y, 1/2-z; b = x + 1/2, 1/2-y, -z; c = x, -y, -z; d = x-1, y, z; e = x-1, -y, -z; f = -x, -y, z-1/2; g = -x, y, 1/2-z; h = 1-x, -y, z-1/2; i = 1/2-x, y + 1/2, 1/2-z; j = x-1/2, 1/2-y, -z; k = x-1/2, y + 1/2, z; l = -x-1/2, y + 1/2, 1/2-z, m = 1/2-x, 1/2-y, z + 1/2, n = x + 1/2, y + 1/2, z. *Bond-valence parameters from Brown and Altermatt (1985) and Brown (2009).

units (vu), respectively). Fe1 is surrounded by two chlorine atoms and four oxygens of the sulfate ions, with the following average distances: Fe1–O 2.125 Å and Fe1–Cl 2.472 Å; and Fe2 is surrounded by three chlorine atoms and three oxygens of the sulfate ions, with the following average distances: Fe2–O 2.111 Å and Fe2–Cl 2.531 Å. The structural type of acmonidesite is unprecedented and displays finite clusters made by four Fe vertex-sharing distorted octahedra and sulfate tetrahedra (Fig. 5), interacting each other only through the sulfate anions. Iron octahedra linked *via* vertices to form infinite chains encased from both sides by SO₄ tetrahedra are also present in parabutlerite (Plášil *et al.*, 2017), however, in acmonidesite each couple of adjacent

Downloaded from https://pubs.geoscienceworld.org/minmag/article-pdf/83/1/137/4662360/s0026461x18001159a.pdf



Fig. 4. Perspective view of the structure of acmonidesite seen almost along [100]. Green octahedra: Fe^{2*} ; yellow tetrahedra: SO_4^{2-} ; blue spheres: NH_4^+ ; orange spheres: Na^*/Pb^{2*} ; magenta sphere: NH_4^+/K^* ; and green spheres: Cl5.



Fig. 5. Perspective view of the discrete cluster of iron and sulfate polyhedra observed in acmonidesite.

octahedra is bridged by two sulfate anions instead of by one. The three independent sulfate anions, one of which located on a two-fold axis (S3), are connected to the Fe polyhedra and to the other cations as shown in Fig. 6. The S1 sulfate shares two

vertices of the tetrahedron with two symmetry-related Fe1 polyhedra of the same cluster. The S2 sulfate shares two vertices with Fe1 and Fe2 polyhedra of the same cluster and one with a Fe2 of an adjacent cluster. The S3 one shares two of the four vertices with Fe1 and Fe2 octahedra of the same cluster and the other two with the corresponding Fe1 and Fe2 polyhedra related by two-fold symmetry. Voids within the three-dimensional framework determined by the arrangement of these clusters are occupied by four independent ammonium ions (two of them partially replaced by K⁺), by one Na⁺ cation, partially substituted by Pb²⁺ and one Cl⁻ anion (Cl5). The larger voids are those occupied by ammonium only (average radius of the cage 3.32-3.46 Å) or by ammonium plus potassium (average radius 3.12-3.14 Å). The smallest (average radius 2.79 Å) are occupied by Na⁺ and Pb^{2+} , as expected by the ionic radii of these cations. Bond-valence calculations (Table 5) are in agreement with the structure model proposed. The value of 1.421 vu obtained for the Na/Pb site accounts for the presence of an amount of the divalent Pb²⁺ cation.

The ammonium ions interact with the surrounding sulfate oxygens and chloride ions via hydrogen bonds. The three sulfate anions display S–O distances ranging from 1.448(5) to 1.483(4) Å with an overall average distance of 1.465 Å, not significantly different from the grand mean S–O distance reported by Hawthorne *et al.* (2000).

In spite of the similar chemical composition with adranosite-(Fe) and therasiaite, no topological relationship of acmonidesite with them is evident. In adranosite-(Fe) iron is present only in the 3+ oxidation state, and its polyhedron does not contain chlorine which is instead coordinated to Na; the FeO₄(OH)₂ distorted octahedra and sulfate tetrahedra are linked to form helicoidal chains extending along [001]. Two different oxidation states for iron are instead present in therasiaite, where three chlorides and three oxygens of the sulfate anions are octahedrally coordinated to the metal centre thus forming $[Fe_2(SO_4)_3Cl_5^{6-}]_n$ infinite chains along [001].

The occurrence of acmonidesite in the fumaroles at La Fossa crater, together with other rare and unique minerals containing ammonium, is an additional example of the singularity of this locality and provides further information in the study of the overall geochemical context of this environment. The presence of these minerals as volcanic sublimates emphasises a high activity of free ammonia and volatile chlorides in the gas phase that prevent dissociation of such minerals, which would be otherwise unstable at the observed temperature.



Fig. 6. The environment about the three independent sulfate anions.

Supplementary material. To view supplementary material for this article, please visit https://doi.org/10.1180/mgm.2018.115.

Acknowledgements. The authors are most indebted to Prof. Silvia Bruni for the FTIR measurements and to the referees Sergey Krivovichev, Peter Leverett and an anonymous referee for useful suggestions.

References

- Borodaev Y.S., Garavelli A., Garbarini C., Grillo S.M., Mozgova N.N., Organova N.I., Trubkin N.V. and Vurro F. (2000) Rare sulfosalts from Vulcano, Aeolian Islands, Italy. III. Wittite and cannizzarite. *The Canadian Mineralogist*, **38**, 23–34.
- Brown I.D. (2009) Recent developments in the methods and applications of the bond valence model. *Chemical Reviews*, **109**, 6858–6919.
- Brown I.D. and Altermatt D. (1985) Bond-valence parameters from a systematic analysis of the inorganic crystal structure database. Acta Crystallographica, B41, 244–247.
- Campostrini I., Demartin F., Gramaccioli C.M. and Russo M. (2011) Vulcano. Tre secoli di mineralogia. Associazione Micro-mineralogica Italiana (editors), Cremona, Italy, 344 pp, ISBN 978-88-905541-0-0.
- Demartin F., Gramaccioli C.M. and Campostrini I. (2010) Adranosite, (NH₄)₄NaAl₂(SO₄)₄Cl(OH)₂, a new ammonium sulfate chloride from La Fossa Crater, Vulcano, Aeolian Islands, Italy. *The Canadian Mineralogist*, **48**, 315–321.
- Demartin F., Campostrini I. and Castellano C. (2013) Acmonidesite, IMA 2013-068. CNMNC Newsletter No. 18, December 2013, page 3250; *Mineralogical Magazine*, 77, 3249–3258.
- Demartin F., Castellano C. and Campostrini I. (2014) Therasiaite, (NH₄)₃KNa₂Fe²⁺Fe³⁺(SO₄)₃Cl₅, a new sulfate chloride from La Fossa Crater, Vulcano, Aeolian Islands, Italy. *Mineralogical Magazine*, **78**, 203–213.

- Farrugia L.J. (1999) WinGX suite for small-molecule single-crystal crystallography. Journal of Applied Crystallography, 32, 837–838.
- Fischer R.X. and Tillmanns E. (1988) The equivalent isotropic displacement factor. *Acta Crystallographica*, C44, 775–776.
- Hawthorne F.C., Krivovichev S.V. and Burns P.C. (2000) The crystal chemistry of sulfate minerals. Pp. 1–112 in: Sulfate Minerals Crystallography, Geochemistry, and Environmental Significance (C.N. Alpers, J.L. Jambor and B.K. Nordstrom, editors). Reviews in Mineralogy and Geochemistry, 40. Mineralogical Society of America and the Geochemical Society, Washington DC.
- Holland T.J.B. and Redfern S.A.T. (1997) Unit cell refinement from powder diffraction data: the use of regression diagnostics. *Mineralogical Magazine*, **61**, 65–77.
- Mandarino J.A. (1976) The Gladstone-Dale relationship I. Derivation of new constants. *The Canadian Mineralogist*, 14, 498–502.
- Mandarino J.A. (1981) The Gladstone-Dale relationship. IV. The compatibility index and its application. *The Canadian Mineralogist*, **19**, 441–450.
- Mitolo D., Demartin F., Garavelli A., Campostrini I., Pinto D., Gramaccioli C.M., Acquafredda P. and Kolitsch U. (2013) Adranosite-(Fe), (NH₄)₄NaFe₂(SO₄)₄Cl(OH)₂, a new ammonium chloride from La Fossa Crater, Vulcano, Aeolian Islands, Italy. *The Canadian Mineralogist*, **51**, 57–66.
- Pinto D., Balić Žunić T., Garavelli A., Garbarino C., Makovický E. and Vurro F. (2006) First occurrence of close-to-ideal kirkiite at Vulcano (Aeolian Islands, Italy): chemical data and single crystal X-ray study. *European Journal of Mineralogy*, 18, 393–401.
- Plášil J., Petřiček V and Majzlan J. (2017) A commensurately modulated structure of parabutlerite, Fe^{III}SO₄(OH)·2H₂O. Acta Crystallographica, B73, 856–862.
- Sheldrick G.M. (2000) SADABS Area-Detector Absorption Correction Program, Bruker AXS Inc., Madison, WI, USA.
- Sheldrick G.M. (2008) A short history of SHELX. Acta Crystallographica, A64, 112–122.